ALUMINUM

5052

MATERIAL / REFERENCE CONDITION

O · H32 · H34

Typical applications Formed covers, chassis and sheet-metal brackets.

Reference product form	Sheet & plate
Data notes	H32 sheet/plate: tensile 215-265 MPa; 0.2% proof strength >= 160 MPa. Elongation depends on thickness. ASTM B209M reference in source.

Original technical reference | Atlas Steels · external reference

View 5052 data sheet (PDF)

atlassteels.com.au | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.