TOOL STEEL

Cr12MoV

MATERIAL / REFERENCE CONDITION

Cold-work tool steel

Typical applications Blanking dies and wear inserts

Material type	Cold-work tool steel
Condition / reference grade	Annealed stock; final hardened and tempered condition to drawing
Manufacturing	Milling · EDM · grinding
Reference data	Selected composition: C 1.45-1.70%; Cr 11.00-12.50%; Mo 0.40-0.60%; V 0.15-0.30%.
Specification notes	Confirm the full specification; do not automatically substitute D2 or SKD11.

Original technical reference | Fushun Metal

Technical reference

www.fushunspecialsteel.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.