ENGINEERING PLASTICS

PEEK

MATERIAL / REFERENCE CONDITION

Polyether ether ketone

Typical applications High-performance bushings and insulating parts

Material type	Polyether ether ketone
Condition / reference grade	TECAPEEK natural (example)
Manufacturing	Machining or molding; confirm grade-specific route
Reference data	Example tensile strength: 116 MPa; tensile modulus: 4200 MPa (ISO 527).
Specification notes	Unfilled reference; glass/carbon-filled grades need their own sheet. Branded examples are references, not a statement of stocked brand.

Original technical reference | Ensinger

Manufacturer grade reference

www.ensingerplastics.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.