ENGINEERING PLASTICS

POM

MATERIAL / REFERENCE CONDITION

Acetal copolymer

Typical applications Gears, bushings and sliding parts

Material type	Acetal copolymer
Condition / reference grade	TECAFORM AH natural (example)
Manufacturing	Machining or molding; confirm grade-specific route
Reference data	Example density 1.41 g/cm3; tensile strength 67 MPa, DIN EN ISO 527-2, 50 mm/min.
Specification notes	Stock-shape data; do not transfer directly to another molded resin or POM-H grade. Branded examples are references, not a statement of stocked brand.

Original technical reference | Ensinger

Manufacturer grade reference

www.ensinger-online.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.