ELASTOMERS

Silicone

MATERIAL / REFERENCE CONDITION

Silicone elastomer / VMQ

Typical applications Molded seals and flexible interfaces

Material type	Silicone elastomer / VMQ
Condition / reference grade	ELASTOSIL LR 3003/50 (example)
Manufacturing	Molding · application-specific finishing
Reference data	Example: 50 Shore A, density 1.13 g/cm3, tensile strength 10.3 MPa (ISO 37 Type 1).
Specification notes	Values apply to the named cured compound. Specify curing and post-curing requirements. Confirm the selected compound before production.

Original technical reference | WACKER

Compound reference

www.wackerconnect.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.