

SECTION 09240
SECTION 098316 (2004 CSI Format)

ACOUSTICAL PLASTER

PART 1 – GENERAL

Section includes interior acoustical plaster finish for ceilings and walls.

1.01 RELATED DOCUMENTS

- A. Drawings and general provisions of the contract, including General and supplementary conditions and Division 1 Specification Sections, apply to this section.

1.02 WORK INCLUDED

- A. This Section includes:

- 1. Field applied premixed Acoustical Plaster as indicated on the drawings.

- B. Related Sections:

Section 05500, Metal Fabrications; structural steel framing system components to support work of this section.

1.03 SUBMITTALS

- A. Product Data: show manufacturer's installation recommendations.
- B. Samples for Verification: samples of finished products showing texture & colour for approval.
- C. Product Test Reports: ASTM-E84 test for flame spread, NRC test per ASTM C-423. Testing performed by laboratory accredited by the National Institute of Standards and Technology NVLAP (National Voluntary Laboratory Accreditation Program).

1.04 SYSTEM PERFORMANCE REQUIREMENTS

- A. Sound absorption at 10 mm thickness shall be 0.50 at 4 KHz frequency.
- B. Average thermal conductivity should be 0.35 W/mK
- C. Thermal Resistance "R value for 15mm thickness: .042 m²k/W.
- D. Heat flow "U value for 15mm thickness: 23.8 W/m²k.
- E. Standard Test Method for compressive strength of Hydraulic cement mortars ASTM C349

1.05 QUALITY ASSURANCE

- A. Installer Qualifications: Engage an experienced installer who has attended a training seminar by this manufacturer. Provide copy of certificate of training.
- B. Single Source Responsibility, provide only proprietary, factory formulated materials as produced or recommended by Saudi Vetonit Co. Ltd.-Saveto. Substitutes within the system are not permitted.

1.06 DELIVERY, STORAGE, AND HANDLING

- A. Deliver materials to project site in original, unopened packages, and store them in a fully enclosed space where they will be protected against damage from moisture, and other harmful conditions.
- B. Inspect materials upon delivery and immediately report to Architect damaged or defective materials.

1.07 PROJECT CONDITIONS

- A. Environmental Limitations: do not install Saveto Acoustic Plaster until spaces are enclosed and weatherproof, wet-work in spaces is complete and dry, work above ceilings is complete, and ambient temperature and humidity conditions are maintained at the levels indicated for project when occupied for its intended use.

1.08 COORDINATION

- A. A. Coordinate layout and installation of Saveto Acoustic Plaster with others including light fixtures, HVAC equipment, fire - suppression system, and partition assemblies.

PART 2 – PRODUCT INFORMATION

2.01 MANUFACTURERS

Acoustic Plaster is manufactured by Saudi Vetont Co. Ltd.-Saveto Factories in MENA area including Saudi Arabia, Jordan, United Arab Emirates, Qatar & Egypt. Web Address: www.Saveto.com.

2.02 PRODUCT

- A. Saveto Acoustic Plaster

2.03 MATERIAL

- A. Saveto Acoustic Plaster System provide manufacturer's complete system of proprietary materials specifically formulated for compatibility.
- B. Apply mixed material Lightweight levelling tools are required in conjunction with trowel to fill in holes
- C. Acoustic Plaster is composed of a retarded gypsum, Perlite & selected aggregates and special additives. It is supplied as a dry powder in pre-weighed bags ready to use on site, which requires only addition of clean water to produce cohesive mix.

Acoustic Plaster is generally applied in a single coat method using spray machine or trowel technique to cover the area to desired thickness.

- D. Accessories & Tools: use manufacturer's recommended accessories and tools.
- E. Water: Clean, fresh, potable, and free of mineral or organic matter.

PART 3 – EXECUTION

3.01 MOCKUP

Construct a 10' x 10' mock-up of the acoustical plaster for architectural approval of finish texture and colour. Mock-up shall be installed, if possible, as part of the finished walls & ceiling and shall remain intact throughout the project. Actual installation shall not commence until approval has been received.

3.02 EXAMINATION

Verify the suitability of existing conditions before starting work. Do not begin work of this section until unsatisfactory conditions have been corrected.

3.03 PREPARATION

- A. Comply with manufacturer's written instructions for substrate preparation.
 - 1. The surface should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.
 - 2. Prior to Acoustic Plaster application, wet the entire surfaces with clean potable water and allow to dry prior to Acoustic Plaster application.
- B. Protect adjacent surfaces.

3.04 INSTALLATION

- A. General: Apply Acoustic Plaster system as per manufacturer's recommendations.
- B. Acoustic Plaster is generally applied in a single coat method, use directly on block walls & rough surfaces, on smooth surfaces apply first a coat of Vetonit Spatter Dash S or SB.
- C. Apply mixed material using spray machine or trowel technique to cover the area to desired thickness. Lightweight levelling tools are required in conjunction with trowel to fill in holes.
- D. When the plaster stiffens lightly, treat the surface to a smooth level to eliminate all traces of protrusions and undulations. Let the plaster set for about 30 min. using wet sponge, wipe the surface to a creamy smooth finish.