

Analysis of Concrete Strength Model Visualisations

This report explains how the machine-learning models estimate concrete compressive strength and interprets the generated graphs.

Overall conclusion: the Random Forest Regressor performs best. It has the lowest RMSE (4.91), lowest MAE (2.75), and highest R2 (0.988). This means its predictions are closest to the measured concrete compressive strength values in the test data.


Compressive strength is predicted from mix-design and curing variables such as cement, water, binder, water-binder ratio, aggregates, supplementary cementitious materials, superplasticizer, temperature, age, and whether the sample is UHPC. The target variable is cs, which represents measured compressive strength.

- Simple Linear Regression uses one selected predictor, binder, and fits a straight-line relationship between that feature and strength.
- Multiple Linear Regression uses all input features in a weighted linear equation, so each feature adds or subtracts from the predicted strength.

Model	RMSE	MAE	R2
Random Forest Regressor	4.91	2.75	0.988
Gradient Boosting Regressor	6.66	4.94	0.979
Support Vector Regressor	9.55	6.01	0.956
K-Nearest Neighbours Regressor	9.85	4.91	0.953
Neural Network Regressor	13.56	9.14	0.911
Multiple Linear Regression	16.74	12.26	0.865
Simple Linear Regression (binder)	21.56	15.54	0.776
Naive Bayes Strength-Range Model	32.72	25.57	0.485

- Support Vector Regression uses a kernel method to fit a flexible nonlinear prediction surface.
- K-Nearest Neighbours predicts strength from similar concrete mixes in the training data.
- Neural Network Regression learns nonlinear combinations of the input variables through hidden layers.
- Naive Bayes is adapted by predicting strength ranges first, then converting each range into an approximate strength value.


Model Performance Comparison



- RMSE and MAE measure the size of prediction errors. Lower values mean the predicted compressive strength is closer to the real measured value.
- R2 measures how much of the variation in compressive strength is explained by the model. Values closer to 1 indicate stronger predictive performance.
- Random Forest is best on this graph because it has the smallest errors and the highest R2. Gradient Boosting is second, while SVR, KNN, and Neural Network Regression improve on the linear models but do not beat the tree-based methods.


Actual vs Predicted Strength

Actual vs Predicted Concrete Strength




- The diagonal line represents perfect predictions. Points close to that line mean the model predicted concrete strength accurately.
- Random Forest has the tightest cluster around the diagonal line, showing strong agreement between predicted and actual strength values.
- The Naive Bayes strength-range model is more spread out because it predicts broad strength categories before converting them back to approximate numeric values.

Residual Analysis



- Residuals are calculated as actual strength minus predicted strength. A good model should have residuals scattered closely around zero.
- Random Forest shows the smallest residual spread, meaning its errors are generally smaller and less systematic.
- The weaker models show wider residual patterns, which suggests they miss important nonlinear relationships such as the combined effect of water-binder ratio, age, and cementitious materials.

Feature Importance and Model Behaviour



- The tree-based models rely most strongly on water-binder ratio and age. This agrees with concrete technology: lower water-binder ratio usually increases strength, and curing age strongly affects strength gain.
- Multiple Linear Regression spreads influence across many variables because it can only form a weighted sum. Coefficients show direction and relative effect after standardisation, but not complex interactions.
- SVR, KNN, Neural Network Regression, and Naive Bayes are included in the performance plots, but they do not provide feature-importance values as directly as the linear and tree-based models.

Final Interpretation

The graphs show that concrete compressive strength is not explained well by a single variable or by a simple straight-line equation. Strength depends on several interacting factors, especially water-binder ratio, curing age, and binder composition.

Random Forest performs best because it can model nonlinear relationships and interactions while remaining stable through averaging many trees. Gradient Boosting also performs strongly, but in these results it has slightly larger errors. SVR, KNN, and Neural Network Regression are useful nonlinear comparison models, but they do not beat the tree-based methods. Multiple Linear Regression is useful for interpretation, but its straight-line structure limits accuracy. Simple Linear Regression and the binned Naive Bayes model are weaker baselines.

Therefore, based on the visualisations and the test-set metrics, the recommended model for predicting concrete compressive strength is the Random Forest Regressor.