



Jindapeng powder coatings



Electrostatic Spray Application

POWDER PROPERTIES:

Binder system : Epoxy

Density: 1.2 ~ 1.32g / c m³

preheating temperature: 190 ~ 220 °C

post Cur temperature: 180 °C

post Cur time (at a temperature of 180 °C at): 20 ~ 40 minutes

Storage stability :12months

physical property:

Color: Flame red Color(RAL3000)

Recommended filmthickness: 250 ~ 350 um

Gloss at 60° angle :75-85units

Flow: smooth

Hardness :2H

Cross cut test :Gt0

Impact resistance :>5 joule

Qingdao Jindapeng Powder Technology CO.,LTD

Zhaojialing Industrial Park No. 586, Tongji , Jimo City, Shandong Province,
china

Post Code: 266228

Tel: +86 0532 82513968

Mobile: 015865329690

Fax: +86 0532 82513968

E-mail: jindapengfenmo@163.com

Contact: Sun Peng