



中国认可  
国际互认  
检测  
TESTING  
CNAS L0167

检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 1 of 6



客户名称: 重庆纤居新材料有限公司  
客户地址: 重庆市大渡口区建胜镇新建村（建桥工业 B 区 2-1）号（F01 线生产厂房）

样品名称 : 玻纤增强复合材料型材（E-TS-AB）

以上信息及样品由客户提供及确认，SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性的责任。

\*\*\*\*\*

SGS 参考号 : CQP26-009118  
收样日期 : 2026-07-15  
测试开始时间 : 2026-07-15  
测试结束时间 : 2026-07-30  
测试结果 : 请见下页（除另有特别说明外，此报告结果仅对测试样品负责）

通标标准技术服务有限公司广州分公司  
授权签名

李叶娇

李叶娇 授权签字人

ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%.  
Added notes are not issued or certified by the laboratory. Verify  
seals/signatures using the untouched source PDF.

TEST REPORT | GZMR260702529004 | 30 July 2026

Client: Chongqing Xianju New Materials Co., Ltd.

Address: Xinjian Village, Jiansheng Town, Dadukou District,  
Chongqing (Jianqiao Industrial Zone B, No. 2-1), F01 production  
building.

Sample: Glass-fibre-reinforced composite profile (E-TS-AB).

The above information and the sample were provided and  
confirmed by the client. SGS accepts no responsibility for  
verifying the accuracy, appropriateness and/or completeness of  
client-provided information.

SGS reference: CQP26-009118.

Sample received: 15 July 2026.

Testing: 15-30 July 2026.

Results: See following pages. Unless otherwise stated, results  
relate only to the tested samples.

SGS-CSTC Standards Technical Services Co., Ltd., Guangzhou  
Branch.

Authorized signatory: Li Yejiao.



SGS-CSTC Standards Technical Services Co., Ltd.  
Guangzhou Branch Central Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf,  
available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability,  
indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects  
the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole  
responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations  
under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any  
unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted  
to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such  
sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443,  
or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
□ No.198, Kaifu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaifu Road, Huangpu District, Guangzhou, China t:(86-20) 82155555 www.sgs.com.cn  
中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t:(86-20) 82155555 sgs.china@sgs.com

Report holder: Chongqing Xianju New Material Co., Ltd., part of FengDu New Material (F1  
Composite is FengDu's export company). The results cover only that company's samples, not other  
suppliers' products. Verify: [www.f1composite.com/resources/evidence/sgs-gzmr260702529004](http://www.f1composite.com/resources/evidence/sgs-gzmr260702529004)



检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 2 of 6

结果总结:

| 序号 | 测试项目                             | 测试方法                        | 结果  | 结论 |
|----|----------------------------------|-----------------------------|-----|----|
| 1  | 50W (20mm) 垂直燃烧; V-0, V-1, 或 V-2 | UL 94-2023 Rev.2-2024 第 8 节 | V-0 | 合格 |

备注: 合格: 达到要求  
不合格: 未达到要求  
N/A: 不下判定

ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%.  
Added notes are not issued or certified by the laboratory. Verify seals/signatures using the untouched source PDF.

RESULT SUMMARY

Item 1: 50 W (20 mm) vertical burning; V-0, V-1 or V-2.

Method: UL 94-2023 Rev.2-2024, Section 8.

Result: V-0.

Conclusion: Pass.

Legend: Pass = meets requirements; Fail = does not meet requirements; N/A = no determination made.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing/inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
□ No.198, Kaifu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, China t:(86-20) 82155555 www.sgsgroup.com.cn  
中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t:(86-20) 82155555 sgs.china@sgs.com



检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 3 of 6

1. 测试项目: 50W (20mm) 垂直燃烧; V-0, V-1, 或 V-2

样品描述: A1-板材

测试方法: UL 94-2023 Rev.2-2024 第 8 节

测试条件:

常态试样: (125 ± 5) mm x (13.0 ± 0.5) mm x 10.1 mm

老化态试样: (125 ± 5) mm x (13.0 ± 0.5) mm x 10.1 mm

测试结果:

样品 A1-经向

| 处理条件                                                   | 处理条件: (23±2) °C, (50±10) %RH, 48 h |   |   |   |   | 处理条件: (70 ± 2) °C, 168 h → 干燥器, (23 ± 2) °C, 4 h |   |   |   |   |
|--------------------------------------------------------|------------------------------------|---|---|---|---|--------------------------------------------------|---|---|---|---|
| 试样                                                     | 1                                  | 2 | 3 | 4 | 5 | 1                                                | 2 | 3 | 4 | 5 |
| 第一次施加火焰后余焰时间 (t <sub>1</sub> ), s                      | 0                                  | 0 | 0 | 0 | 0 | 0                                                | 0 | 0 | 0 | 0 |
| 第二次施加火焰后余焰时间 (t <sub>2</sub> ), s                      | 0                                  | 0 | 0 | 0 | 0 | 0                                                | 0 | 0 | 0 | 0 |
| 第二次施加火焰后余辉时间 (t <sub>3</sub> ), s                      | 0                                  | 0 | 0 | 0 | 0 | 0                                                | 0 | 0 | 0 | 0 |
| 任何状态调节, 总余焰时间 (t <sub>1</sub> +t <sub>2</sub> ), s     | 0                                  |   |   |   |   | 0                                                |   |   |   |   |
| 第二次施加火焰后余焰时间加余辉时间 (t <sub>2</sub> +t <sub>3</sub> ), s | 0                                  | 0 | 0 | 0 | 0 | 0                                                | 0 | 0 | 0 | 0 |
| 试样余焰或余辉是否蔓延到夹具                                         | 否                                  | 否 | 否 | 否 | 否 | 否                                                | 否 | 否 | 否 | 否 |
| 燃烧颗粒或滴落物是否引燃脱脂棉                                        | 否                                  | 否 | 否 | 否 | 否 | 否                                                | 否 | 否 | 否 | 否 |
| 等级                                                     | V-0                                |   |   |   |   |                                                  |   |   |   |   |
| 客户要求                                                   | V-0                                |   |   |   |   |                                                  |   |   |   |   |
| 结论                                                     | 合格                                 |   |   |   |   |                                                  |   |   |   |   |

ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%. Added notes are not issued or certified by the laboratory. Verify seals/signatures using the untouched source PDF.

VERTICAL BURNING TEST

Sample description: A1 - sheet.

Method: UL 94-2023 Rev.2-2024, Section 8.

Both as-conditioned and aged specimens: (125 ± 5) mm × (13.0 ± 0.5) mm × 10.1 mm.

Sample A1 - longitudinal direction.

Conditioning, left group: (23 ± 2) °C, (50 ± 10)% RH, 48 h.

Conditioning, right group: (70 ± 2) °C for 168 h, then desiccator at (23 ± 2) °C for 4 h.

Five specimens per conditioning group.

RESULT ROWS (same order as original)

Afterflame time after first flame application (t1): 0 s for all specimens.

Afterflame time after second application (t2): 0 s for all specimens.

Afterglow time after second application (t3): 0 s for all specimens.

Total afterflame time (t1 + t2) for each conditioning group: 0 s.

Afterflame plus afterglow after second application (t2 + t3): 0 s for all specimens.

Did afterflame/afterglow reach the holding clamp? No, all specimens.

Did burning particles or drops ignite the cotton? No, all specimens.

Classification: V-0. Client requirement: V-0. Conclusion: Pass.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
□ No.198, Kezhu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaichuang Avenue, Huanggu District, Guangzhou, China t(86-20) 82155555 [www.sgs.com](http://www.sgs.com)  
中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t(86-20) 82155555 [sgs.china@sgs.com](mailto:sgs.china@sgs.com)




检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 4 of 6

表 1:

| 判定条件                                                    | V-0  | V-1   | V-2   |
|---------------------------------------------------------|------|-------|-------|
| 单个试样余焰时间, t <sub>1</sub> 和 t <sub>2</sub>               | ≤10s | ≤30s  | ≤30s  |
| 任何状态调节, 总余焰时间(5 个试样的 t <sub>1</sub> +t <sub>2</sub> )   | ≤50s | ≤250s | ≤250s |
| 第二次施加火焰后单个试样余焰时间加余辉时间 (t <sub>2</sub> +t <sub>3</sub> ) | ≤30s | ≤60s  | ≤60s  |
| 任一试样余焰或余辉是否蔓延到夹具                                        | 否    | 否     | 否     |
| 燃烧颗粒或滴落物是否引燃脱脂棉                                         | 否    | 否     | 是     |

备注:  
测试试样从样品中截取。  
测试照片:



ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%.  
Added notes are not issued or certified by the laboratory. Verify  
seals/signatures using the untouched source PDF.

TABLE 1 - CLASSIFICATION CRITERIA

Columns: V-0 / V-1 / V-2.

Individual afterflame time t1 and t2: ≤10 s / ≤30 s / ≤30 s.

Total afterflame time for five specimens in each conditioning  
group: ≤50 s / ≤250 s / ≤250 s.

Individual afterflame plus afterglow after second application (t2 +  
t3): ≤30 s / ≤60 s / ≤60 s.

Afterflame/afterglow reaches holding clamp: No / No / No.

Burning particles or drops ignite cotton: No / No / Yes.

Note: Test specimens were cut from the submitted sample.

PHOTO CAPTIONS

Left: Original sample - A1.

Right: During testing - A1.




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
□ No.198, Kaifu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, China t:(86-20) 82155555 www.sgs.com.cn  
中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t:(86-20) 82155555 sgs.china@sgs.com



检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 5 of 6



设备信息:

| 设备名称    | 型号    | 设备编号         | 校准日期       | 下次校准日期     |
|---------|-------|--------------|------------|------------|
| 水平垂直燃烧仪 | HVUL2 | GZMR-PL-E297 | 2026-02-27 | 2027-02-26 |
| 电热鼓风烘箱  | UF750 | GZMR-AG-E181 | 2026-05-22 | 2027-05-21 |

ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%.  
Added notes are not issued or certified by the laboratory. Verify  
seals/signatures using the untouched source PDF.

PHOTO CAPTIONS

Upper left: Before testing - A1, as-conditioned.  
Upper right: Before testing - A1, after ageing.  
Lower left: After testing - A1, as-conditioned.  
Lower right: After testing - A1, after ageing.

EQUIPMENT INFORMATION

Columns: equipment name; model; equipment ID; calibration  
date; next calibration due.  
  
Horizontal/vertical burning tester: HVUL2; GZMR-PL-E297; 27  
February 2026; 26 February 2027.  
  
Forced-air electric oven: UF750; GZMR-AG-E181; 22 May 2026;  
21 May 2027.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf,  
available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability,  
indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects  
the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole  
responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations  
under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any  
unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted  
to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such  
sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443,  
or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
SGS CSTC (Guangzhou) Technical Services Co., Ltd. □ No.198, Keshu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, China t:(86-20) 82155555 www.sgs.com.cn  
Guangzhou Branch China Services Co., Ltd. 中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t:(86-20) 82155555 sgs.china@sgs.com



检测报告

编号 : GZMR260702529004  
日期 : 2026-07-30  
页码 : 6 of 6

附录信息:

- \*除非另有说明, 参照 ILAC-G8:09/2019, 使用简单接受 (w=0) 的二元判定规则进行符合性判定。
- \*检测报告仅用于客户科研、教学、内部质量控制、产品研发等目的, 仅供内部参考。

\*\*\*\*\* 报告结束\*\*\*\*\*

ENGLISH TRANSLATION NOTES

F1 Composite translation copy • Original page retained at 100%.  
Added notes are not issued or certified by the laboratory. Verify  
seals/signatures using the untouched source PDF.

APPENDIX INFORMATION

Unless otherwise specified, conformity is determined using the  
binary decision rule of simple acceptance (w = 0), with reference  
to ILAC-G8:09/2019.

The test report is intended only for the client's scientific research,  
teaching, internal quality control, product development and similar  
purposes, and is for internal reference only.

END OF REPORT



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
□ No.198, Kaifu Road, Science City Economic & Technology Development Area, Guangzhou, Guangdong, China □ Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, China t:(86-20) 82155555 [www.sgs.com.cn](http://www.sgs.com.cn)  
中国·广东·广州高新技术产业开发区科学城科珠路198号 中国·广东·广州市黄埔区开创大道1501号3栋101房 t:(86-20) 82155555 [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

Report holder: Chongqing Xianju New Material Co., Ltd., part of FengDu New Material (F1 Composite is FengDu's export company). The results cover only that company's samples, not other suppliers' products. Verify: [www.f1composite.com/resources/evidence/sgs-gzmr260702529004](http://www.f1composite.com/resources/evidence/sgs-gzmr260702529004)