



Sales Office : #807. 103, Digitaempire II, Sinwon-Ro 88, Yeongtong-Gu, Suwon-Si, Gyeonggi-Do 16681 Korea
Tel : +82-31-224-7595(Rep) Fax : +82-31-224-7589 E-mail : export@keumjung.com http://www.keumjung.com

Head Office, Factory : 208-13, GacheonKeumsagil, Samnam-Eup, Ulju-Gun, Ulsan 44953 Korea
Tel : +82-52-264-8586(Rep) Fax : +82-52-264-8589

Okcheon Factory : 86-11, Donginonggonggil, Dongi-Myeon, Okcheon-Gun, Chungcheongbuk-Do 29023 Korea
Tel : +82-43-733-9733(Rep) Fax : +82-43-733-9737

Onsan Factory : 17-22, Sannam-gil, Onsan-eup, Ulju-gun, Ulsan 45010 Korea
Tel : +82-52-237-2580(Rep) Fax : +82-52-237-2582

CERTIFICATE OF ANALYSIS

INVOICE NO. AND DATE KJC-2412015 2024-12-09

ORDER NO. AND DATE MSC-2412BLOD_1 2024-12-09

Product Name : **TBM-38.5**

Technical Data from Manufacturer's Records

Test Item	Specification	Unit	R e s u l t		Remark
Lot Number			2041226	2041230	
Manufacture Date			2024-12-26	2024-12-30	
Quantity			4,800kg	4,800kg	
Appearance	Oily Paste	-	Oily Paste	Oily Paste	Visual
Active oxygen	min. 3.06	%	3.22	3.27	Wet Method
TBM content	Min. 36.0	%	37.9	38.5	Wet Method
TBHP content	Max. 1.0	%	0.01	0.01	Wet Method
silica content	3 ± 0.5	%	3.0	3.0	
Triacetin content	58.5 ± 2	%	59.1	58.5	

I hereby certify that above statement of quality is true and correct.

Date : 2025-01-06

Signed by
KeumJung Co., Ltd.

Quality Control Manager