

REPORT - EMR0000035

Elastic Moduli of Intact Rock Core Specimens in Uniaxial Compression

מודול אלסטיות של מדגמי סלע בלחיצה חד-צירית
(According to ASTM D7012, Method D)

Page 1 of 2

No.	B - 9
Specimen, No.	-

Project No.	609029
Site	Kokhav Hayarden
Date of sampling	
Date of testing	01/07/2018

Rock description	Piroclastic
------------------	-------------

Specimen conditions:		
Diameter	mm	53.60
Length	mm	109.50
Height to diameter ratio	--	2.04
Dry Unit Weight	kg/m ³	1956
Water content	%	5.26
Void Ratio	-	-
Degree of saturation	%	-

Test results:	
Unconfined Compres. Stress in failure, MPa :	19.0
Young's modulus, E, GPa :	6.3
Poisson's ratio, ν :	0.17
Ultrasonic Velocity, m/sec	

Actual equipment & Test conditions:	
Electrical resistance strain gages (axial and lateral)	
Stress rate, Mpa/s	0.5 ÷ 1.0
Time to failure, min	4:07
Temperature during the test T, C°	25



Note:
1. The test was performed by an internal procedure 1202
2. The test was performed at natural moisture content.
3. Due to preparation procedure, the moisture content of the specimen was slightly decreased

Performed by:

Sergey Shemborsky
Lab. Technician

End of report

1. מסמך זה הינו רכוש הבלעדי של המבדקה, עד למילוי כל התחייבויותיו של המזמין כלפי המבדקה.
2. התוצאות מתייחסות לפריט שנבדק בלבד.
3. יש להתייחס למסמך זה במלואו ובשלמותו ואין להעתיק או לפרסם ממנו קטעים או חלקים כלשהם.
4. הפרטים והנתונים על הנטילה / הבדיקה, הינם כפי שנמסרו על ידי המזמין או בא כוחו.

REPORT - EMR0000035


Elastic Moduli of Intact Rock Core Specimen in Uniaxial Compression

מודול אלסטיות של מדגמי סלע בלחיצה חד-צירית
(According to ASTM D7012-04, Method D)

Page 2 of 2

Boring No.	B - 9
Specimen, No.	-

Project No.	609029
Site	Kokhav Hayarden
Date of sampling	
Date of testing	01/07/2018

Graphical Presentation of Data

Method of calculation Young's modulus, E, is method (b):

Average Modulus of Linear Portion of Axial Stress-Strain Curve

S_{max} for Linear Part of Stress/Strain Curves, MPa	5
S_{min} for Linear Part of Stress/Strain Curves, MPa	1.3
Axial Strain e_{amax} (με) at Stress Value $S_i = S_{max}$	-735
Axial Strain e_{amin} (με) at Stress Value $S_i = S_{min}$	-147
Lateral Strain e_{lmax1} (με) at Stress Value $S_i = S_{max}$	128
Lateral Strain e_{lmin1} (με) at Stress Value $S_i = S_{min}$	29.6

1. מסמך זה הינו רכוש הבלעדי של המבדקה, עד למילוי כל התחייבויותיו של המזמין כלפי המבדקה.
2. התוצאות מתייחסות לפריט שנבדק בלבד.
3. יש להתייחס למסמך זה במלואו ובשלמותו ואין להעתיק או לפרסם ממנו קטעים או חלקים כלשהם.
4. הפרטים והנתונים על הנסילה / הבדיקה, הינם כפי שנמסרו על ידי המזמין או בא כוחו.