

**ASTM E 648-10e1**  
**Standard Test Method for Critical Radiant**  
**Flux of Floor-Covering Systems Using a**  
**Radiant Heat Energy Source**

**TEST REPORT**

<b>Client:</b>	Beynon Sports Surfaces, Inc.
<b>Address:</b>	16 Alt Road Hunt Valley, MD 21030
<b>Report No:</b>	16110-112656
<b>Sample Received:</b>	March 18, 2012
<b>Test Date:</b>	March 20, 2012
<b>Sample Conditioning:</b>	70.0±5.0°F and 50±5% relative humidity
<b>Sample Identification:</b>	BSS-2000 "Hobart" System
<b>Description:</b>	BSS-2000 "Hobart" System <i>The sample was adhered to a 0.25" thick cement board with a noncombustible adhesive.</i>

**Test Overview**

This procedure provides a way of measuring *critical radiant flux* (the level of incident radiant heat energy on a floor covering system at the most distant flame-out point, reported as W/cm<sup>2</sup>) of horizontally mounted floor-covering systems exposed to a flaming ignition source while being exposed to radiant heat energy from a panel with approximately a 30° angle from the horizontal. The radiant flux ranges from 1.08 W/cm<sup>2</sup> at the 100mm mark to 0.10 W/cm<sup>2</sup> at the 900mm mark.

**Test Procedure**

At least three specimens shall be tested. The specimens are conditioned at 70.0 ± 5.0°F and a relative humidity of 50±5% for a minimum of 48 hours. Following the ASTM E 648-10e1 calibration procedures, the first specimen was then loaded into the test chamber. After a 5 minute pre-heat time, the pilot flame was placed on top of the specimen at the 0 mm mark. This pilot flame is to remain in contact with the specimen for 5 minutes, then removed. If the specimen does not propagate flame during the 5 minute pilot flame contact, then the test is terminated. For specimens that do propagate flame, the test is continued until the flame goes out. The distance to the farthest flame-out point is noted, which is then used to determine the critical radiant flux, based on a radiant heat energy flux profile curve of the apparatus obtained during calibration.

**Omega Point Laboratories, Inc.**  
16015 Shady Falls Road  
Elmendorf, Texas 78112-9784  
210-635-8100 / FAX: 210-635-8101 / 800-966-5253  
[www.opl.com](http://www.opl.com) / email: [moreinfo@opl.com](mailto:moreinfo@opl.com)

### Test Results

Specimen	1	2	3
Maximum Distance (mm)	634	610	615
Time to Max. Distance (min.)	91.2	97.6	95.3
Critical Radiant Flux (W/cm2)	0.49	0.48	0.47
Time to All Flame Out (min.)	93.5	101.2	98.6

### Observations (min)

Run No.	Melting	Ignition	Blisters	Smoking	Dripping
1	4.9	5.0	3.8	3.7	5.2
2	4.9	5.0	4.0	3.7	5.2
3	4.9	5.0	3.8	3.7	5.2

The average critical flux was 0.48 W/cm2 and the standard deviation was 0.01

The coefficient of variation was 4.36

*This report is for the exclusive use of the client named herein. Omega Point Laboratories, Inc. authorizes the client to reproduce this report only if reproduced in its entirety. The test specimen identification is as provided by the client and Omega Point Laboratories, Inc. accepts no responsibility for any inaccuracies therein. The description of the test procedure, as well as the observations and results obtained, contained herein are true and accurate within the limits of sound engineering practice. These results are valid only for the specimens tested and may not represent the performance of other specimens from the same or other production lots. This report does not imply certification of the product by Omega Point Laboratories, Inc. Any use of the Omega Point Laboratories name, any abbreviation thereof or any log, mark, or symbol therefore, for advertising material must be approved in writing in advance by Omega Point Laboratories, Inc. The client must have entered into and be actively participating in a Listing & Follow-up Service program. Products must bear labels with the Omega Point Laboratories Certification Mark to demonstrate acceptance by Omega Point Laboratories, Inc. into the listing program.*

This report contains a total of two pages.