TEST REPORT

Laboratory evaluation of an athletic track product

Tests performed according to EN 13501-1 standards (2019)

Report Number	**R22007CAN-A1**
Product	**BSS 1000 (Hobart)** Beynon Sports Surfaces Inc.
Client	**Mike Gasparovic** 16 Alt Road, Hunt Valley Maryland 21030 USA
Date	**June 6th 2022**

This report contains 3 pages in total. Reproduction of this report is authorized only in its entire form. Results reported are valid only for the products tested. To declare the conformity (or not), the uncertainty of the results was not taken into account. Detailed results are available on request.

LABOSPORT CANADA ● contact@labosport.com ● (514) 277–9111
5661 Rue De Lanaudière ● Montréal ● Québec ● H2G 3A5 ● Canada
www.labosport.com

INFORMATION

Description of the wear layer	PU, SBR, EPDM			
Product identification	Absolute thickness	13 mm	Mass per unit area	18 kg/m²
	Color	Red	Flame Resistance treated	Untreated
Name of the product	BSS 1000			
Manufacturer	Beynon Sports Surfaces Inc.			
Sample Reference	T2206807			
Date of Reception	April 4th 2022			
Date of Testing	April - June 2022			
Test specimen details	Substrate	Fibre cement board – density (1800 ± 200) kg.m^{-3}		
	Mounting	Loose-laid		
	Joint	At 25 cm		

Face view



Back view

Note: Pictures taken from Report R18185US-D2 for the same product.

RESULTS

Property	Condition	Test method	Parameter	Results	EN 13501-1 Category - Pass/Fail
Single flame source test	After 14 days at T = 23°C ; Relative Humidity = 50%	EN ISO 11925-2 (2020)	Flame spreads 150mm	No	Pass
			Flame spreads 150mm - Additional remarks	No melted debris within 20s	Pass
				No resulting holes within 20s	Pass
		EN ISO 9239-1 (2010)	Heat flux Duration = 30 min	4.6 kW.m^{-2}	E_{fl}
			Smoke density : Light attenuation	239 %.min	s1

REPORTED BY

Jad MAAZOUZI
(Laboratory Technician) – Writer

Maxime FAVÉ
(Laboratory Manager) – Writer/Approver