



BSS-1000

Full Pour System "Embedded"

13mm (9+4)

Primer

BEYPRIM 20 or BEYPUR 300/320 - (Asphalt Primer)	0.25 lbs/yd^2	(0.12 kg/m^2)
BEYPRIM 30 or 60 – (Concrete Primer)	55 yd²/gal	$(17.5 \text{ m}^2/\text{L})$

Base Layer

BEYPUR 280A (2-C self-leveling polyurethane – component A)	13.02 lbs/yd^2	(7.35 kg/m^2)
UNIVERSAL B (component B)	1.55 lbs/yd^2	(0.87 kg/m^2)
SBR (Fine Mesh) Rubber	3.43 lbs/yd^2	(2.00 kg/m^2)

Texture Wear Layer

BEYPUR 250A (2-C self-leveling polyurethane – component A)	$3.20 \mathrm{lbs/yd^2}$	(1.76 kg/m^2)
UNIVERSAL B (component B)	0.80 lbs/yd^2	(0.44 kg/m^2)
EPDM (1-4mm) Rubber Granules	$\sim 7.50 \text{ lbs/yd}^2$	(4.10 kg/m^2)

BSS-1000 is IAAF Certified (S-03-0034)





