

Fixture Filament Technical Data Sheet

Property	Testing Method	Typical Value
Density	ISO 1183	1,24 g/cm ³
Tensile strength (X-Y)	ISO 527	52 MPa
Heat deflection temperature	ISO 75, 0.45 MPa	68 °C
Melting temperature DSC, 10 °C/min	160 °C	
Charpy impact strength	243 ± 79.4 kJ/m ² ISO 179	
Shore D Hardness	43 ISO 868	

Printing settings

Nozzle temperature 230 - 250 °C

Bed temperature 80 °C

Storage and shelf life

Store below 20% RH