

Fixture Filament Technical Data Sheet

Property	Testing Method	Typical Value
Density	ISO 1183	1,24 g/cm ³
Tensile strength (X-Y)	ISO 527	52 MPa
Heat deflection temperature	ISO 75, 0.45 MPa	68 °C
Melting temperature DSC, 10 °C/min 160 °C		

Printing settings

Nozzle temperature 230 - 250 °C

Charpy impact strength 243.3 ± 79.4 kJ/m²

Store below 20% RH