



Liquid Type Alkaline Soak Cleaner

DIPSOL LC-34

Can be used in all method

DIPSOL LC-34 is a liquid type alkaline degreaser which does not contain silicates. It has an excellent degreasing power in all methods such as dipping, electrolytic, spraying, rocking and ultrasonic use.

1. Features

- (1) It is silicate-free degreaser and has an excellent degreasing power.
- (2) Easy to use due to one liquid type.
- (3) It can be used for dipping, electrolytic, spraying, rocking and ultrasonic use and effective in all method.

2. Composition and Properties

Strong alkaline, White-Light brown liquid

Specific Gravity : 1.46 at 25°C

Containing NaOH : 30%, KOH : 8% (hazardous substance)

3. Application

- (1) It is used by dipping, electrolytic and spray degreasing for steel, stainless steel, tubes and parts.
- (2) It can also be used for the degreaser in hoop line for cold strip line and continuous plating line.

4. Operation

(1) Soak cleaning

Concentration	20 ~ 100 g/L
Temperature	40 ~ 80°C
Time	2 ~ 5 min
Method	Dipping, Electrolytic, Spray, Rocking, Ultrasonic

(2) Electrolytic cleaning

Current density	1 ~ 10 A/dm ²
Method	Anode, Cathode, PR

5. Maintenance

The solution consumes by electrolysis, drag-out and others. Therefore, it is necessary to replenish an insufficient quantity of it by means of periodical analysis. The quantity to be replenished is calculated by measuring the points of the solution.

〈Measurement of points〉

- (a) Pipette 10 mL of the solution into a 300 mL conical flask and add 100mL of distilled water.
- (b) Add 2 or 3 drops of Methyl Orange as an indicator.
- (c) Titrate with 1 mol/L-Hydrochloric Acid (HCl) until a color changes from Yellow to Vermilion color.
- (d) Let mL number of the 1 mol/L-HCl required in the titration be the present point.

DIPSOL LC-34 Concentration(g/L) = $10 \times \text{mL of 1 mol/L-HCl} \times f$
f : Factor of 1 mol/L-hydrochloric acid standard solution

6. Packing

DIPSOL LC-34 : 25kg UN Plastic Jerry Can

Caution in handling

1. Safety and health

- Operate in a predetermined place.
- Provide an exhaust system in the operation place depending on the circumstances.
- After operation, wash the hands and gargle sufficiently.

2. Storage and container

- Seal the containers and store in a cool dark place.
- When taking out liquid from a container, do not spill it.
If it is spilt out, dispose of it according to "Safety Data Sheet (SDS)."
- Wash thoroughly the used containers with water and collect in a predetermined place.
- Do not enter any other chemical than the specified in the containers.

3. Application range

- Do not use any product for other than specified applications or beyond the specified application range.



Before use, be sure to thoroughly read and observe the precautions and prohibitions in "Safety Data Sheet (SDS)."
Wrong use may cause fire or personal injury.



DIPSOL CHEMICALS CO., LTD.

<http://www.dipsol-jp.com>

■ Head Office

2-7-12, Yaesu, Chuo-ku, Tokyo, 104-0028 Japan
TEL: +81-3-3548-9351 FAX: +81-3-3548-9370

■ Sales Administration Division

• East Japan Sales Dept.

Tokyo Branch

2-7-12, Yaesu, Chuo-ku, Tokyo 104-0028
TEL: +81-3-3548-9354 FAX: +81-3-3548-9370

North Kanto Office

44-13-101, Nishi-honcho, Ota-shi, Gunma 373-0033
TEL: +81-276-40-4133 FAX: +81-276-31-0999

• Central Japan Sales Dept.

Nagoya Branch

2-350, Kamiotai, Nishi-ku, Nagoya-shi, Aichi 452-0821
TEL: +81-52-505-2566 FAX: +81-52-505-2568

Shizuoka Office

442-1, Shimoe-cho, Minami-ku, Hamamatsu-shi, Shizuoka 430-0825
TEL: +81-53-425-4310 FAX: +81-53-426-4718

• West Japan Sales Dept.

Osaka Branch

2-11-8, Oyodo-naka, Kita-ku, Osaka-shi, Osaka 531-0076
TEL: +81-6-6451-0894 FAX: +81-6-6451-1009

Kyusyu Office

2-3-24-102, Doi, Higashi-ku, Fukuoka-shi, Fukuoka 813-0032
TEL: +81-92-663-6170 FAX: +81-92-663-6171

• Overseas Sales Dept.

2-7-12, Yaesu, Chuo-ku, Tokyo 104-0028
TEL: +81-3-3548-9355 FAX: +81-3-3548-9370

■ Manufacturing Administration Division

(Ichihara Factory)

2-8-3, Tamasaki-nishi, Ichihara-shi, Chiba 290-0044
TEL: +81-436-22-2155 FAX: +81-436-22-5210

■ Research and Development Division

(Otakanomori Technical Center)

5-59-1, Nishi-hatsuishi, Nagareyama-shi, Chiba 270-0121
TEL: +81-50-5846-3002 FAX: +81-4-7178-9184

★ The contents of this technical report are created based on the materials, information, and data obtained at this time, however are not intended to assure the correctness and completeness of the information.

★ When there is any question, contact your nearest Sales Dept. of Sales Administration Division.

★ The contents are subject to change of specifications and design without prior notice for improvement of products.