





BRILLIANTZ

Quartz Surface

evershine



BQ-34032
Natural Calacatta





Snow Quart
BQ-2850 (20mm)



River Wave
BQ-20153 (15mm)




Grey Sand
BQ-2857 (20mm)




Black Matrix
BQ-2937 (20mm)




Black Sand
BQ-2872 (20mm)






Silver Night Stone
BQ-2942 (20mm)



Black Stone
BQ-2805 (20mm)



Matsuke
BQ-29 (20mm)





Arctic Wave
BQ-31607 (20mm)



Parola
BQ-3321



Patine Gris
BQ-31601 (20mm)



Cream Parola
BQ-31602



Noir Calacatta
BQ-31647



Natural Calacatta
BQ-34032 (20mm)



Carrara Calacatta
BQ-34029 (20mm)



BQ-34088



BQ-34007



BQ-36131



BQ-31647
Noir Calacatta

...pure and simple



BQ-31607
Arctic Wave


BRILLIANTZ

Quartz Surface

PHYSICAL DATA SHEET

Property	Typical Result	Test Method
Specific Gravity	> 2.35	ASTM D 792
Tensile Strength	17.5 Mpa	ASTM D 638
Flexural Strength	> 37 Mpa	ASTM D 790
Flexural Modulus	38.5 GPa	ASTM D 790
Compression Strength (Dry)	190.5MPa	ASTM C 170
Compression Strength (Wet)	184.1 Mpa	ASTM C 170
Abrasion Resistance (Weight Loss)	1095 mg	ASTM D4060
Hardness	> 6.5 Mohs	Hardness Scale
Thermal Expansion	1.55×10^{-5} in/in/deg C	ASTM D 696
Colorfastness	Passes	ANZI Z 1 24.6.5.1
Wear and Cleanability	Passes	ANZI Z 1 24.6.5.3
Stain Resistance	Passes	ANZI Z 1 24.6
Fungal & Bacterial Resistance	No Growth	ASTM G 21
High Temperature Resistance	None To Slight Effect	NEMA LD 3.3.6
Boiling Water Resistance	None To Slight Effect	NEMA LD 3.3.5
Freeze-Thaw Cycling	Unaffected	ASTM C 1026
Point Impact	Passes	ANZI Z 1 24.6.4.2
Water Absorption	< 0.02%	ASTM D 570
Flammability	Class A	ASTM E 84, NFPA 255

Standard Specification of Kitchen Top



PERFORMANCE COMPARISON

Performance	BRILLIANTZ	GRANITE	SOLID SURFACE
Materials			
Hardness	★★★★★	★★★★	★★
Scratch Resistance	★★★★★	★★★★	★
Mold/Mildew Resistance	★★★★★	★★	★★★★★
Heat Resistance	★★★★★	★★★★★	★★
Burn Resistance	★★★★★	★★★★★	★★
Chemical Resistance	★★★★★	★★★	★★★★
Stain Resistance	★★★★★	★★★	★★★★★
Color Richness	★★★★★	★★★★	★★★★
Color Stability	★★★★★	★★★	★★★★

evershine
the inner space surfacing specialist

Head Quarter:
19 Gul Way
T (65) 6897 8888
F (65) 6897 8128/ 38
Singapore 629195

Retail Branch:
5 Sungei Kadut Street 2
#02-09, Trendspace
T (65) 6365 7797
F (65) 6365 7747
Singapore 729227

www.evershine.com
www.facebook.com/evershinecorp/

Co. Reg. No. 19750180
GST. Reg. No. M2-0022665-8