

## PRODUCT DATA SHEET

**Date:** 01/03/2017 **Doc ID:** 767E63

**Spinnaker Coating** 518 East Water Street Troy, Oh 45373 800 543-9452









## 2.3 mil TC White Polypropylene \*\* SFATM \*\* 40# liner

Item#: 0041934 ----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
New York	2.5 K	3"	3"
New York	5 K	3"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Los Angeles	2.5 K	3"	3"
Los Angeles	5 K	3"	3"

Facestock: 2.3 mil TC White Polypropylene

A glossy white, biaxially-oriented polypropylene designed with a unique top coating to be compatible with water-based and solvent-based inks.

## **Typical Value**

Basis Weight: 39 #/3300 ft<sup>2</sup> Caliper: 2.3 mils

Tensile MD/CD: 26,800 / 22,500 PSI

Elongation @ Break MD/TD: 80 / 100% Opacity: 80%

Adhesive: **SFATM** A clear, general purpose, emulsion acrylic permanent adhesive

> designed for applications with film facestocks. SFA exhibits excellent ultimate adhesion to polyethylene, polypropylene and glass. Well suited

for small, cylindrical labeling and is glove friendly.

**Typical Value** 

Coat Weight: 13 #/3300 ft<sup>2</sup> Coat Weight: 19.24 grams/m<sup>2</sup>

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° 27

Peel):

Loop Tack, oz.: 33

Service Temperature: -40 to +200 °F

Minimum Application Temperature: 40 °F

Shear (1000g): 450 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and

stripping characteristics. Recommended for use in roll-to-roll

applications.

**Typical Value** 

Basis Weight:  $41 \#/3000 \text{ ft}^2$ 

Caliper: 2.5 mils

Tensile MD/CD: 34 / 21 #/inch
Tear MD/CD: 34 / 36 grams
Opacity: 69 max%

**Total Product Caliper:** 5.4 mils **Product Basis Weight Per MMSI:** 204.42 #

For application recommendations call 877-210-5104

For samples or other questions please call your Sales

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH *Representative*.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Coating, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Coating, LLC. Because of the variety of possible applications for Spinnaker Coating's products and the continuing development of new applications, all Spinnaker Coating, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Coating, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 08/15/2016