

# Development and Testing of Solar Reflectors

C. Kennedy, K. Terwilliger, and M. Milbourne

*Presented at the 2004 DOE Solar Energy Technologies  
Program Review Meeting  
October 25-28, 2004  
Denver, Colorado*

**Conference Paper**  
**NREL/CP-520-36582**  
**January 2005**

NREL is operated by Midwest Research Institute • Battelle Contract No. DE-AC36-99-GO10337



### NOTICE

The submitted manuscript has been offered by an employee of the Midwest Research Institute (MRI), a contractor of the US Government under Contract No. DE-AC36-99GO10337. Accordingly, the US Government and MRI retain a nonexclusive royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for US Government purposes.

This report was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or any agency thereof.

Available electronically at <http://www.osti.gov/bridge>

Available for a processing fee to U.S. Department of Energy  
and its contractors, in paper, from:

U.S. Department of Energy  
Office of Scientific and Technical Information  
P.O. Box 62  
Oak Ridge, TN 37831-0062  
phone: 865.576.8401  
fax: 865.576.5728  
email: <mailto:reports@adonis.osti.gov>

Available for sale to the public, in paper, from:

U.S. Department of Commerce  
National Technical Information Service  
5285 Port Royal Road  
Springfield, VA 22161  
phone: 800.553.6847  
fax: 703.605.6900  
email: [orders@ntis.fedworld.gov](mailto:orders@ntis.fedworld.gov)  
online ordering: <http://www.ntis.gov/ordering.htm>



Printed on paper containing at least 50% wastepaper, including 20% postconsumer waste

# Development and Testing of Solar Reflectors

C. Kennedy, K. Terwilliger, M. Milbourne  
National Renewable Energy Laboratory  
1617 Cole Blvd., Golden, CO 80401  
[cheryl\\_kennedy@nrel.gov](mailto:cheryl_kennedy@nrel.gov)

## ABSTRACT

To make concentrating solar power technologies more cost competitive, it is necessary to develop advanced reflector materials that are low in cost and maintain high reflectance for extended lifetimes under severe outdoor environments. The Advanced Materials Team performs durability testing of candidate solar reflectors at outdoor test sites and in accelerated weathering chambers. Several materials being developed by industry have been submitted for evaluation. These include silvered glass mirrors, aluminized reflectors, and front-surface mirrors. In addition to industry-supplied materials, NREL is funding the development of new, innovative reflectors, including a new commercial laminate reflector and an advanced solar reflective mirror (ASRM). To help commercialize the ASRM, a cost analysis was performed; it shows the total production cost could meet the goal. The development, performance, and durability of these candidate solar reflectors and cost analysis results will be described.

### 1. Objectives

The viability of CSP systems requires the development of advanced reflector materials that are low in cost and maintain high specular reflectance for lifetimes of 10 to 30 years under severe outdoor environments. Cost reductions can be achieved in lightweight front-surface reflectors that include anti-soiling coatings through technology advances, as discussed in the Solar Program Multi-Year Technical Plan [1]. The objective of this research is to identify new, cost-effective advanced reflector materials that are durable with weathering.

### 2. Technical Approach

Candidate reflector materials are identified based on their potential for low cost and high optical performance and durability. All candidate materials are optically characterized prior to exposure testing and as a function of exposure time to assess optical durability. These mirrors are subjected to accelerated or outdoor weathering at a variety of geographically diverse exposure sites.

### 3. Results and Accomplishments

#### 3.1 Glass Mirrors

Glass mirrors have excellent durability in terms of corrosion of reflective layer, are readily available, have the confidence of the solar manufacturing industry, and are commercially deployed. However, they are heavy and fragile and curved shapes require slumped glass, which is expensive. Recently, two significant changes in mirror manufacturing

have occurred in the classical wet chemistry process because of environmental concerns. The first is the method of forming a copper-free reflective mirror, and the second is the use of lead-free paints.

Trough mirrors (used in commercial solar plants), manufactured by Flabeg, use silvered, thick, slumped glass with a proprietary multilayer paint system designed for outdoor exposure. Initial hemispherical reflectance is ~93% and cost is \$43.2–\$64.8/m<sup>2</sup> for large-volume purchases. The original Flabeg mirrors (with copper back layers, original proprietary multilayer paint system, and 4-mm glass) were very durable. Flabeg converted its mirror line to 5-mm glass, the copper-free process, and a new lead-free paint system in FY 2003. The manufacturer reports durability is expected to be equivalent. Side-by-side exposure testing began in second-quarter FY 2004.

Pilkington introduced a 4-mm copper-free mirror in 2000 for interior use. Testing of samples of Pilkington and “Spanish” (Cristaleria Espanola S.A) glass mirrors (3 mm, copper-free, and lead-free paint), bonded to steel with four different candidate adhesives, was initiated in FY 2001 for possible use at Solar Tres. Initial hemispherical reflectance is 93% and their cost is ~\$15 to 16/m<sup>2</sup>. Neither Pilkington nor Spanish mirrors exposed outdoors show degradation after 30 months, but in accelerated testing (WOM) the Pilkington mirrors exhibit better optical durability and adhesive-related degradation is more prevalent with Spanish glass mirrors.

Thin-glass mirrors use traditional wet-silvered processes on thin (<1 mm), relatively lightweight glass. They have greater material costs, are more difficult to handle, and have higher associated labor costs (25%–40%) than advanced reflector technologies. Initial hemispherical reflectance is ~93% to 96% and their cost is ~\$16.1 to 43.0/m<sup>2</sup>. Choice of adhesive affects the performance of weathered thin-glass mirrors and corrosion has been observed in deployed mirrors. Initial analysis of a thin glass mirror matrix exposed in the WOM indicates commercial (non-mirror) back protective paint applied post mirror manufacturing is not beneficial. CPV manufacturers expressed significant concern regarding the durability of thin-glass mirrors made with copper-free and lead-free paint systems.

Although glass mirrors with copper backlayers and heavily leaded paints have been considered robust outdoors, the new copper-free back layer and lead-free paint systems were designed for interior mirror applications and do not have the same durability. Development of a mirror-backing paint system suitable for outdoor applications, to be applied during mirror manufacturing, will be required to provide sufficient durability.

#### 3.2 Aluminized Mirrors

Aluminized reflectors use a polished aluminum substrate, enhanced aluminum reflective layer, and a protective oxidized

topcoat [2]. The reflectors' initial reflectance is ~90% and the product was commercially available from Alanod in Germany for <\$21.52/m<sup>2</sup>. The major concern has been poor durability of such materials in urban and industrialized (polluted) locations. An improved anodized aluminum mirror incorporated a protective polymeric overcoat onto PVD aluminized aluminum. However, specularly degraded with outdoor exposure at Arizona, Florida, and NREL, and with accelerated exposure in the WOM. Aluminized reflectors from other manufacturers exhibit similar performance. Recently, Alanod stopped selling this material for outdoor use because of problems associated with the delamination of the overcoat. The company is working to find a solution and to improve the abrasion resistance of the reflector [3].

### 3.3 Silvered Polymer Reflectors

A new polymeric solar reflector developed through collaborative research with ReflecTech has an initial solar-weighted hemispherical reflectance of 94%, a specular reflectance of 94% at 25-mrad (1.4°) acceptance angle, and can be supplied in roll widths up to 1.2 m for less than \$14/m<sup>2</sup>. In FY 2001, a very small pilot run on standard commercial equipment demonstrated that all production steps could be achieved using standard commercial film converter equipment. This initial pilot-run material shows no significant loss in solar-weighted reflectance after 2.5 years of real-time outdoor exposure in Golden, CO. In addition, accelerated ACUVEX<sup>®</sup> outdoor weathering tests (natural sunlight in Phoenix, AZ, is concentrated 7 to 8 times with a Fresnel-reflector while the samples are cooled with a fan to near ambient conditions and sprayed with deionized water 8 min per natural sun hour [4]) are near a 10-year equivalent time period, and show no significant loss in solar-weighted reflectance. However, WOM results showed significant reflectance loss earlier than anticipated. Prototype materials to test modifications to the baseline construction were produced using pilot-line coating equipment. These tests were successful in identifying changes to the baseline construction that dramatically improved the accelerated weathering durability of the reflective film. These improvements were then incorporated into a new pilot plant production run delivered late FY 2004; durability testing is ongoing and the material is being deployed. We expect the new reflector to considerably outperform the original material (which has maintained durability after 10 equivalent years of ACUVEX<sup>®</sup> exposure), however testing has only recently been initiated, and further real time exposure will be needed to determine its actual lifetime.

### 3.3 Advanced Solar Reflective Mirror (ASRM)

A promising low-cost reflector material, developed under a subcontract with Science Applications International Corporation (SAIC) that ended 9/30/04, has a silvered specular substrate protected by an alumina coating several microns thick. The alumina hard coat is deposited by ion-beam-assisted deposition (IBAD). Samples of this "super thin glass technology" have been deposited at 20 nm/s both by batch and on a laboratory roll-coater. Many samples prepared have maintained 95% hemispherical reflectance after more than 3 years accelerated and outdoor exposure; testing is continuing. A new cost analysis shows the ASRM has the potential for a manufacturing cost lower than \$10.76/m<sup>2</sup>, but the deposition rate must be increased to 30–50 nm/s [5,6]. Although thin oxide coatings are routinely deposited at

deposition rates greater than 100 nm/s, increasing the deposition rate while maintaining the optimized IBAD deposition conditions could be difficult. For long-term durability, edge protection will be necessary and the addition of adhesion-promoting layer could improve durability. The ASRM can be transitioned to a commercial roll-coating company, with SAIC's consultation, if NREL establishes the relationship. Prior to transition, a short subcontract to evaluate different web materials, adhesion-promotion and anti-soiling layers, and use of a lower-purity alumina is warranted.

## 4. Conclusions

Positive progress has been made to develop an advanced solar reflector, but work has been severely limited due to a lack of funding during the last few years. Durability testing of the reflectors supplied by industry is ongoing. The glass mirrors, ReflecTech, and ASRM may meet the 10-year lifetime goals based on accelerated exposure testing. However, predicting an outdoor lifetime based on accelerated exposure testing is risky. At this time, because all solar reflectors have recently changed their production considerably, none of the solar reflectors available have been in test long enough to demonstrate the 10- to 30-year lifetime goal, outdoors in real time.

## REFERENCES

- [1] *Solar Energy Technologies Program Multi-Year Technical Plan, 2003-2007 and Beyond*, DOE/GO-102004-1775, U.S. Department of Energy, Washington DC, January 2004.
- [2] Fend, T., Jorgensen, G. J., Küster, H., 2000, "Applicability of Highly Reflective Aluminum Coil for Solar Concentrators," *Solar Energy*, Vol. 68, pp. 361-370.
- [3] Kennedy, C.E.; and Terwilliger, K., 2004, "Dual 2004: Optical Durability of Candidate Solar Reflectors," In publication, ISEC2004-65111, *Proc. 2004 Solar Conf. and J Sol Energy Eng Trans ASME*, July 2005.
- [4] ASTM Standard G90-98 (Reapproved 1998). "Standard Practice for Performing Accelerated Outdoor Weathering of Nonmetallic Materials Using Concentrated Natural Sunlight" *Ann. Book of ASTM Standards 2004*, Vol. 14.04, American Society of Testing and Materials, Philadelphia, PA.
- [5] Kennedy, C.E.; Swisher, R.; and Smilgys, R.V., 2003, "Cost Analysis of Solar Reflective Hard Coat Materials," *Proceedings 2003 AIMICAL Fall Technical Conference; 17th International Conference on Vacuum Web Coating*.
- [6] Kennedy, C.E.; and Swisher, R., 2004, "Dual 2004: Cost Analysis of Solar Reflective Hard-Coat Materials Deposited by Ion-Beam-Assisted Deposition," In publication, ISEC2004-65112, *Proc. 2004 Solar Conf. and J Sol Energy Eng Trans ASME*, July 2005.

# REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Executive Services and Communications Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.

1. REPORT DATE (DD-MM-YYYY) January 2005			2. REPORT TYPE Conference Paper		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Development and Testing of Solar Reflectors				5a. CONTRACT NUMBER DE-AC36-99-GO10337		
				5b. GRANT NUMBER		
				5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) C. Kennedy, K. Terwilliger, and M. Milbourne				5d. PROJECT NUMBER NREL/CP-520-36582		
				5e. TASK NUMBER CP043000		
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Renewable Energy Laboratory 1617 Cole Blvd. Golden, CO 80401-3393				8. PERFORMING ORGANIZATION REPORT NUMBER NREL/520-36582		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S) NREL		
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER		
12. DISTRIBUTION AVAILABILITY STATEMENT National Technical Information Service U.S. Department of Commerce 5285 Port Royal Road Springfield, VA 22161						
13. SUPPLEMENTARY NOTES						
14. ABSTRACT (Maximum 200 Words) To make concentrating solar power technologies more cost competitive, it is necessary to develop advanced reflector materials that are low in cost and maintain high reflectance for extended lifetimes under severe outdoor environments. The Advanced Materials Team performs durability testing of candidate solar reflectors at outdoor test sites and in accelerated weathering chambers. Several materials being developed by industry have been submitted for evaluation. These include silvered glass mirrors, aluminized reflectors, and front-surface mirrors. In addition to industry-supplied materials, NREL is funding the development of new, innovative reflectors, including a new commercial laminate reflector and an advanced solar reflective mirror (ASRM). To help commercialize the ASRM, a cost analysis was performed; it shows the total production cost could meet the goal. The development, performance, and durability of these candidate solar reflectors and cost analysis results will be described.						
15. SUBJECT TERMS PV; concentrating solar power; advanced reflector materials; silvered glass mirrors; aluminized reflectors; front-surface mirrors; advanced solar reflective mirror (ASRM);						
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UL	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON	
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code)	

Standard Form 298 (Rev. 8/98)  
Prescribed by ANSI Std. Z39.18