CROWN®

PREMIUM GALVANIZE COATINGS

7007 COLD GALVANIZE COATING 93% ZINC RICH

The leader in the industry in corrosion prevention. Can be easily sprayed, brushed, or dipped onto any metal surface. Its zinc-rich formula is designed for permanent protection.

- 93% pure zinc in dry film
- Meets performance requirements of MIL-P-46105(MR), MIL-P-21035B, and DOD-P-21035A
- Withstands 2000 hours of 5% salt spray testing (ASTM B-117)
- Light gray, matte finish
- Zinc sacrifices itself to protect the base metal surface
- Provides protection equal to or better than hot-dipped galvanizing
- Outstanding weld-through primer

Uses: Industrial type applications such as aviation, marine, manufacturing, etc.

CAN SIZE (NET)	WEIGHT	CASE PACK
16-oz. Aerosol (13 oz.)	14 lbs.	12 Cans
Quart Can	26 lbs.	4 Quarts
Gallon Can	25 lbs.	1 Gallon

7008 BRITE GALVANIZE COATING 65% ZINC RICH

A restorative coating fortified with zinc for preventing rust and corrosion on ferrous metal surfaces with one coat application.

- A glistening coating with 65% pure zinc in dry film
- Stops rust and corrosion on any iron or steel surface for protection equal to or better than hot-dipped galvanizing
- Restores galvanized surfaces to the bright look of hot-dipped galvanizing
- Meets performance requirements of ASTM A-780-93A
- Withstands 500 hours 5% salt spray (ASTM B-117)

Uses: Repair of welds, handrails, rims, guardrails, metal chain fences, pipes, corrugated metal buildings, or anywhere the bright look of hot-dipped surfaces is desired.

CAN SIZE (NET)	WEIGHT	CASE PACK
16-oz. Aerosol (13 oz.)	14 lbs.	12 Cans
Quart Can	13 lbs.	4 Quarts
Gallon Can	13 lbs.	1 Gallon

LOW VOC FORMULAS MEET CALIFORNIA, CONNECTICUT AND OTHER STATE REQUIREMENTS.

7007VG LOW VOC COLD GALVANIZE COATING 93% ZINC RICH

A low VOC version of our Cold Galvanize Coating with a VOC content of less than 100 g/l. Contains 97% pure zinc that yields 93% zinc in a dry film.

- Meets multiple performance requirements of ASTM, MIL, and DOD specifications (see product data sheet for details)
- Performs at temperatures up to 150°F (65°C)
- Withstands up to 2,000 hours salt spray exposure

CAN SIZE (NET)	WEIGHT	CASE PACK
Gallon Can	20 lbs.	1 Gallon

7008VG LOW VOC BRITE GALVANIZE 65% ZINC RICH

A low VOC version of our Brite Galvanize Coating with a VOC content of less than 250 g/l.

- Meets performance requirements of ASTM A-780-93A
- Withstands 500 hours 5% salt spray (ASTM B-117)

CAN SIZE (NET)	WEIGHT	CASE PACK
Gallon Can	20 lbs.	1 Gallon