P3: two references per class help, least on microstructure

Difference and paired 95% bootstrap interval for JEV and Clef-Flash on the test images. Two references per class (k = 2) minus none (k = 0), both with the final description (pans: generic).

