Kaneda Fabrication Works (fictional)

WELDER PERFORMANCE QUALIFICATION (WPQ)

Format per ASME BPVC Section IX, Form QW-484A (see QW-301)

WPQ no.	**WPQ-204**
Welder stamp	**204**
Test date	**2024-06-12**

Welder's name	Identification no.	Test type
R. Wibowo (fictional)	**204**	**Test coupon**

Identification of WPS followed	Date welded
WPS-09	**2024-06-12**

Specification and type/grade of base metal(s)	Thickness
SA-36 to SA-36	**10 mm**

TESTING VARIABLES AND QUALIFICATION LIMITS (QW-350)

Welding variables	Actual values	Range qualified
Welding process(es)	FCAW	FCAW
Type (manual, semi-automatic)	Semi-automatic	Semi-automatic
Backing (with / without)	With (steel backing)	With
Plate / pipe (diameter if pipe)	Plate, 10 mm	Groove: pipe 610 mm OD and over; fillet: all
Base metal P-Number to P-Number	P-No.1 to P-No.1	P-No.1 through P-No.15F, 34, 41-49
Filler metal specification / class (info)	SFA-5.20 E71T-1C	-
Filler metal F-Number(s)	F-6	F-6 and lower
Deposit thickness for each process	10 mm	max. 20 mm
Position(s)	3G and 4G	Groove F, V, O; fillet all positions
Vertical progression	Uphill	Uphill
Base metal thickness	10 mm	max. 20 mm

RESULTS

Visual examination of completed weld (QW-302.4): acceptable.

2 face + 2 root bends (QW-462.3(a)) per coupon: acceptable.

Film or specimens evaluated by: Halvorsen Test Lab (fictional) · mechanical tests lab no. HTL-W204

We certify that the statements in this record are correct and that the test coupons were prepared, welded and tested in accordance with the requirements of Section IX of the ASME BPVC.

Welding supervised by	Certified by (QA manager)
K. Mori (fictional)	**L. Ortega (fictional)**
signed K. Mori 2024-06-12	*signed L. Ortega* 2024-06-12

CONTINUITY LOG (QW-322.1) - USE OF EACH PROCESS, AT LEAST ONCE EVERY 6 MONTHS

Date	Job	Weld / work	Process	Verified by
2025-11-18	Job 25-204	Platform frame	FCAW	QC - T. Rahman
2026-03-02	Job 26-030	Skid frame	FCAW	QC - T. Rahman

Last recorded use of FCAW: 2026-03-02.

SYNTHETIC DOCUMENT - generated for software testing - not a real record