Kaneda Fabrication Works (fictional)

HYDROSTATIC TEST REPORT

Job 26-118 · Vessel V-110 · Drawing HBK-PV-110 rev B

Report no.	**HT-0412**
Date	**2026-10-13**
Code	**ASME VIII-1 UG-99**

TEST DATA

Item **Vessel V-110 after PWHT**		Test medium **Water, chloride < 50 ppm**
Test pressure applied (at top) **1.90 MPa**	Holding time **30 min**	Metal temperature **18 °C**
Water temperature **17 °C**	Inspection pressure **1.90 MPa**	Leaks **None**

GAUGES

Gauge	Range	Serial no.	Calibrated	Due
Test gauge 1	0 - 4 MPa	G-11-4471	2026-07-02	2027-01-02
Test gauge 2	0 - 4 MPa	G-12-4480	2026-07-02	2027-01-02

PRESSURE / TIME

Time	Pressure (MPa)	Note
10:00	0	Start, vents closed
10:20	1.90	Test pressure reached
10:50	1.90	End of hold; examined all welds
11:00	0	Depressurized

Result: no leaks, no visible deformation.

Tested by	Witnessed by
T. Rahman (fictional), QC *signed T. Rahman* 2026-10-13	**J. Hartono (fictional), Authorized Inspector** *signed J. Hartono* 2026-10-13

SYNTHETIC DOCUMENT - generated for software testing - not a real record