Post-Weld Heat Treatment Record

Baytown Heavy Spool Mill (fictional) | Document no. PWHT-118

Chart no.	PWHT-118
Weld	W-04
Procedure	620 C, hold 60 min (W-04 only)
Soak temperature	620 C
Hold time	60 min
Heating / cooling rate	max 150 C/h above 300 C
Date	2026-10-11
Result	Chart attached, within procedure

Authorised signatory	*D. Reyes*
Role	Heat treatment operator
Date	2026-10-11

SYNTHETIC DOCUMENT - generated for software testing - not a real certificate or record