Welding Procedure Specification (WPS)

Baytown Heavy Spool Mill (fictional) | Document no. WPS-07

WPS no.	WPS-07
Supporting PQR	PQR-2291
Code	ASME IX / B31.3
Process	GTAW root + SMAW fill
Base metal	P-No.1 Group 1 (A106 Gr.B, A234 WPB, A105)
Filler metal	ER70S-6 / E7018-1
Position	6G
Preheat	10 C min
Current range	110-140 A
Voltage range	22-26 V
Post-weld heat treatment	620 C, hold 60 min (W-04 only)
Revision	2

Authorised signatory	*T. Okafor*
Role	Welding engineer
Date	2026-06-02

SYNTHETIC DOCUMENT - generated for software testing - not a real certificate or record