HOORVIA - POLYMER CLAY BAKE TIMES CHART: PRINTABLE TEMPERATURE & TIME GUIDE

Quick Reference Cheat Sheet · A4 Printable

Crafting & DIY · Sheet #1

Brand / Clay	Temperature	Time per 1/4 in	Notes
Sculpey III	275°F (135°C)	15 min	Most common beginner clay
Original Sculpey	275°F (135°C)	15 min	Soft, best for simple shapes
Super Sculpey	275°F (135°C)	15 min	Firm, for sculpting detail
Premo! Sculpey	275°F (135°C)	30 min	Strongest Sculpey, for jewelry
Soufflé by Sculpey	275°F (135°C)	30 min	Lightweight, suede finish
Fimo Professional	230°F (110°C)	30 min	Firm, holds fine detail
Fimo Soft	230°F (110°C)	30 min	Softer, easy conditioning
Fimo Effect	230°F (110°C)	30 min	Glitter, metallic, stone effects
Cernit	230-265°F (110-130°C)	30 min	Translucent and doll clays
1/4 in thick (6 mm)	Package temp	15-30 min	Standard reference thickness
1/2 in thick (12 mm)	Package temp	30-60 min	Double the time, same temperature
Oven thermometer	Check before baking	-	Home ovens run 25°F / -4°C off or more