HOORVIA - CRICUT HEAT PRESS TEMPERATURE CHART

Quick Reference Cheat Sheet · US Letter Printable

Crafting & DIY

Material / Blank	Temp F / C	Time	Pressure / Peel
Everyday Iron-On on cotton	315°F / 157°C	30 sec	Firm; warm peel
Everyday Iron-On on polyester	315°F / 157°C	30 sec	Firm; warm peel
Everyday Iron-On on cotton/poly blend	315°F / 157°C	30 sec	Firm; warm peel
Glitter Iron-On on cotton	330°F / 166°C	30 sec	Firm; cool peel
Holographic Iron-On	330°F / 166°C	30 sec	Firm; cool peel
SportFlex Iron-On (activewear)	305°F / 152°C	30 sec	Firm; warm peel
Foiled Iron-On	310°F / 154°C	20 sec	Light; cool peel
Patterned Iron-On	340°F / 171°C	30 sec	Firm; warm peel
Infusible Ink on T-shirt (poly	385°F / 196°C	40 sec	Light; cool peel, handle with gloves
Infusible Ink on coaster (ceramic)	400°F / 204°C	240 sec	Light; cool peel
Infusible Ink on mug (Mug Press)	Follow Mug Press preset	~360 sec	Use Mug Press cycle, not a flat press
Hat (EasyPress on cap)	320°F / 160°C	30 sec	Firm with hat form; warm peel
Tote bag (canvas)	315°F / 157°C	30 sec	Firm; warm peel; press inside seams flat
Wood sign (HTV)	300°F / 149°C	40 sec	Medium; cool peel; seal after

PRO TIP: Print on US Letter or A4 and hang it above or beside your heat press, where you can glance at it while the press heats up. Choose "Save as PDF" in the print dialog for a PDF copy and set Letter or A4 to suit your printer. Because craft rooms collect vinyl scraps, dust and heat, laminate this sheet or put it in a sleeve - it will stay readable far longer than plain paper pinned to a wall. If you use both an EasyPress and a Mug Press, keep this chart with the flat press and write your Mug Press cycle notes in the margin.