HOORVIA - RESIN MIXING RATIO CHART

Quick Reference Cheat Sheet · US Letter Printable

Crafting & DIY

Epoxy - coating / tabletop (1:1)			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
1 part resin : 1 part hardener	Volume	30-45 min	24-72 hrs

Epoxy - general (2:1)			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
2 parts resin : 1 part hardener	Volume (check label)	30-50 min	24-72 hrs

Epoxy - some brands (3:1)			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
3 parts resin : 1 part hardener	Volume (check label)	40-60 min	48-72 hrs

Epoxy - by weight brands			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
Follow label, e.g. 100 : 83 by weight	Weight only	Per label	Per label

Deep-pour epoxy			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
2:1 or 3:1 (per label)	Per label	2-4 hrs	72 hrs - 7 days

UV resin			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
No mixing - ready to use	-	Until UV light applied	2-5 min under UV lamp

Polyester resin			
Mix ratio	**Measure by**	**Working time (approx.)**	**Full cure (approx.)**
Resin + 1-2% catalyst (MEKP)	Weight/volume per label	10-20 min	24 hrs

PRO TIP: Print on US Letter or A4 and keep this chart outside the immediate pouring area, where resin drips cannot reach it - a wall above the workbench is ideal. Choose "Save as PDF" in the print dialog for a PDF copy in Letter or A4, and laminate the printed sheet so it survives a dusty workshop and can be wiped clean. Many resin makers keep a second copy inside a project notebook with notes on which brand and ratio they used for each piece, because "epoxy" alone is not enough information when you reorder months later.