HOORVIA - SUBLIMATION TIME & TEMP: PRINTABLE BLANK GUIDE

Quick Reference Cheat Sheet · US Letter Printable

Crafting & DIY · Sheet #1

Blank Substrate	Heat Press Temp (°F)	Dwell Time (Seconds)	Pressure Level	Peel Temperature
100% Polyester T-Shirt	385°F-400°F / 196°C-204°C	45-60 secs	Medium (40 psi)	Warm Peel
20oz Skinny Tumbler (Press)	385°F / 196°C	50 secs + rotate 50 secs	Firm Pressure	Cool completely
Ceramic Mug (Mug Press)	380°F-400°F / 193°C-204°C	180-240 secs	Medium-Firm	Cool in warm water bath
Hardboard Coasters	400°F / 204°C	60 secs	Medium	Hot Peel
FRP Plastic Keychains	385°F / 196°C	60-75 secs	Medium-Light	Cool under heavy book
Photo Slate Plaque	400°F / 204°C	300-360 secs (Face down)	Medium-Firm	Let cool completely
Polyester Tote Bag	385°F-400°F / 196°C-204°C	45-60 secs	Medium	Warm Peel
Mousepad	400°F / 204°C	60 secs	Medium	Hot Peel
Metal License Plate	400°F / 204°C	60 secs	Medium	Hot Peel
Ceramic Tile	400°F / 204°C	300-420 secs	Medium-Firm	Let cool completely
Polyester Hoodie	385°F-400°F / 196°C-204°C	45-60 secs	Medium	Warm Peel
Stainless Tumbler (Oven)	375°F-400°F / 191°C-204°C	6 min, rotate halfway	-	Cool completely