



FORT WAYNE METALS

9609 Ardmore Ave | Ft Wayne, IN | 46809
260-747-4154

Tuesday, January 20, 2026 12:42:43 PM

Customer	
Quality Order Number	
Production Order Number	
Alloy Type	
Sales Order Number	
Purchase Order Number	
Operator	
Production Machine	
Instron	TT-
Load Cell Used	
Method description	216- Lake 6% Strain 3% Measured
Gage Length	5.00000 in

	Serial Number	Diameter [in]	Breakload [lbf]	Tensile Strength [psi]	Elongation [%]	Upper Plateau Load [lbf]	Upper Plateau Stress [psi]	Lower Plateau Load [lbf]	Lower Plateau Stress [psi]
1		0.02110	38.210	109276	4.5	30.371	86857	30.330	86741
2		0.01387	22.279	147453	25.2	16.033	106111	16.002	105911
Mean		0.01748	30.245	128364	14.8	23.202	96484	23.166	96326
Standard deviation		0.00511	11.26492	26995.71835	14.63710	10.13891	13614.41096	10.13137	13555.81674
Mean + 3 SD		0.03282	64.039	209352	58.7	53.619	137327	53.560	136993
Mean - 3 SD		0.00215	-3.550	47377	-29.1	-7.215	55641	-7.228	55659
Minimum		0.01387	22.279	109276	4.5	16.033	86857	16.002	86741
Maximum		0.02110	38.210	147453	25.2	30.371	106111	30.330	105911

	Yield Load [lbf]	Yield Strength [psi]	Permanent Set [%]	Modulus [Msi]	Visual Surface s Prim	Visual Surface s Sec	Straightness	Out of Roundness
1	30.371	86857	2.08	20.275				
2	16.033	106111	2.33	22.403				
Mean	23.202	96484	2.20	21.339				
Standard deviation	10.13891	13614.41096	0.17773	1.50500				
Mean + 3 SD	53.619	137327	2.74	25.854				
Mean - 3 SD	-7.215	55641	1.67	16.824				
Minimum	16.033	86857	2.08	20.275				



FORT WAYNE METALS

9609 Ardmore Ave | Ft Wayne, IN | 46809
260-747-4154

Tuesday, January 20, 2026 12:42:43 PM

	Yield Load [lbf]	Yield Strength [psi]	Permanent Set [%]	Modulus [Msi]	Visual Surface s Prim	Visual Surface s Sec	Straightness	Out of Roundness
Maximum	30.371	106111	2.33	22.403				

Results Table 2

	Spool Number	Operator
1	697-7 1200C4FPM	
2	697-6 1200C4FPM	

Tensile Test

