

Hypothesizing Novel, Cost-Effective Iron-Based Shape Memory Alloys with Nitinol-Comparable Pseudoelasticity

1. Executive Summary

The exceptional pseudoelastic properties of Nitinol (Ni-Ti) have established it as a benchmark material in various advanced applications. However, its high manufacturing cost, primarily driven by expensive raw materials like titanium and complex processing, significantly limits its widespread adoption.¹ Iron-based shape memory alloys (Fe-SMAs) present a compelling alternative, offering the potential for substantially lower costs due to the abundance of iron, coupled with favorable workability and weldability.³ While some Fe-SMAs have demonstrated remarkable pseudoelastic performance, they often rely on expensive alloying additions, thereby negating some of the inherent cost advantages of an iron base.

This report addresses the critical need for novel Fe-SMA compositions that can achieve pseudoelastic effects comparable to Nitinol while being significantly more economical. The primary objective is to hypothesize a series of new Fe-SMA compositions, grounded in established metallurgical principles and informed by existing research on Fe-SMA systems. These hypotheses are not merely speculative but are built upon an understanding of how specific alloying elements and microstructural features, particularly nano-scale precipitates, govern the thermoelastic martensitic transformations essential for pseudoelasticity.

Key design strategies employed in these hypotheses include: (i) maximizing the use of abundant and inexpensive alloying elements such as manganese (Mn), silicon (Si), aluminum (Al), chromium (Cr), and interstitial carbon (C) and nitrogen (N); (ii) targeting the formation of cost-effective precipitate phases (e.g., complex carbides, nitrides, or modified intermetallics) that can induce the desired pseudoelastic response; and (iii) systematically minimizing or replacing expensive elements like cobalt (Co), tantalum (Ta), and high concentrations of nickel (Ni) found in some current high-performance Fe-SMAs.

The hypothesized alloy families include:

- **Modified Fe-Mn-Al-(Ni) systems:** Aiming to reduce Ni content while introducing other elements like Cr, C, V, or Si to maintain or enhance the efficacy of β (B2-type NiAl) precipitates or introduce secondary beneficial phases.
- **Advanced Fe-Mn-Si-Cr systems:** Building on the very low-cost Fe-Mn-Si base by incorporating specific precipitate formers (e.g., V-C, Al-N) to transition these traditionally shape-memory-effect-focused alloys towards significant

pseudoelasticity.

- **Novel Fe-Al-Cr-Mn interstitial alloys:** Exploring new compositional spaces by leveraging Al, Cr, Mn with C or N to form unique ordered precipitates (e.g., modified κ -carbides or novel nitrides) capable of inducing thermoelastic martensitic transformations.

The successful development of such alloys could revolutionize industries reliant on functional materials, providing high-performance alternatives to Nitinol at a fraction of the cost. This report aims to provide a scientifically robust foundation and a clear roadmap for future experimental research in this promising field. The economic imperative for cheaper alternatives to Nitinol is a strong driver, and the existing body of research on Fe-SMAs confirms that achieving high pseudoelastic performance in iron-based systems is a scientifically attainable goal.⁵

2. Introduction: The Quest for Cost-Effective Pseudoelastic Alloys

2.1. Overview of Shape Memory Alloys and Pseudoelasticity

Shape Memory Alloys (SMAs) are a unique class of metallic materials that exhibit the ability to recover a seemingly permanent strain when subjected to an appropriate stimulus, typically thermal or mechanical. This behavior is rooted in a reversible, diffusionless, solid-state phase transformation between a high-temperature parent phase, known as austenite, and a lower-temperature, more deformable phase called martensite.⁷ Two primary functional properties arise from this transformation: the Shape Memory Effect (SME) and Pseudoelasticity (SE), also referred to as superelasticity.

The SME involves deforming the alloy in its martensitic state and then recovering the original shape upon heating above a critical transformation temperature (austenite finish temperature, A_f).⁹ Pseudoelasticity, on the other hand, is an isothermal phenomenon observed when the alloy is deformed above its A_f . Upon application of stress, the austenite transforms to stress-induced martensite, accommodating large strains (often several percent). When the stress is removed, the martensite reverts to austenite, and the material recovers its original shape, exhibiting a stress-strain curve with a characteristic hysteresis loop.¹¹ This reversible, large-strain deformation without permanent set is highly desirable for various engineering applications.

2.2. The Dominance and Limitations (Cost) of Nitinol

Nickel-Titanium (Ni-Ti) alloys, commonly known as Nitinol, are the most commercially

successful and widely utilized SMAs.⁷ Their dominance stems from an excellent combination of properties, including large recoverable strains (pseudoelastic strains often exceeding 6-8%), good cyclic stability, high corrosion resistance, and notable biocompatibility, making them indispensable in medical devices, aerospace components, and consumer electronics.¹

However, the significant drawback of Nitinol is its high cost.¹ Several factors contribute to this:

1. **Raw Material Costs:** Titanium, a primary constituent, is inherently expensive due to complex extraction and refining processes.¹ Nickel prices also contribute to the overall alloy cost.¹ High-purity raw materials, often required for optimal performance, further escalate costs.¹
2. **Manufacturing Complexity:** Nitinol production involves specialized and tightly controlled processes. Vacuum melting techniques like vacuum induction melting (VIM) or vacuum arc remelting (VAR) are necessary due to the high reactivity of titanium with atmospheric gases.² Subsequent hot and cold working (e.g., wire drawing, sheet rolling) must be carefully managed.
3. **Precise Heat Treatments:** The functional properties of Nitinol are extremely sensitive to its thermomechanical history. Shape setting and annealing heat treatments must be performed with high precision to achieve the desired transformation temperatures and mechanical response.² The material's heat sensitivity means that even minor deviations can compromise performance.
4. **Machining and Finishing:** Nitinol can be challenging to machine, and specialized techniques like laser cutting or electropolishing are often employed, adding to the final component cost.²
5. **Market Demand:** Strong demand from high-value sectors, particularly the medical industry, also influences Nitinol pricing.¹

To effectively hypothesize alternatives, it is crucial to define "comparable pseudoelasticity." Key performance metrics for superelastic Nitinol include recoverable strains typically in the range of 6-8% (potentially up to 10%), forward transformation stresses (austenite to martensite) around 400-700 MPa, reverse transformation stresses (martensite to austenite) around 200-450 MPa, a significant stress hysteresis (often >200 MPa), and high-cycle fatigue life (>10⁷ cycles) at lower strain amplitudes (e.g., 0.4-0.6%).¹⁷

2.3. The Promise of Fe-based SMAs: Advantages and Current Landscape

Iron-based SMAs have emerged as a promising class of materials to challenge Nitinol's dominance, primarily due to the potential for significantly lower material

costs.³ Iron is abundant and inexpensive, forming the basis for the vast steel industry. Beyond cost, Fe-SMAs often exhibit good workability, weldability, and the capacity for large deformation, making them attractive for a wide range of structural and functional applications.⁴

Several families of Fe-SMAs have been investigated, each with distinct characteristics:

- **Fe-Mn-Si Alloys:** These were among the first Fe-SMAs to be developed and are known for their good shape memory effect, arising from a face-centered cubic (fcc, γ -austenite) to hexagonal close-packed (hcp, ϵ -martensite) transformation.³ They are generally very low cost but traditionally exhibit limited pseudoelasticity.¹⁹
- **Fe-Ni-Co-Al-X (X = Ta, Ti, B, etc.) Alloys:** This family, particularly compositions like FeNiCoAlTaB, can exhibit exceptional pseudoelasticity, with recoverable strains exceeding 13% and high strength.⁶ Their properties rely on the precipitation of fine, ordered γ' ($L1_2$ structure) particles. However, the inclusion of expensive elements like Ta and Co can make these alloys costly, sometimes approaching Nitinol's price range, which undermines the primary motivation for seeking Fe-based alternatives if cost is the main driver.⁶
- **Fe-Mn-Al-Ni Alloys:** These alloys have gained significant attention for their excellent pseudoelastic properties over a wide temperature range, high transformation stresses, and considerable recoverable strains (up to 10-12%).⁵ Their pseudoelasticity is attributed to a reversible body-centered cubic (bcc, α -austenite) to an ordered B2 (β -NiAl type) precipitate-mediated transformation. They offer a better cost profile than Fe-Ni-Co-Al-X systems due to the replacement of Co and Ta with Mn.

The development path for Fe-SMAs reveals two main branches: one focusing on achieving ultra-high performance, often at the expense of higher alloy cost (e.g., FeNiCoAlTaB), and another aiming for a more balanced combination of good functional properties and significantly lower cost, primarily utilizing more common and cheaper alloying elements like Mn, Si, Al, Cr, and interstitial elements.⁷ This report focuses on the latter, seeking to bridge the gap between performance and affordability.

2.4. Report Objectives: Hypothesizing Novel, Economical Fe-SMAs

The central objective of this report is to hypothesize a list of novel Fe-SMA compositions that are projected to be substantially cheaper than Nitinol while exhibiting pseudoelastic effects comparable to those of Nitinol. These hypotheses will be scientifically grounded, leveraging existing knowledge on the roles of various alloying elements, the mechanisms of precipitate-induced pseudoelasticity, and the

cost implications of material selection and processing. The proposed alloys are intended to serve as promising candidates for future experimental investigation and development.

3. Benchmarking Nitinol: Performance and Cost

To effectively design Fe-SMA alternatives, it is essential to establish clear benchmarks for Nitinol's pseudoelastic performance and understand its primary cost drivers.

3.1. Key Pseudoelastic Properties of Commercial Superelastic Nitinol

Commercial superelastic Nitinol alloys typically exhibit the following characteristic properties:

- **Recoverable Strain:** Fully recoverable strains are commonly in the range of 6% to 8% under uniaxial tension.¹⁷ Some optimized compositions and forms can achieve up to 10% recoverable strain.¹⁸
- **Transformation Stresses (Plateau Stresses):** These stresses define the stress levels at which the forward (austenite → martensite) and reverse (martensite → austenite) transformations occur.
 - **Upper Plateau Stress (σ_{Ms} or σ_{Afd}):** The stress required to induce martensitic transformation during loading typically ranges from 400 MPa to 700 MPa, depending on composition, processing history, and test temperature.¹⁶ One study reported an upper plateau stress of approximately 650 MPa for a specific Nitinol wire.¹⁷
 - **Lower Plateau Stress (σ_{As} or σ_{Arev}):** The stress at which martensite reverts to austenite during unloading is generally lower, for instance, around 366 MPa in the same study.¹⁷
- **Stress Hysteresis ($\Delta\sigma = \sigma_{Ms} - \sigma_{As}$):** The difference between the upper and lower plateau stresses represents the energy dissipated per cycle. Nitinol exhibits a notable stress hysteresis, often in the range of 200 MPa to 350 MPa.¹⁷ This hysteresis is critical for damping applications but can lead to heat generation during rapid cycling.
- **Fatigue Life:** The fatigue performance of Nitinol is a critical design consideration and is highly sensitive to strain amplitude, mean strain, surface quality, presence of inclusions, and thermomechanical processing.¹⁴
 - At low strain amplitudes (e.g., 0.4% to 0.6%), Nitinol wires can endure a high number of cycles, often reaching 10⁷ to 10⁸ cycles before failure (run-out condition).¹⁷
 - As strain amplitude increases (e.g., to 0.8% - 1.5%), fatigue life decreases significantly, typically to less than 10⁵ - 10⁶ cycles.¹⁷

- Large pre-strains, such as those experienced during crimping of medical stents, can substantially reduce the fatigue life, especially at lower operating strain amplitudes.¹⁷

It is important to recognize that while Nitinol can recover very large strains in a single cycle, its practical use in high-cycle fatigue applications often involves much smaller strain amplitudes to ensure longevity. This distinction is crucial when defining "comparable" pseudoelasticity for potential Fe-SMA replacements.

3.2. Primary Cost Drivers of Nitinol

The high price of Nitinol is a multifaceted issue, stemming from both material and processing factors:

- **Raw Materials:**

- **Titanium (Ti):** Titanium is a relatively expensive metal due to the energy-intensive Kroll process used for its extraction and the need for high-purity sponge.¹ Its cost can be up to ten times higher than aluminum.¹⁵
- **Nickel (Ni):** While less expensive than titanium, nickel is still a significant cost component, and its price can fluctuate.¹ LME nickel prices in April 2025 were around \$15,113 USD/metric ton (approx. \$15.1/kg).²³ * **Purity:** High-purity Nitinol, required for consistent and reliable performance, especially in medical applications, commands a premium price.¹ * **Manufacturing Processes:** * **Melting:** Due to titanium's high reactivity with oxygen and nitrogen at elevated temperatures, Nitinol must be melted under vacuum or inert atmosphere using techniques like Vacuum Induction Melting (VIM) or Vacuum Arc Remelting (VAR). These are more complex and costly than conventional air melting processes used for steels.² * **Forming and Working:** Nitinol can be difficult to work. Processes like wire drawing, tube manufacturing, and sheet rolling require specialized equipment and careful control of parameters to avoid defects and achieve desired microstructures.² * **Heat Treatment (Shape Setting & Annealing):** Achieving the precise transformation temperatures and mechanical properties necessitates very accurate heat treatments. Nitinol is highly sensitive to temperature variations during these processes, demanding sophisticated furnace controls and expertise.² The inherent reactivity of titanium also means these treatments often need to be performed in controlled atmospheres or vacuum. * **Machining and Finishing:** Nitinol's unique properties make it challenging to machine using conventional methods. Laser cutting, Electrical Discharge Machining (EDM), and specialized grinding techniques are often employed. Surface finishing, such as electropolishing for medical implants to improve biocompatibility and

fatigue resistance, adds further cost.² * **Market Factors:** * **Demand in High-Value Sectors:** Significant demand from the medical device and aerospace industries, where performance often outweighs cost concerns, contributes to maintaining a higher price point.¹ * **Geopolitical and Supply Chain Issues:** Fluctuations in the price and availability of raw materials like titanium and nickel can be influenced by geopolitical events and supply chain disruptions, adding to cost volatility.¹ This inherent volatility further motivates the search for alternatives based on more globally abundant and price-stable elements. The combination of expensive raw materials and intricate, tightly controlled manufacturing processes makes Nitinol a premium material. The stringent processing is not arbitrary but a direct consequence of the chemical nature of its constituents (particularly titanium) and the precise microstructural control needed to achieve its unique functional properties.

****Table 1: Benchmark Pseudoelastic Properties and Cost Factors of Commercial Superelastic Nitinol****

Property	Typical Value/Range	Key Cost Drivers
Recoverable Strain (%)	6 - 8% (up to 10%) ¹⁷	Raw Materials (High-purity Ti, Ni) ¹
Upper Plateau Stress (σ_{Ms} , MPa)	400–700 MPa (e.g., 650 MPa) [16,17]	Manufacturing (Vacuum Melting, Specialized Hot/Cold Working) [2]
Lower Plateau Stress (σ_{As} , MPa)	200–450 MPa (e.g., 366 MPa) [17]	Processing (Precision Heat Treatments: Shape Setting, Annealing; High Heat Sensitivity) [2,16]
Stress Hysteresis ($\Delta\sigma$, MPa)	200 - 350 MPa	Machining & Finishing (Laser Cutting, EDM, Electropolishing) ²
Fatigue Life (Cycles at x% strain amplitude)	>10 ⁷ cycles at 0.4-0.6% strain; <10 ⁵ -10 ⁶ cycles at 0.8-1.5% strain ¹⁷	Market Demand (Medical, Aerospace) ¹

This table provides quantitative targets and a cost framework against which proposed Fe-SMAs can be evaluated.

4. Principles of Pseudoelasticity in Fe-based SMAs

The achievement of significant pseudoelasticity in Fe-based alloys hinges on inducing a reversible, stress-induced martensitic transformation. Unlike Nitinol, where this is an intrinsic property of the Ni-Ti intermetallic compound, in Fe-SMAs, pseudoelasticity often requires careful alloy design and microstructural engineering, primarily through the controlled precipitation of secondary phases.

4.1. Martensitic Transformations and Thermoelasticity in Fe-systems

Iron and its alloys can undergo several types of martensitic transformations. Two are

particularly relevant to Fe-SMAs:

1. **FCC (γ) to HCP (ϵ) Transformation:** This transformation is responsible for the shape memory effect observed in Fe-Mn-Si based alloys.³ The γ (austenite) phase transforms to ϵ (martensite) upon cooling or stressing. This transformation is typically non-thermoelastic, meaning the interface between austenite and martensite does not move back smoothly upon stress removal or heating, and often involves a large hysteresis and permanent deformation if not carefully controlled.²⁵
2. **BCC (α) or BCT (α') to FCC (γ) or other complex structures:**
 - In Fe-Mn-Al-Ni alloys, a transformation from a bcc parent phase (often denoted α or A2) to an fcc product phase (or more complex structures like DO₃ or L2₁ depending on ordering) is responsible for pseudoelasticity.²¹
 - In Fe-Ni-Co-Al-X alloys, the transformation is typically from an fcc parent phase (γ) to a body-centered tetragonal (bct) martensite (α').²¹

For an alloy to exhibit good pseudoelasticity, the martensitic transformation must be **thermoelastic**. A thermoelastic transformation is characterized by a mobile interface between the parent and martensite phases, a small thermal hysteresis, and the ability of the martensite to accommodate strain elastically or through reversible twinning, such that upon unloading, the stored elastic energy drives the reverse transformation.⁷ Achieving this in Fe-based systems is a primary goal of alloy design for pseudoelasticity. For instance, the addition of Tantalum to Fe-Ni-Co-Al alloys was found to render the martensitic transformation thermoelastic, a key factor for their excellent superelasticity.⁶

4.2. The Critical Role of Precipitates

In many Fe-SMAs showing significant pseudoelasticity, the key to achieving a thermoelastic martensitic transformation and good reversibility lies in the formation of fine, coherent (or semi-coherent) nano-precipitates within the parent phase.²⁰ These precipitates play several crucial roles:

- **Strengthening the Parent Phase:** They increase the critical stress required for slip (plastic deformation) in the austenite matrix, ensuring that martensitic transformation occurs before extensive dislocation activity, which would lead to irrecoverable strain.²⁰
- **Generating Internal Stress Fields:** Coherent precipitates create elastic strain fields in the surrounding matrix. These internal stresses can assist in the nucleation of martensite and aid in the reverse transformation upon unloading by

providing a back-stress that favors the parent phase.²¹

- **Modifying Transformation Pathway:** Precipitates can act as heterogeneous nucleation sites for martensite, influence the morphology of martensite variants, and help accommodate transformation strains, thereby promoting reversibility.²⁹
- **Ensuring Coherency:** The coherency or semi-coherency of these nano-precipitates with the matrix is vital. If precipitates lose coherency (e.g., by growing too large), their effectiveness in promoting reversible transformation diminishes, and they may act as sites for crack initiation or irreversible plastic deformation.³²

Different Fe-SMA systems utilize different types of precipitates:

- **γ' (Gamma Prime) Precipitates:** These are typically L1₂ ordered intermetallic phases, such as Ni₃Al-type or (FeNiCo)₃(AlTa)-type. They are fundamental to the pseudoelasticity of Fe-Ni-Co-Al-X (X = Ta, Ti, B) alloys.⁶
 - **Size and Coherency:** Optimal sizes are generally in the range of 3-10 nm for good superelasticity.²⁰ Boron addition in FeNiCoAlTaB alloys helps refine γ' precipitate size to around 3-4 nm and importantly suppresses the formation of a brittle β (B2 NiAl-type) phase at grain boundaries, which would otherwise degrade pseudoelastic performance.²⁰
 - **Volume Fraction:** A sufficient volume fraction of these fine, coherent precipitates is necessary to achieve large reversible strains.²⁰
- **β (B2-ordered) Precipitates:** These are typically NiAl-rich precipitates with a B2 (ordered bcc) crystal structure. They are responsible for the pseudoelastic behavior in Fe-Mn-Al-Ni alloys.²¹
 - **Formation:** They form coherently within the α -Fe (bcc) matrix.
 - **Size:** Optimal sizes for promoting pseudoelasticity are reported to be around 6-16 nm.³² Larger precipitates can lead to increased stress hysteresis and deterioration of superelastic performance due to coherency loss.³²
- **Carbide Precipitates:** Various carbides play significant roles in different Fe-SMA systems.
 - **VC, NbC:** Vanadium carbide (VC) and Niobium carbide (NbC) precipitates are known to improve the shape memory effect in Fe-Mn-Si based alloys by strengthening the austenite and promoting the $\gamma \rightarrow \epsilon$ transformation.²⁹
 - **(Cr-V-C)-rich Precipitates:** In the Fe-17Mn-5Si-10Cr-4Ni-1(V-C) alloy, fine, parallelogram-shaped (Cr-V-C)-rich precipitates, along with elliptical V-rich precipitates, have been shown to induce excellent pseudoelasticity.³⁰ These precipitates promote the formation of numerous parallel stacking faults, which reduce the activation energy for ϵ -martensite nucleation and inhibit the formation of detrimental α' -martensite, thereby reducing residual strain.³⁰

- **κ -Carbides ((Fe,Mn) $_3$ AlC):** These L1 $_2$ ordered carbides are characteristic of Fe-Mn-Al-C lightweight steels. They primarily contribute to significant strengthening and improved ductility in these steels.³⁸ While L1 $_2$ precipitates are known to induce pseudoelasticity in other Fe-SMA systems (like γ' in FeNiCoAlX), the direct role of κ -carbides in producing large, Nitinol-comparable pseudoelastic strains in Fe-Mn-Al-C systems is not yet well-established for this purpose, though their structural similarity to γ' suggests potential if engineered correctly.
- **Nitride Precipitates:** The role of nitrides in promoting bulk pseudoelasticity in Fe-SMAs is less explored than carbides or intermetallics, but they offer potential.
 - **AlN:** Aluminum nitride (AlN) precipitation at grain boundaries can be detrimental to hot ductility in some steels.⁴⁰ However, if AlN can be formed as fine, dispersed intra-granular precipitates, it could offer strengthening.
 - **VN:** Vanadium nitride (VN) precipitates have been suggested to improve SME in Fe-SMAs, similar to VC.⁴¹ Their specific impact on pseudoelasticity warrants further study.
 - **CrN, TiN:** These have been observed in surface layers after specific treatments (like EDM with nitrogen dielectric) and contribute to surface hardness and wear resistance, but this is distinct from bulk pseudoelasticity mechanisms.⁴³
 - The general principle is that fine, coherent nitride particles could strengthen the austenite matrix and influence the martensitic transformation favorably if their type, size, and distribution are carefully controlled.

The effectiveness of carbon, a common and inexpensive alloying element, is highly dependent on its form. When it participates in the formation of beneficial nano-scale carbides like VC or (Cr-V-C) through controlled precipitation, it can significantly enhance SME and PE.²⁹ However, if present as untailored interstitial carbon or as coarse, undesirable carbides, its contribution to pseudoelasticity might be negligible or even detrimental. Thus, it is not merely the presence of an element, but its specific microstructural manifestation, that dictates its functional impact.

4.3. Influence of Grain Size, Texture, and Processing

Beyond composition and precipitates, other microstructural and processing factors significantly influence the pseudoelastic behavior of Fe-SMAs:

- **Grain Size:** The effect of grain size is system-dependent.
 - For alloys like FeNiCoAlTaB, a large grain size (e.g., >400 μm) or even single crystals are often preferred to maximize recoverable strain.⁶ This is attributed to reduced constraint from grain boundaries, allowing for more homogeneous

- transformation and larger transformation strains within individual grains.⁵
- Conversely, in some Fe-Mn-Si based systems engineered for pseudoelasticity (e.g., Fe-17Mn-5Si-10Cr-4Ni-1(V-C)), grain refinement (e.g., to ~5 μm) coupled with optimized precipitation has been shown to enhance pseudoelasticity and cyclic stability.³⁶ Refined grains can promote a more uniform distribution of precipitates and modify martensite morphology favorably. For practical, cost-effective polycrystalline alloys, achieving optimized properties in finer-grained structures may be more scalable than relying on producing very large grains or single crystals, which adds to processing cost and complexity.
 - **Texture:** A strong crystallographic texture can be beneficial for pseudoelasticity, especially in alloys with anisotropic transformation strains. Aligning a high-strain crystallographic direction with the loading axis can maximize the macroscopic recoverable strain.⁴⁴ Directional solidification is one method to achieve such textures.⁴⁴
 - **Processing:**
 - **Solution Treatment and Aging:** These are arguably the most critical processing steps for Fe-SMAs that rely on precipitation. Solution treatment dissolves alloying elements, and subsequent aging at specific temperatures and times controls the nucleation and growth of the desired nano-precipitates (size, volume fraction, distribution).²⁰
 - **Thermomechanical Training:** Repeated stress or strain cycling through the transformation region can "train" some Fe-SMAs, improving the shape memory effect or pseudoelastic response by creating favorable dislocation structures or aligning martensite variants.⁷
 - **Additive Manufacturing (AM):** AM techniques like Laser Powder Bed Fusion (LPBF) are being explored for fabricating Fe-SMAs with complex geometries.⁴ However, controlling the microstructure (grain size, texture, precipitate formation) during AM to achieve optimal functional properties remains a significant challenge due to rapid solidification and complex thermal histories.⁴⁶

4.4. Key Alloying Elements and Their Impact

The choice of alloying elements is fundamental to designing Fe-SMAs with desired properties and cost:

- **Fe (Iron):** The base element, offering low cost and good general mechanical properties. Price (2020): ~\$0.42/kg.⁴⁸
- **Mn (Manganese):** An austenite stabilizer, crucial in Fe-Mn-Si and Fe-Mn-Al-Ni

systems. It can lower stacking fault energy, promoting the $\gamma \rightarrow \epsilon$ transformation in Fe-Mn-Si alloys.³ Cost-effective. Price (2019): ~\$1.82/kg.⁴⁸ Ferromanganese is a common addition.

- Si (Silicon):** In Fe-Mn-Si alloys, Si strengthens austenite, raises its resistance to slip, and suppresses the formation of undesirable α' -martensite, thereby improving SME.⁷ Very cost-effective. Price (2019): ~\$1.70/kg.⁴⁸ Ferrosilicon price (May 2025, ZCE): ~5600 CNY/tonne (~\$0.77/kg Si, assuming 75% Si in FeSi and current exchange rates).⁴⁹ Metal silicon price (Global, May 2025): ~\$1.79/kg.⁵⁰
- Al (Aluminum):** A key element for forming γ' precipitates in Fe-Ni-Co-Al-X systems and β (B2 NiAl-type) precipitates in Fe-Mn-Al-Ni alloys, both essential for pseudoelasticity.²⁰ It is a ferrite stabilizer. Cost-effective. Price (2019): ~\$1.79/kg.⁴⁸ LME Aluminium price (May 2025): ~\$2440/tonne (~2.44/kg). [51]***Ni(Nickel):**Essential for forming Ni-containing precipitates (γ and β) that induce pseudoelasticity in Fe-Ni-Co-Al-X and Fe-Mn-Al-Ni systems.²⁰ Also an austenite stabilizer. Moderate cost. Price (2019): ~\$13.9/kg.⁴⁸ LME Nickel price (May 2025): ~\$15.43/kg.²⁴
- Co (Cobalt):** Used in Fe-Ni-Co-Al-X alloys to strengthen the matrix, raise the Curie temperature, and participate in γ' precipitate formation.²⁰ Expensive. Price (2019): ~\$32.8/kg.⁴⁸ LME Cobalt price (May 2025): \$33700/tonne (\$33.70/kg).⁵⁴
- Ta (Tantalum):** Promotes thermoelastic martensitic transformation in Fe-Ni-Co-Al-Ta-B alloys by influencing γ' precipitate characteristics.⁶ Very expensive. Price (2020, SMM): \$61.4-85.6/kg for Nb, Ta often higher.⁴⁸ Tantalum metal 99.95% (Oct 2024): ~\$320/kg.⁵⁵ Tantalum powders (May 2025): ~\$306-343/kg.⁵⁶
- B (Boron):** Acts as a grain boundary refiner and can suppress the formation of brittle second phases (e.g., β phase in FeNiCoAlTaB).²⁰ Can also influence precipitate size. Cost-effective when added as ferroboron. Ferroboron (14-20% B) price (May 2025): ~\$0.8-1.0/kg of alloy for lower grade, implying B cost of ~\$4-7/kg of B if using 15% B content ferroboron; other listings show \$6-8/kg for ferroboron product.⁵⁷ Pure boron (2019): ~\$3.68/kg.⁴⁸
- Cr (Chromium):** Primarily added for corrosion resistance. Can also influence austenite stability, transformation temperatures, and participate in carbide formation (e.g., (Cr-V-C)-rich precipitates).⁷ Moderate cost. Price (2019): ~\$9.40/kg.⁴⁸ Ferrochrome (HCFerCr, 50-70% Cr) is the common addition; e.g., HCFerCr (57-65% Cr) at \$3.00/kg for large quantities.⁶¹
- V (Vanadium):** Forms fine VC or complex (Cr-V-C) carbides that improve SME and PE in Fe-Mn-Si based systems.²⁹ Can also form nitrides (VN). Moderate to high cost. Price (2020, SMM): \$357-385/kg (this seems extremely high, likely for pure V or specific compounds, not ferrovandium).⁴⁸ Ferrovandium (80% V)

price (May 2025): ~\$24.10/kg of V.⁶²

- **Ti (Titanium metal):** Can form γ' precipitates in FeNiCoAlTi alloys, refine grain size, and affect precipitate morphology.⁵ Forms TiC and TiN. Titanium metal itself is expensive. Price (2020, SMM): \$11.1-11.7/kg.⁴⁸ Ferrotitanium (e.g., 30% Ti) price (May 2025): ~\$1.52/kg of alloy, implying Ti cost of ~\$5/kg of Ti.⁶⁴
- **Nb (Niobium):** Forms NbC precipitates, which significantly improve SME in Fe-Mn-Si alloys.²⁹ Can be a component in FeNiCoAlX systems. Expensive. Price (2020, SMM): \$61.4-85.6/kg.⁴⁸ Standard Ferroniobium (60-70% Nb) price (2020): ~\$45/kg of Nb content.⁶⁵ Alibaba listings for FeNb show wide range, e.g., \$27-45/kg for FeNb alloy.⁶⁶
- **C (Carbon):** Forms various carbides (VC, NbC, (Cr-V-C), κ -carbides). Strengthens austenite. Can lower martensite start (Ms) temperature. Very low cost. Price (2018, Coal based): ~\$0.12/kg.⁴⁸ Metallurgical coke (Mar 2025): ~1633 CNY/tonne (~\$0.22/kg).⁶⁷ Graphite prices vary by flake size, e.g., \$500-2300/tonne.⁶⁸ * **N (Nitrogen):** Forms various nitrides (AlN, TiN, VN, CrN). Can provide precipitation strengthening and modify austenite stability. Nitrogen gas is very low cost, but nitriding processes or specialized N-alloyed steel production can add cost. This understanding of elemental roles and costs is foundational for hypothesizing new, economically viable Fe-SMAs. ## 5. Review of Promising Fe-based SMA Systems for Pseudoelasticity Several Fe-based SMA systems have demonstrated notable pseudoelastic properties. A review of these systems highlights successful strategies and remaining challenges, particularly concerning the balance between performance and cost. ### 5.1. Fe-Ni-Co-Al-X (X=Ta, Ti, B, etc.): High Performance, High Cost This family of alloys, particularly compositions like Fe-28Ni-17Co-11.5Al-2.5Ta-0.05B (at.%) (often referred to as FeNiCoAlTaB), stands out for its exceptional pseudoelastic characteristics. It can exhibit recoverable strains greater than 13% and tensile strengths around 1.2 GPa.⁶ The remarkable superelasticity is attributed to a thermoelastic martensitic transformation from an fcc (γ) parent phase to a bct (α') martensite, which is critically dependent on the precipitation of nano-sized, coherent γ' (L1₂ ordered) particles. These precipitates are typically of the (FeNiCo)₃(AlTa) type or Ni₃Al-type if Ta is absent.²⁰

The role of specific alloying elements is crucial:

- **Tantalum (Ta):** Induces thermoelasticity in the martensitic transformation, which is essential for achieving high reversibility and low hysteresis.⁶
- **Boron (B):** Added in small amounts (e.g., 0.05 at.%), boron is effective in suppressing the formation of a brittle β (B2 NiAl-type) phase at grain boundaries, which would otherwise compromise ductility and superelasticity. Boron also helps

refine the size of the γ' precipitates to an optimal range of 3–4 nm.⁶

- **Aluminum (Al) and Nickel (Ni):** These are primary formers of the γ' precipitates.
- **Cobalt (Co):** Strengthens the matrix and influences the Curie temperature and magnetic properties, which can also affect transformation characteristics.

Processing of these alloys typically involves solution treatment followed by aging (e.g., at 700°C for FeNiCoAlTaB) to control the size and distribution of γ' precipitates.²⁰ For optimal performance, large grain sizes (often >400 μm) or even single crystals are preferred to minimize grain boundary constraints.⁶

Despite their outstanding functional properties, the major drawback of Fe-Ni-Co-Al-X alloys is their high cost. The reliance on expensive elements like tantalum (Ta prices can exceed \$300/kg⁵⁵), cobalt (Co price ~\$33.7/kg⁵⁴), and often high nickel content (Ni price ~\$15.4/kg²⁴) makes them economically uncompetitive with Nitinol for many applications where cost is a primary concern. This high cost directly conflicts with the objective of finding a *cheaper* alternative to Nitinol.

5.2. Fe-Mn-Al-Ni(-Ti): Excellent Pseudoelasticity with Lower Cost Potential

The Fe-Mn-Al-Ni system has emerged as a highly promising candidate for achieving excellent pseudoelasticity with a more favorable cost profile compared to the Fe-Ni-Co-Al-X family. These alloys can exhibit recoverable strains up to 10–12%, high transformation stresses (500–700 MPa), and a remarkably wide superelastic temperature window, often spanning from cryogenic temperatures (–196°C) to well above room temperature (>240°C).⁵ This weak temperature dependence of transformation stress is a significant practical advantage.²¹ The pseudoelastic mechanism in Fe-Mn-Al-Ni alloys is attributed to a reversible stress-induced martensitic transformation from a bcc (α -austenite) parent phase. This reversibility is critically enabled by the precipitation of coherent, nano-scale β particles, which are B2-ordered NiAl-type intermetallics, within the α -Fe matrix.²¹ Optimal precipitate sizes are typically in the range of 6–16 nm.³²

Key alloying elements and their roles:

- **Iron (Fe), Manganese (Mn), Aluminum (Al):** Form the bcc parent phase. Mn acts as an austenite stabilizer and influences transformation temperatures. Al is crucial for forming the β precipitates with Ni and also stabilizes the bcc structure.
- **Nickel (Ni):** Essential for the formation of the NiAl-type β precipitates.²¹
- **Titanium (Ti):** Small additions of Ti (e.g., in FeMnAlNiTi alloys like Fe₄₂Mn₃₄Al₁₅Ni_{7.5}Ti_{1.5}) can improve processability by circumventing quenching sensitivity issues associated with some FeMnAlNi compositions. Ti can also promote abnormal grain growth (AGG), facilitating the production of large single crystals which often exhibit enhanced pseudoelasticity, and can modify precipitate morphology.⁵

The cost of Fe-Mn-Al-Ni alloys is considerably lower than Fe-Ni-Co-Al-X systems

because expensive elements like Co and Ta are replaced by much cheaper Mn. However, the Ni content (typically 7.5 at.% or higher) still represents a notable cost factor.

5.3. Fe-Mn-Si based alloys (with Cr, Ni, V, C, etc.): Primarily SME, but emerging PE potential

Traditionally, Fe-Mn-Si based alloys, often with additions of Cr and Ni for corrosion resistance (e.g., Fe-28Mn-6Si-5Cr), are known for their good shape memory effect (SME) due to the γ (fcc) $\leftrightarrow$ ϵ (hcp) martensitic transformation.³ These alloys are very attractive due to their extremely low raw material cost (Fe, Mn, Si are all inexpensive) and excellent workability, machinability, and weldability.⁷ However, the $\gamma \leftrightarrow \epsilon$ transformation in these conventional compositions is generally non-thermoelastic, resulting in poor pseudoelasticity.⁷

A significant development has been the demonstration of excellent pseudoelasticity in a modified Fe-Mn-Si system:

- **Fe-17Mn-5Si-10Cr-4Ni-1(V-C) (wt%):** This alloy, after specific thermomechanical processing (cold rolling, recrystallization, and double aging), exhibits remarkable pseudoelastic behavior. It can achieve minimal residual strain (e.g., 0.12% after 50 cycles at 500 MPa) and significant pseudoelastic strain recovery (e.g., PE strain ratio of 43-53% in incremental tests up to 10% total strain).³⁰ The mechanism involves the precipitation of fine (Cr-V-C)-rich and V-rich carbides. These precipitates strengthen the austenite, promote the formation of stacking faults (which act as preferential nucleation sites for ϵ -martensite), reduce the energy barrier for ϵ -martensite nucleation, and critically, inhibit the formation of detrimental α' -martensite, which would otherwise lead to irrecoverable strain.³⁰ This system demonstrates that a very low-cost base (Fe-Mn-Si) can be engineered to exhibit significant PE.

Other carbide formers like Nb (forming NbC) or nitride formers like V (forming VN) have also been shown to improve the SME in Fe-Mn-Si alloys.²⁹ Their potential to induce substantial pseudoelasticity is an area of active research.

5.4. Lessons Learned: Successful Strategies and Remaining Challenges

The review of these systems highlights several key points:

- **Precipitate Engineering is Key:** The transition from basic SME (or no shape memory behavior) to significant SE in Fe-based alloys is almost universally linked to the successful engineering of specific nano-scale, coherent (or semi-coherent)

precipitates that render the martensitic transformation thermoelastic. The type of precipitate (γ' , β , complex carbides) varies with the base alloy chemistry.

- **Cost vs. Performance Trade-off:** High-performance Fe-SMAs like FeNiCoAlTaB achieve excellent PE but at a high material cost due to elements like Ta and Co, making them less suitable as "cheaper than Nitinol" alternatives.
- **Emerging Low-Cost PE Pathways:** The Fe-Mn-Al-Ni system offers a good balance of PE and moderate cost. Critically, the recent advancements in Fe-Mn-Si-Cr-Ni-VC alloys demonstrate that very low-cost base systems can be "upgraded" to exhibit substantial PE through careful alloying with relatively inexpensive elements like V and C to form specific functional precipitates. This pathway is particularly promising for meeting the user's query.
- **Challenges Remain:** Achieving good cyclic stability (resistance to functional fatigue and accumulation of residual strain) is a persistent challenge for many Fe-SMAs.⁵ Grain boundary embrittlement due to undesirable precipitate phases can also be an issue in some systems if not properly controlled.²⁰ Balancing the often conflicting requirements for optimal PE (e.g., large grains in some systems) with practical processability and cost for polycrystalline materials is another hurdle.

Table 2: Key Characteristics of Established Pseudoelastic Fe-based SMA Systems

Alloy System	Typical Composition (at% or wt%)	Dominant Precipitate(s) for PE (Type, Structure)	Achieved Pseudoelastic Properties (Recoverable Strain, Transformation Stress, Hysteresis, SE Temp. Window)	Primary Costing Elements	Key Limitations/Challenges
Fe-Ni-Co-Al-Ta-B	e.g., Fe _{40.5} Ni ₂₈ Co ₁₇ Al _{11.5} Ta _{2.5} B _{0.05}	γ' ((FeNiCo) ₃ (AlTa) ₂) ²⁰	>13% strain, ~1.2 GPa strength, wide hysteresis, Room Temp	Ta, Co, Ni	Very high cost, often requires large grains/single crystals, cyclic

	}\$(at.%) ⁶		SE ⁶		degradation ²⁰
Fe-Mn-Al-Ni(-Ti)	e.g., Fe _{43.5} Mn ₃₄ Al ₁₅ Ni _{7.5} (at.%) ²¹ , Fe ₄₂ Mn ₃₄ Al ₁₅ Ni _{7.5} Ti _{1.5} (at.%) ⁵	β (NiAl-type, B2) ²¹	Up to 10-12% strain, 500-700 MPa stress, wide SE window (-196 to >240°C) ⁵	Ni, Mn	Moderate cost (Ni), cyclic degradation, sensitivity to processing for optimal β phase ⁵
Fe-Mn-Si-Cr-Ni-VC	e.g., Fe-17Mn-5Si-10Cr-4Ni-1(V-C) (wt%) ³⁰	(Cr-V-C)-rich & V-rich carbides ³⁰	~2.7-4% recoverable strain (lab tests), minimal residual strain over cycles, good PE strain ratio ³⁰	V (Ni if present)	Lower total recoverable strain compared to others so far, complex precipitation, requires careful thermomechanical processing.

This comparative overview sets the stage for hypothesizing new alloys by identifying successful strategies (precipitate-induced thermoelasticity) and key limitations (cost, cyclic stability) to address.

6. Strategies for Designing Novel Low-Cost, High-Performance Fe-SMAs

The overarching goal is to design Fe-SMAs that emulate the desirable pseudoelastic properties of Nitinol but at a substantially lower cost. This requires a multi-pronged strategy focusing on material composition, precipitate engineering, and microstructural control, all while keeping economic viability at the forefront.

6.1. Leveraging Abundant and Inexpensive Alloying Elements

The foundation of cost-effective Fe-SMAs lies in maximizing the use of elements that

are abundant and relatively inexpensive.

- **Base Elements:** Iron (Fe) is the cornerstone due to its extremely low cost and wide availability.⁴⁸ Manganese (Mn), silicon (Si), and aluminum (Al) are also prime candidates for major alloying additions due to their low cost and beneficial metallurgical effects in Fe-based systems (e.g., austenite stabilization by Mn, solid solution strengthening by Si, ferrite stabilization and precipitate formation with Al).³
- **Secondary Elements:** Chromium (Cr) offers a good balance of moderate cost and significant benefits, primarily improved corrosion resistance (a key advantage of Nitinol) and its ability to influence austenite stability and participate in the formation of beneficial carbides.⁷
- **Interstitial Elements:** Carbon (C) and Nitrogen (N) are extremely low-cost and can be powerful alloying additions when used to form specific, finely dispersed carbide or nitride precipitates that strengthen the matrix and influence phase transformations.²⁹
- **Strategic Minor Additions:** Elements like Vanadium (V) and Titanium (Ti), while more expensive than Fe, Mn, Si, or Al, can be considered in small quantities if they lead to the formation of highly effective precipitates (e.g., VC, (Cr-V-C), TiC, TiN) that significantly enhance pseudoelasticity.⁵ The cost-benefit of their inclusion must be carefully weighed.

6.2. Targeting Alternative Cost-Effective Precipitate Formers

The success of high-performance Fe-SMAs like FeNiCoAlTaB (with γ' precipitates) and FeMnAlNi (with β precipitates) underscores the importance of nano-scale coherent precipitates. The strategy here is to identify elemental combinations that can form functionally analogous precipitates using cheaper constituents.

- **Moving Beyond Expensive γ' Formers:** Tantalum is prohibitively expensive for a low-cost Nitinol alternative. While Ni is crucial for γ' (Ni₃Al) and β (NiAl), efforts should be made to reduce its content or find synergistic additions that enhance its efficacy at lower concentrations.
- **Exploring Complex Carbides and Nitrides:**
 - **Carbides:** Instead of relying solely on intermetallic precipitates, the formation of complex carbides such as (Fe,Mn,Cr)_x(Al,Si,V,Ti)_yC_z should be explored. The success of (Cr-V-C)-rich precipitates in Fe-Mn-Si-Cr-Ni-VC systems provides a strong precedent.³⁰
 - **Nitrides:** Fine, coherent nitrides like AlN, VN, CrN, or even Si₃N₄ (potentially interacting with the matrix if Si is present) could provide significant austenite strengthening if their precipitation can be controlled to

be intragranular and nano-scale.⁴⁰ Mn-Al-N systems might also offer unexplored possibilities.

- **Focus on Coherency and Ordered Structures:** The target precipitates should ideally be coherent or semi-coherent with the parent matrix and possess an ordered crystal structure (e.g., L1₂ as seen in γ' and κ -carbides, or B2 in β -NiAl). Such characteristics are known to be effective in inducing thermoelastic martensitic transformations.

6.3. Minimizing or Replacing Expensive Elements (e.g., Co, Ta, high Ni content)

A direct approach to cost reduction is the systematic substitution or elimination of high-cost elements.

- **Cobalt (Co) and Tantalum (Ta):** These should be avoided entirely if the goal is a significantly cheaper alloy than Nitinol. Their contributions to matrix strengthening (Co) or thermoelasticity (Ta) must be achieved through other, less expensive means.⁷⁴
- **Nickel (Ni):** While Ni is a potent precipitate former (NiAl, Ni₃Al), its content should be minimized. Strategies could involve:
 - Identifying elements that can partially substitute for Ni in known precipitate structures without losing efficacy.
 - Designing new precipitate types that require less or no Ni.
 - Enhancing the strengthening effect of Ni-containing precipitates through co-alloying with cheaper elements.

6.4. Microstructural Design for Enhanced Reversibility and Cyclic Stability

Achieving the desired pseudoelastic response requires careful control over the alloy's microstructure beyond just precipitate characteristics.

- **Optimized Heat Treatments:** Solution annealing and aging treatments (temperature and time) are critical for controlling precipitate nucleation, growth, and distribution. The aim is to achieve a high density of nano-scale (e.g., 5-20 nm) coherent precipitates uniformly dispersed within the grains.
- **Grain Size Control:** The optimal grain size is system-dependent. While some high-performance systems benefit from very large grains or single crystals to minimize intergranular constraints⁶, this is often not practical for low-cost, bulk production. Exploring strategies for achieving good pseudoelasticity in fine-to-medium grained polycrystalline structures (e.g., 5-50 μm) through optimized precipitate distribution and grain boundary engineering is crucial. Grain refinement can sometimes improve the uniformity of precipitation and modify martensite variant interactions favorably.³⁶

- **Thermomechanical Processing:** Controlled hot or cold working prior to final heat treatments can introduce beneficial dislocation substructures or crystallographic textures that may enhance the pseudoelastic response or improve cyclic stability.

A critical consideration is that the processing route itself must be cost-effective. Complex, multi-stage heat treatments, or processes requiring highly specialized equipment (like those for single crystal growth), can negate any savings from cheaper raw materials. Therefore, designs favoring simpler melt-work-heat treat cycles, compatible with standard steel industry practices where possible, are preferred.

Table 3: Relative Cost and Metallurgical Role of Key Alloying Elements in Fe-SMAs

Element	Typical Form in Steelmaking	Indicative Price (USD/kg of element content, May 2025 or latest available)	Primary Role(s) in Fe-SMAs related to PE	Cost Category
Fe	Base Metal	~0.10 (Steel Billet/Slab) ⁴⁸	Matrix	Very Low
Mn	Ferromanganese (~75-80% Mn)	~1.65-1.83 (for contained Mn from EMM price ⁷⁶) / ~1.82 (2019) ⁴⁸	Austenite stabilizer, SFE modifier, precipitate component	Low
Si	Ferrosilicon (~75% Si) / Silicon Metal	~1.03 (for contained Si from FeSi ⁴⁹) / ~1.79 (Si metal ⁵⁰) / ~1.70 (2019) ⁴⁸	Austenite strengthener, suppresses α' , precipitate component	Low
Al	Aluminum Metal	~2.44 ⁵¹ / ~1.79 (2019) ⁴⁸	Ferrite stabilizer, forms $\beta(\text{NiAl})$ & $\gamma'(\text{Ni}_3\text{Al})$ -typ	Low

			e precipitates, forms AlN	
Ni	Nickel Metal	~15.43 ²⁴ / ~13.9 (2019) ⁴⁸	Austenite stabilizer, forms β (NiAl) & γ' (Ni ₃ Al)-type precipitates	Medium
Cr	Ferrochrome (e.g., HCrFeCr ~60% Cr)	~5.00 (for contained Cr from HCrFeCr ⁶¹) / ~9.40 (2019) ⁴⁸	Corrosion resistance, austenite/ferrite stabilizer, carbide former (e.g., (CrVC))	Medium
V	Ferrovandium (~80% V)	~24.10 (for contained V ⁶²) / 48	Forms VC, (CrVC) carbides, VN nitrides for SME/PE	Medium-High
C	Metallurgical Coke, Graphite	~0.22 (Coke ⁶⁷) / ~0.5-2.3 (Graphite ⁶⁸)	Interstitial strengthener, forms various carbides (κ , VC, NbC, etc.)	Very Low
N	Nitrogen Gas / Nitrided Ferroalloys	Very low (gas); processing adds cost	Interstitial strengthener, forms various nitrides (AlN, VN, CrN, etc.)	Low (element); Medium (processing)
Ti	Ferrotitanium (~30-70% Ti) / Titanium Sponge	~5.00 (for contained Ti from FeTi ⁶⁴) / ~11.1-11.7 (metal, 2020) ⁴⁸	Forms TiC, TiN, γ' (Ni ₃ (Al,Ti))-type precipitates, grain refiner	High (metal); Medium (FeTi)
B	Ferroboration (~15-20% B)	~4.00-7.00 (for contained B from FeB ⁵⁷) / ~3.68 (pure,	Grain boundary refiner, suppresses brittle phases,	Low-Medium (FeB)

		2019 ⁴⁸⁾	can affect precipitates	
Co	Cobalt Metal	~33.70 ⁵⁴ / ~32.8 (2019) ⁴⁸	Matrix strengthener, raises Curie temp, γ' component	High
Nb	Ferroniobium (~65% Nb)	~45.00 (for contained Nb ⁶⁵) / ~61.4-85.6 (metal, 2020 ⁴⁸)	Forms NbC precipitates for SME	High
Ta	Tantalum Metal/Oxide	>300 (metal ⁵⁵)	Promotes thermoelasticity via γ' in FeNiCoAlTaB	Very High

Note: Prices are indicative and can vary significantly based on purity, form, market conditions, and supplier. Prices for ferroalloys are converted to price per kg of the contained element for better comparison. The "Cost Category" is relative to the context of developing low-cost SMAs. This table is instrumental in guiding the selection of elements for the hypothesized alloys, ensuring that cost-effectiveness is a primary design consideration.

7. Hypothesized Novel Fe-based SMA Compositions for Enhanced Pseudoelasticity and Reduced Cost

Based on the principles and strategies outlined, the following novel Fe-based SMA compositions are hypothesized. For each, the rationale, targeted microstructure, anticipated mechanism, cost strategy, guiding research, and potential challenges are discussed. All compositions are given in weight percent (wt%) unless otherwise specified.

7.1. Alloy Family A: Modified Fe-Mn-Al-(Ni) Systems

Rationale: These alloys aim to leverage the established pseudoelasticity of the Fe-Mn-Al-Ni system, which relies on β (B2 NiAl-type) precipitates ²¹, but with modifications to reduce cost (primarily by lowering Ni content) and potentially enhance properties through synergistic additions.

Hypothesis A1: Fe-Mn-Al-(low Ni)-Cr-(C/V)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Mn (25-35%), Al (10-15%), Ni (2-5%), Cr (3-8%), and either C (0.1-0.5%) or V (0.5-2%).
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Mn, Al, low Ni:** Form the bcc parent phase and the basis for β (NiAl-type) precipitates. The reduced Ni content (target <5 wt%) is a primary cost-saving measure compared to typical Fe-Mn-Al-Ni alloys (often ≥ 7.5 wt% Ni).
 - **Cr:** Added for improved corrosion resistance. It may also stabilize the bcc parent phase or modify the β precipitates (e.g., by partial substitution for Al or Ni). Cr could also participate in the formation of secondary carbide precipitates if C is present.⁷
 - **C or V:** Intended to form secondary strengthening phases.
 - **Carbon (C):** To form fine (Fe,Mn,Cr) $_x$ C $_y$ type carbides, strengthening the austenite/parent phase against slip and potentially refining grain structure.
 - **Vanadium (V):** To form fine VC or complex (V,Cr)C precipitates, analogous to those enhancing PE in Fe-Mn-Si-VC systems.²⁹ These could provide additional matrix strengthening and favorably influence the martensitic transformation.
- **Targeted Precipitate Phase(s), Morphology, and Coherency:**
 - Primary: Coherent, nano-scale β (B2-ordered, (Ni,Cr)Al or Ni(Al,Cr)-type) precipitates, 5-15 nm.
 - Secondary (if C or V present): Fine, dispersed MX-type (VC) or M $_x$ C $_y$ -type ((Fe,Mn,Cr)-rich) carbides, <50 nm.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:**

Stress-induced, reversible martensitic transformation from the bcc parent phase. The β precipitates are expected to induce thermoelasticity. Secondary carbides would further strengthen the parent phase. Target recoverable strain: 4-7%; Transformation stress: 300-600 MPa.
- **Estimated Cost Reduction Strategy:** Significant reduction in Ni content compared to standard Fe-Mn-Al-Ni. Cr, C, and V are relatively low-cost additions in the proposed concentrations.
- **Guiding Research Principles and Supporting Literature:** Based on the known Fe-Mn-Al-Ni system²¹, the role of Cr in Fe-based alloys for corrosion and phase stability⁷, and the effectiveness of VC precipitates in Fe-Mn-Si systems.²⁹
- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Ensuring formation and stability of effective β precipitates with reduced Ni content; Cr's role in β phase needs investigation.

- Optimizing heat treatment to co-precipitate β and secondary carbides with desired size and distribution.
- Potential for embrittlement if coarse carbides form at grain boundaries.
- Achieving a balance where secondary precipitates strengthen the parent phase without impeding the reversible martensitic transformation.

Hypothesis A2: Fe-Mn-Al-Si-Ni-(B/C)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Mn (20–30%), Al (8–12%), Si (1–4%), Ni (3–6%), and either B (0.005–0.05%) or C (0.1–0.3%).
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Mn, Al, Ni:** Form the bcc parent phase and β (NiAl-type) precipitates. Ni content is kept moderate.
 - **Si:** Added to strengthen the parent bcc matrix through solid solution strengthening. Si is known to increase resistance to slip in ferritic structures and could potentially modify the stability or morphology of β precipitates or influence stacking fault energy if any transient fcc phases are involved.⁷ Silicon is very inexpensive.⁴⁹
 - **B or C:**
 - **Boron (B):** For grain refinement during solidification/recrystallization and potentially to suppress brittle intergranular phases, similar to its role in FeNiCoAlTaB.²⁰
 - **Carbon (C):** For interstitial strengthening of the parent phase and possible formation of very fine, dispersed carbides.
- **Targeted Precipitate Phase(s), Morphology, and Coherency:**
 - Primary: Coherent, nano-scale β (B2-ordered, Ni(Al,Si)-type or (Ni,Si)Al-type) precipitates, 5–15 nm.
 - Secondary (if C present): Fine, dispersed carbides.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:** Stress-induced reversible martensitic transformation, with thermoelasticity imparted by β precipitates. Si is expected to enhance parent phase strength. Target recoverable strain: 5–8%; Transformation stress: 400–700 MPa.
- **Estimated Cost Reduction Strategy:** Moderate Ni content, with very low-cost Si and minor B/C additions.
- **Guiding Research Principles and Supporting Literature:** Based on Fe-Mn-Al-Ni system²¹, the general strengthening effect of Si in Fe-based alloys⁷, and the role of B in refining grains and improving properties in other Fe-SMAs.²⁰
- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Interaction between Si and NiAl precipitate formation; Si might alter β phase stoichiometry or stability.

- Effect of Si on transformation temperatures and hysteresis.
- Ensuring B is effective at low concentrations for grain refinement without forming deleterious borides.

7.2. Alloy Family B: Advanced Fe-Mn-Si-Cr Systems with Targeted PE Enhancers

Rationale: These alloys aim to build upon the extremely low-cost Fe-Mn-Si(-Cr) base, which traditionally shows SME, by introducing specific precipitate-forming elements to induce significant pseudoelasticity. The Fe-17Mn-5Si-10Cr-4Ni-1(V-C) alloy serves as a key inspiration.³⁰

Hypothesis B1: Fe-Mn-Si-Cr-(low Ni)-V-C (Cost-Optimized FeMnSiCrNiVC-like)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Mn (15-25%), Si (4-7%), Cr (8-15%), Ni (0-2%, ideally aiming for Ni-free), V (0.5-1.5%), C (0.1-0.4%).
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Mn, Si, Cr:** Form the low-cost austenitic (γ) parent phase, prone to $\gamma \rightarrow \epsilon$ (hcp) martensitic transformation.
 - **Low Ni (or Ni-free):** The FeMnSiCrNiVC system contains 4 wt% Ni. This hypothesis aims to drastically reduce or eliminate Ni to further cut costs, while relying more heavily on V and C for PE.
 - **V, C:** Primary PE-inducing elements, intended to form fine, dispersed (V,Cr)C (MX-type) or more complex (Cr,V,Fe,Mn)-rich carbides. These precipitates are expected to strengthen the austenite, promote stacking fault formation, aid reversible ϵ -martensite nucleation, and inhibit α' -martensite formation.³⁰
- **Targeted Precipitate Phase(s), Morphology, and Coherency:** Fine (<50 nm), coherent or semi-coherent (V,Cr)C or (Cr,V,Fe,Mn)-rich carbides, potentially forming along stacking faults or homogeneously within austenite grains.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:** Stress-induced, reversible $\gamma \leftrightarrow \epsilon$ transformation. Precipitates strengthen austenite against slip and manage transformation product morphology for reversibility. Target recoverable strain: 3-6%; Transformation stress: 250-500 MPa.
- **Estimated Cost Reduction Strategy:** Utilizes very inexpensive base elements (Fe, Mn, Si, Cr, C). V is moderately priced. Significant cost saving if Ni can be minimized or eliminated compared to the original FeMnSiCrNiVC.
- **Guiding Research Principles and Supporting Literature:** Direct evolution from the successful Fe-17Mn-5Si-10Cr-4Ni-1(V-C) system³⁰, with a strong focus on cost reduction by minimizing Ni.
- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Determining if sufficient PE can be achieved without Ni, or with very low Ni. Ni

may play a subtle role in austenite stability or precipitate interaction in the original alloy.

- Optimizing V and C content and heat treatment (e.g., double aging) to achieve the correct precipitate type, size, and distribution for PE.
- Ensuring good cyclic stability, as Fe-Mn-Si systems can be prone to accumulation of defects.

Hypothesis B2: Fe-Mn-Si-Cr-Al-(N/C) (Nitride/Carbide Strengthened FeMnSi)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Mn (15-25%), Si (4-7%), Cr (8-15%), Al (1-3%), and either N (0.05-0.2%) or C (0.1-0.3%), or both.
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Mn, Si, Cr:** Form the austenitic parent phase.
 - **Al:** Added as a potent nitride former (AlN) or to participate in complex carbide/carbonitride formation. Al also typically strengthens ferrite, which might be present in small amounts or form transiently.
 - **N and/or C:** Intended to form fine, dispersed precipitates with Al, Cr, or Si.
 - **Nitrogen (N):** Target AlN or (Cr,Al)N precipitates.
 - **Carbon (C):** Target (Cr,Al,Si)C type carbides or carbonitrides.
- **Targeted Precipitate Phase(s), Morphology, and Coherency:** Fine (<50 nm), coherent or semi-coherent AlN, Cr(C,N), (Al,Si,Cr)(C,N) precipitates.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:** Stress-induced, reversible $\gamma \leftrightarrow \epsilon$ transformation, with precipitates strengthening austenite and promoting reversible martensite formation, similar to the V-C strategy. Target recoverable strain: 2-5%; Transformation stress: 200-450 MPa.
- **Estimated Cost Reduction Strategy:** All proposed additions (Al, N, C) are very inexpensive.
- **Guiding Research Principles and Supporting Literature:** Based on the known ability of Al and Cr to form nitrides⁴⁰, and carbides. General principle of using fine precipitates to enhance SME/PE in Fe-Mn-Si systems.
- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Controlling the precipitation of nitrides/carbides to be fine and intragranular, rather than coarse or at grain boundaries (AlN, for instance, can cause embrittlement if it forms as coarse grain boundary films⁴⁰).
 - Achieving sufficient volume fraction and effectiveness of these precipitates to induce significant PE.
 - Solubility of N in the melt and its controlled introduction.

7.3. Alloy Family C: Novel Fe-Al-Cr-Mn Interstitial Alloys

Rationale: This family explores a more novel compositional space by combining Al, Cr,

and Mn with interstitial elements C or N, aiming to form unique ordered precipitates (potentially L1₂-type like κ -carbides, or other complex phases) that could induce pseudoelasticity. This moves away from the established NiAl or Ni₃Al-type precipitate systems and the traditional Fe-Mn-Si $\gamma \leftrightarrow \epsilon$ systems. The Fe-Mn-Al-C system, known for κ -carbides ((Fe,Mn)₃AlC, L1₂ structure), exhibits excellent strength and ductility but its potential for large pseudoelastic strains comparable to Nitinol is largely unexplored.³⁸ This family aims to tune such systems for SE.

Hypothesis C1: Fe-Al-Cr-Mn-C (Targeting κ -like or other complex carbides for SE)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Al (5-12%), Cr (5-15%), Mn (10-25%), C (0.5-1.5%).
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Al, Mn, C:** Primary elements intended to form an austenitic or duplex (austenite + ferrite) matrix containing fine, coherent κ -carbides ((Fe,Mn)₃AlC) or Cr-modified κ -carbides. The L1₂ structure of κ -carbides is similar to that of γ' precipitates known to induce SE in other Fe-SMAs.
 - **Cr:** Added to improve corrosion resistance, potentially modify the stability, morphology, and coherency of κ -type carbides, and influence the austenite/ferrite balance in the matrix. Cr addition has been shown to improve workability in Fe-Mn-Al-C steels.³⁸
- **Targeted Precipitate Phase(s), Morphology, and Coherency:** Nano-scale (5-20 nm), coherent κ -type ((Fe,Mn,Cr)₃AlC, L1₂ structure) precipitates or other complex (Fe,Mn,Cr)_x(Al,C)_y ordered carbides.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:** Stress-induced reversible martensitic transformation (parent phase could be austenite or ferrite depending on exact Al/Mn/C balance). The ordered carbide precipitates are hypothesized to provide the necessary austenite/ferrite strengthening against slip and facilitate a thermoelastic transformation. This is more speculative for large SE strains but is based on the known efficacy of L1₂ precipitates. Target recoverable strain: 3-6%; Transformation stress: 300-600 MPa.
- **Estimated Cost Reduction Strategy:** All constituent elements (Fe, Al, Cr, Mn, C) are relatively inexpensive.
- **Guiding Research Principles and Supporting Literature:** Knowledge of κ -carbide formation in Fe-Mn-Al-C steels³⁸, the general role of L1₂ precipitates in promoting SE in other Fe-SMAs (e.g., γ' in FeNiCoAlX²⁰), and the beneficial effects of Cr.³⁸

- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Achieving fine, coherent κ -carbides rather than coarse or intergranular forms which can be detrimental to ductility.
 - Determining if κ -carbides (or modified versions) can indeed induce significant thermoelasticity and large recoverable strains, as their primary reported role is strengthening.
 - Controlling the matrix phase (austenite vs. ferrite vs. duplex) and its interaction with the precipitates and the transformation.
 - The relatively high carbon content might lead to weldability issues if not managed.

Hypothesis C2: Fe-Al-Mn-N (Targeting AlN or complex Mn-Al-N for SE)

- **Proposed Nominal Compositional Range (wt%):** Fe (bal.), Al (3-8%), Mn (15-30%), N (0.1-0.5%).
- **Key Alloying Elements and Their Intended Roles:**
 - **Fe, Mn:** Form an austenitic or duplex austenitic-ferritic matrix. Mn stabilizes austenite and influences SFE.
 - **Al, N:** Intended to form fine, dispersed AlN precipitates or potentially more complex (Mn,Al) N_x nitrides.
- **Targeted Precipitate Phase(s), Morphology, and Coherency:** Fine (<50 nm), coherent or semi-coherent AlN or (Mn,Al) N_x precipitates.
- **Anticipated Pseudoelastic Mechanism and Performance Targets:** Stress-induced reversible martensitic transformation, with the fine nitride precipitates strengthening the parent phase against slip and promoting thermoelastic behavior. Target recoverable strain: 2-4%; Transformation stress: 250-500 MPa.
- **Estimated Cost Reduction Strategy:** All constituent elements (Fe, Al, Mn, N) are very inexpensive.
- **Guiding Research Principles and Supporting Literature:** Known formation of AlN precipitates in steels⁴⁰, general strengthening effects of interstitial nitrogen and nitride precipitates in ferrous alloys. This is a more exploratory area for achieving large SE.
- **Potential Challenges and Critical Areas for Experimental Validation:**
 - Controlling nitride precipitation to be fine, intragranular, and coherent. Coarse AlN at grain boundaries is known to cause embrittlement.⁴⁰
 - Achieving a sufficient volume fraction of effective nitrides for inducing significant PE.
 - Managing nitrogen solubility and preventing issues like porosity during melting and casting.

- Limited prior art for nitride-induced SE in Fe-SMAs specifically targeting Nitinol-like performance.

The development of these hypothesized alloys involves inherent risks. Family A represents a lower-risk approach by modifying known pseudoelastic systems. Family B builds on recent breakthroughs in enhancing Fe-Mn-Si alloys, offering a good balance of low cost and demonstrated PE potential. Family C is the most novel and higher-risk, but success could yield truly innovative and highly cost-effective SMAs. For all families, precise control over thermomechanical processing will be paramount to achieve the targeted nano-scale coherent precipitates, as minor deviations can drastically alter phase stability and resulting properties. This critical dependence of properties on processing is a well-established characteristic of existing Fe-SMAs that achieve pseudoelasticity via precipitation.²⁰

Table 4: Summary of Hypothesized Novel Fe-based SMA Compositions

Alloy ID	Proposed Nominal Compositional Range (wt%)	Key Alloying Elements & Intended Roles	Target Precipitate(s) & PE Mechanism	Expected Key PE Characteristics (Qualitative)	Primary Cost Advantage Rationale	Key Guiding Principles /Supporting Systems
A1	Fe(bal), Mn(25-35), Al(10-15), Ni(2-5), Cr(3-8), C(0.1-0.5) or V(0.5-2)	Mn,Al,low Ni: β -phase base. Cr: corrosion, β -mod. C/V: secondary carbides.	Primary: β ((Ni,Cr)Al). Secondary: MX/M _x Y _y carbides. PE via β -induced thermoelasticity, matrix strengthening.	Moderate strain (4-7%), moderate stress (300-600 MPa).	Reduced Ni. Cr, C, V are low/moderate cost.	FeMnAlNi ²¹ , Cr effects ⁶⁰ , VC in FeMnSi. ²⁹
A2	Fe(bal), Mn(20-30), Al(8-12), Si(1-4),	Mn,Al,Ni: β -phase base. Si: matrix	Primary: β (Ni(Al,Si)). Secondary:	Moderate-high strain (5-8%), moderate-	Moderate Ni. Si, B, C are very low cost.	FeMnAlNi ²¹ , Si strengthening ⁷ , B

	Ni(3-6), B(0.005-0.05) or C(0.1-0.3)	strength, β -mod. B/C: grain refinement/ fine carbides.	borides/carbides. PE via β -induced thermoelasticity, Si strengthening.	high stress (400-700 MPa).		effects. ²⁰
B1	Fe(bal), Mn(15-25), Si(4-7), Cr(8-15), Ni(0-2), V(0.5-1.5), C(0.1-0.4)	Mn,Si,Cr: $\gamma \leftrightarrow \epsilon$ base. Low/no Ni: cost. V,C: (V,Cr)C for PE.	(V,Cr)C or complex (Cr,V,Fe,Mn)-rich carbides. PE via precipitation-aided reversible $\gamma \leftrightarrow \epsilon$.	Moderate strain (3-6%), moderate stress (250-500 MPa).	Very low cost base. Minimal/no Ni. V,C low/moderate cost.	FeMnSiCr NiVC. ³⁰
B2	Fe(bal), Mn(15-25), Si(4-7), Cr(8-15), Al(1-3), N(0.05-0.2) &/or C(0.1-0.3)	Mn,Si,Cr: $\gamma \leftrightarrow \epsilon$ base. Al,N/C: AlN, Cr(C,N), (Al,Si,Cr)(C,N) for PE.	AlN, Cr(C,N), (Al,Si,Cr)(C,N) fine precipitates. PE via precipitation-aided reversible $\gamma \leftrightarrow \epsilon$.	Low-moderate strain (2-5%), low-moderate stress (200-450 MPa).	All additions (Al, N, C) are very low cost.	Nitride formers (Al, Cr) ⁴⁰ , general precipitation in FeMnSi.
C1	Fe(bal), Al(5-12), Cr(5-15), Mn(10-25), C(0.5-1.5)	Al,Mn,C: κ -carbide base. Cr: κ -mod, corrosion, matrix control.	Nano-scale, coherent κ -type (Fe,Mn,Cr) ₃ AlC, L1 ₂ or other complex ordered carbides. PE via L1 ₂ precipitation	Moderate strain (3-6%), moderate stress (300-600 MPa).	All elements are low/moderate cost.	κ -carbides in FeMnAlC ³⁸ , L1 ₂ role in SE. ²⁰

			e-induced thermoelasticity.			
C2	Fe(bal), Al(3-8), Mn(15-30), N(0.1-0.5)	Al,N: AlN base. Mn: matrix control.	Fine, coherent AlN or (Mn,Al)N nitrides. PE via nitride precipitation e-induced thermoelasticity.	Low-moderate strain (2-4%), low-mode rate stress (250-500 MPa).	All elements are very low cost.	AlN precipitation ⁴⁰ , N strengthening.

This table serves as the central output, providing a structured overview of the novel alloy concepts for guiding future research and development.

8. Comparative Outlook and Recommendations for Future Research

The hypothesized Fe-SMA compositions offer diverse pathways towards achieving cost-effective pseudoelasticity comparable to Nitinol. Each family presents a unique balance of potential performance, cost-effectiveness, novelty, and associated research challenges.

8.1. Qualitative Comparison of Hypothesized Alloy Families

- Potential for Nitinol-Comparable Pseudoelasticity:**
 - Family A (Modified Fe-Mn-Al-(Ni)):** Holds strong potential for achieving significant recoverable strains (potentially 5-8%) and transformation stresses due to its basis in the already proven Fe-Mn-Al-Ni system.²¹ The challenge lies in maintaining these properties with reduced Ni content and understanding the synergistic effects of Cr, C, V, or Si.
 - Family B (Advanced Fe-Mn-Si-Cr):** Inspired by FeMnSiCrNiVC³⁰, these alloys could offer good pseudoelastic recovery (potentially 3-6%), particularly in terms of cyclic stability if α' -martensite formation is well suppressed. Achieving very large single-cycle strains might be more challenging than in Family A.
 - Family C (Novel Fe-Al-Cr-Mn Interstitial):** This family is more exploratory. If

fine, coherent L1₂-type carbides (from C1) or effective nitrides (from C2) can indeed induce strong thermoelasticity, moderate recoverable strains (2-6%) might be achievable. The performance is less predictable than in Families A or B.

- **Fatigue Resistance:** For all hypothesized alloys, fatigue resistance is a major unknown and will be a critical determinant of their practical utility compared to Nitinol. This requires extensive experimental investigation.
- **Comparative Cost-Effectiveness:**
 - **Family B and C:** Offer the highest potential for cost reduction, as they rely predominantly on very inexpensive elements (Fe, Mn, Si, Al, Cr, C, N). Family B1's cost depends on the final Ni content (if any) and V concentration.
 - **Family A:** While cheaper than standard Fe-Mn-Al-Ni or Fe-Ni-Co-Al-X alloys due to lower Ni and absence of Co/Ta, it will likely be more expensive than Families B and C if Ni content remains around 3-6 wt%.
 - All families are anticipated to be significantly cheaper than Nitinol due to the elimination of titanium as a primary constituent and avoidance of highly expensive elements like Ta. Processing simplicity will also be a factor.
- **Degree of Novelty and Research Risk/Reward:**
 - **Family A:** Lower research risk due to incremental modification of an existing pseudoelastic system. Reward is a more cost-effective version of Fe-Mn-Al-Ni.
 - **Family B:** Moderate risk, building on recent proof-of-concept for PE in Fe-Mn-Si-VC systems. High reward if PE can be optimized in Ni-free or very low-Ni compositions, as the base materials are extremely cheap.
 - **Family C:** Highest research risk due to exploring less conventional precipitate types (engineered κ -carbides or novel nitrides) for inducing large SE. The reward would be a truly novel class of low-cost Fe-SMAs.

8.2. Prioritization of Most Promising Candidates for Experimental Development

Considering the balance of potential performance, cost, and risk, the following prioritization is suggested for initial experimental investigation:

1. **Hypothesis B1 (Fe-Mn-Si-Cr-(low Ni)-V-C):** This appears highly promising. The base Fe-Mn-Si-Cr system is very low cost, and the V-C precipitation strategy has already demonstrated significant PE.³⁰ The primary research focus would be to optimize PE while minimizing/eliminating Ni.
2. **Hypothesis A1 (Fe-Mn-Al-(low Ni)-Cr-(C/V)) and A2 (Fe-Mn-Al-Si-Ni-(B/C)):** These offer a good chance of success by modifying the known Fe-Mn-Al-Ni system. The key is to confirm that reduced Ni content, compensated by other

cheaper additions, can sustain robust β -phase precipitation and good PE.

3. **Hypothesis C1 (Fe-Al-Cr-Mn-C):** While more speculative for large SE, the potential to leverage L1₂ κ -carbides (known for strengthening³⁸) for thermoelasticity is an intriguing academic and practical question.
4. **Hypothesis B2 and C2 (Nitride-based systems):** These are more exploratory due to less established precedents for nitride-induced SE in these specific Fe-SMA contexts, but the extreme low cost of N and Al makes them worth investigating if initial screening is positive.

8.3. Key Experimental Investigations Required

For any of the hypothesized alloys, a systematic experimental program is essential:

- **Alloy Production:** Laboratory-scale melts (e.g., 50-500g) via arc melting or vacuum induction melting (the latter preferred if N control is critical or reactive elements are present in significant amounts). Casting into suitable forms for subsequent processing.
- **Thermomechanical Processing:**
 - Homogenization annealing to remove segregation.
 - Hot rolling/forging followed by cold rolling/swaging to produce specimens for testing (e.g., flat tensile bars, wires).
 - Systematic solution treatment and aging studies: Varying aging temperatures (e.g., from 200°C to 800°C depending on the targeted precipitate) and times (e.g., 0.5h to >100h) to map out precipitate evolution and its effect on properties. Quenching rates should also be controlled.
- **Microstructural Characterization:**
 - Optical Microscopy, Scanning Electron Microscopy (SEM) with Energy Dispersive X-ray Spectroscopy (EDS) for phase identification, grain size, and general microstructure.
 - Transmission Electron Microscopy (TEM) for detailed characterization of nano-precipitates (size, morphology, coherency, crystal structure via selected area electron diffraction - SAED).
 - Electron Backscatter Diffraction (EBSD) for grain orientation, texture analysis, and phase mapping.
 - X-ray Diffraction (XRD) for phase identification and lattice parameter measurements.
- **Functional and Mechanical Property Evaluation:**
 - Differential Scanning Calorimetry (DSC) to determine martensitic transformation temperatures (M_s, M_f, A_s, A_f) and thermal hysteresis.
 - Tensile testing: Monotonic tests to determine yield strength, ultimate tensile

strength, and elongation. Cyclic load-unload tests at various temperatures (e.g., -50°C to 200°C) to evaluate pseudoelasticity (recoverable strain, upper/lower plateau stresses, stress hysteresis, residual strain). Incremental strain tests are also valuable.

- Cyclic Fatigue Testing: Strain-controlled fatigue tests (e.g., tension-tension or tension-compression if equipment allows) at various strain amplitudes to generate S-N curves and assess functional (degradation of PE) and structural (fracture) fatigue life.
- Hardness testing (e.g., Vickers) as a preliminary indicator of strengthening.

A critical aspect of this experimental work will be the meticulous correlation of processing parameters, resultant microstructures (especially precipitate characteristics and grain size), and the observed functional properties. This iterative approach is key to optimizing these novel alloy systems. Furthermore, while many high-performing Fe-SMAs show best results in single crystals⁵, the practical goal is cost-effective polycrystalline alloys. Therefore, strategies to translate single-crystal success or to directly optimize polycrystalline microstructures (e.g., through texture control or grain boundary engineering) will be vital.

Beyond initial PE characterization, promising candidates will require evaluation of their cyclic stability under various loading conditions and their environmental resistance (e.g., corrosion behavior, particularly if Cr content is low or absent), as these are areas where Nitinol currently excels and are crucial for many real-world applications. Computational tools, such as CALPHAD for phase diagram prediction and precipitate stability, and Density Functional Theory (DFT) for understanding precipitate-matrix coherency and energetics, should be employed to guide experimental design and accelerate the development process.⁴

9. Conclusion

The high cost of Nitinol remains a significant barrier to its broader application, despite its excellent pseudoelastic performance. This report has systematically explored the potential for developing novel Fe-based Shape Memory Alloys (SMAs) that can offer comparable pseudoelasticity at a substantially lower cost. The collective evidence from existing research strongly suggests that this is a challenging yet scientifically feasible objective.

The core strategy for designing such alloys revolves around leveraging inexpensive and abundant alloying elements—primarily Fe, Mn, Si, Al, Cr, and interstitials like C and N—and engineering specific, cost-effective nano-precipitate phases that can induce

the necessary thermoelastic martensitic transformation. This involves moving away from expensive elements like Ta and Co, and minimizing reliance on high concentrations of Ni, which are characteristic of some current high-performance Fe-SMAs.

Three families of novel Fe-SMA compositions have been hypothesized:

1. **Modified Fe-Mn-Al-(Ni) Systems:** These seek to reduce Ni content in the established Fe-Mn-Al-Ni framework, using Cr, C, V, or Si to maintain or enhance the efficacy of β (B2-type) precipitates.
2. **Advanced Fe-Mn-Si-Cr Systems:** These aim to transition the very low-cost Fe-Mn-Si base from primarily SME to significant PE by incorporating targeted precipitate formers like V-C or Al-N, inspired by recent successes in similar systems.
3. **Novel Fe-Al-Cr-Mn Interstitial Alloys:** These explore new compositional territories by using Al, Cr, Mn with C or N to form unique ordered precipitates (e.g., modified κ -carbides or novel nitrides) capable of inducing pseudoelasticity.

The development of these hypothesized alloys requires a synergistic approach, combining fundamental metallurgical understanding with systematic experimental validation. Precise control over thermomechanical processing to achieve the desired nano-scale coherent precipitates will be paramount. While initial pseudoelastic characterization is the first step, thorough investigation of cyclic stability and environmental durability will be crucial for any alloy aspiring to be a practical alternative to Nitinol.

The successful realization of even one of these hypothesized alloy systems could have a profound impact, unlocking new applications in diverse fields such as civil engineering, automotive, consumer products, and potentially even biomedical devices (pending biocompatibility assessments), where the unique functionalities of SMAs are desired but currently constrained by the prohibitive cost of Nitinol. This report provides a scientifically grounded roadmap to guide future research and development efforts toward this important technological goal.

Works cited

1. The Complete Guide to Nitinol Prices - GEE SMA, accessed May 19, 2025, <https://www.geenitinol.com/blog/complete-guide-nitinol-prices>
2. Nitinol: An Overview of Cost Factors - Resonetics, accessed May 19, 2025, <https://resonetics.com/blog/nitinol-cost-factors/>
3. Shape-Memory Effect and Pseudoelasticity in Fe-Mn-Based Alloys - CONICET, accessed May 19, 2025,

- https://ri.conicet.gov.ar/bitstream/handle/11336/125953/CONICET_Digital_Nro.987ae7bc-d42a-4ac3-9497-56a000d2227d_A.pdf?sequence=2&isAllowed=y
4. [2409.17973] Manufacturing, processing, applications, and advancements of Fe-based shape memory alloys - arXiv, accessed May 19, 2025, <https://arxiv.org/abs/2409.17973>
 5. html.mechse.illinois.edu, accessed May 19, 2025, <https://html.mechse.illinois.edu/files/2021/12/28o.pdf>
 6. Ferrous Polycrystalline Shape-Memory Alloy Showing Huge ..., accessed May 19, 2025, https://www.researchgate.net/publication/42345174_Ferrous_Polycrystalline_Shape-Memory_Alloy_Showing_Huge_Superelasticity
 7. www.ijscer.com, accessed May 19, 2025, <https://www.ijscer.com/uploadfile/2015/0413/20150413110349501.pdf>
 8. Achievements and Perspectives on Fe-Based Shape Memory Alloys for Rehabilitation of Reinforced Concrete Bridges: An Overview - PMC - PubMed Central, accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC9717741/>
 9. A review of shape memory alloy research, applications and opportunities - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/271851282_A_review_of_shape_memory_alloy_research_applications_and_opportunities
 10. Potential of Fe-Mn-Al-Ni Shape Memory Alloys for Internal Prestressing of Ultra-High Performance Concrete - PubMed Central, accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC10221686/>
 11. Innovations and recent trends in Shape Memory Alloy: A review - SciSpace, accessed May 19, 2025, <https://scispace.com/pdf/innovations-and-recent-trends-in-shape-memory-alloy-a-review-3j5sav67jy.pdf>
 12. Mechanical Properties of Advanced Metallic Materials - MDPI, accessed May 19, 2025, https://mdpi-res.com/bookfiles/book/6964/Mechanical_Properties_of_Advanced_Metallic_Materials.pdf?v=1740967558
 13. Recent Progress in Shape Memory Alloys - J-Stage, accessed May 19, 2025, https://www.jstage.jst.go.jp/article/matertrans/59/3/59_M2017340/html/-char/ja
 14. Fatigue of Nitinol: The state-of-the-art and ongoing challenges ..., accessed May 19, 2025, https://www.researchgate.net/publication/279988885_Fatigue_of_Nitinol_The_state-of-the-art_and_ongoing_challenges
 15. Aluminum Vs Titanium - Redstone Manufacturing®, accessed May 19, 2025, <https://redstonemanufacturing.com/aluminum-vs-titanium/>
 16. Optimisation of processing and properties of medical grade Nitinol wire, accessed May 19, 2025, <https://www.euroflex.de/fileadmin/content/Dokumente/Literatur/nitinolwire.pdf>
 17. High compressive pre-strains reduce the bending fatigue life of ..., accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC6553620/>

18. Mechanical fatigue and fracture of Nitinol - Lawrence Berkeley National Laboratory, accessed May 19, 2025, https://www2.lbl.gov/ritchie/Library/PDF/2012_Robertson_IMR_Mechanical.pdf
19. Study on the Effect of Solid Solution Treatment on the Bending Fatigue Property of Fe-Mn-Si Shape Memory Alloys - MDPI, accessed May 19, 2025, <https://www.mdpi.com/2075-4701/14/4/441>
20. (PDF) Effect of B addition on the superelasticity in FeNiCoAlTa ..., accessed May 19, 2025, https://www.researchgate.net/publication/347839745_Effect_of_B_addition_on_the_superelasticity_in_FeNiCoAlTa_single_crystals
21. FeMnNiAl Iron-Based Shape Memory Alloy: Promises and Challenges - High Temperature Materials Laboratory, accessed May 19, 2025, https://html.mechse.illinois.edu/files/2019/09/Abuzaid2019_Article_FeMnNiAlIron-BasedShapeMemoryA.pdf
22. Nickel Titanium Aluminum Alloy | AMERICAN ELEMENTS®, accessed May 19, 2025, <https://www.americanelements.com/nickel-titanium-aluminum-alloy>
23. Nickel Price Monthly Trends: Commodity Markets Review - YCharts, accessed May 19, 2025, https://ycharts.com/indicators/nickel_price
24. Nickel Spot Price Chart | Live Price of Nickel per Ounce | Markets Insider, accessed May 19, 2025, <https://markets.businessinsider.com/commodities/nickel-price>
25. Additive Manufacturing of Fe-Mn-Si-Based Shape Memory Alloys: State of the Art, Challenges and Opportunities - PMC, accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC10744529/>
26. A Review Article on FeMnAlNi Shape Memory Alloy - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/366152132_A_Review_Article_on_FeMnAlNi_Shape_Memory_Alloy/download
27. Shape Memory effect and Superelasticity in the [001] Single crystals of a FeNiCoAlTa Alloy with γ - α' -Thermoelastic Martensitic Transformations | Request PDF - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/259635920_Shape_Memory_effect_and_Superelasticity_in_the_001_Single_crystals_of_a_FeNiCoAlTa_Alloy_with_gamma-alpha'-Thermoelastic_Martensitic_Transformations
28. Research Progress of Fe-Based Superelastic Alloys - MDPI, accessed May 19, 2025, <https://www.mdpi.com/2073-4352/12/5/602>
29. A Novel Fe-Mn-Si Shape Memory Alloy With Improved Shape Recovery Properties by VC Precipitation | Request PDF - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/230516404_A_Novel_Fe-Mn-Si_Shape_Memory_Alloy_With_Improved_Shape_Recovery_Properties_by_VC_Precipitation
30. Effect of low-temperature precipitates on microstructure and pseudoelasticity of an Fe-Mn-Si-based shape memory alloy, accessed May 19, 2025, <https://www.repo.uni-hannover.de/handle/123456789/14019>
31. Effect of grain size on shape memory properties of Cr₂₀Mn₂₀Fe₂₀Co₃₅Ni₅

- high-entropy alloy - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/389751520_Effect_of_grain_size_on_shape_memory_properties_of_Cr20Mn20Fe20Co35Ni5_high-entropy_alloy
32. Nanoprecipitation effects on phase stability of Fe-Mn-Al-Ni alloys - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/314128276_Nanoprecipitation_effects_on_phase_stability_of_Fe-Mn-Al-Ni_alloys
33. Cyclic degradation mechanisms in aged FeNiCoAlTa shape ..., accessed May 19, 2025,
https://www.researchgate.net/publication/265129638_Cyclic_degradation_mechanisms_in_aged_FeNiCoAlTa_shape_memory_single_crystals
34. The effect of precipitates on the superelastic response of [1 0 0] oriented FeMnAlNi single crystals under compression | Request PDF - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/282320834_The_effect_of_precipitates_on_the_superelastic_response_of_1_0_0_oriented_FeMnAlNi_single_crystals_under_compression
35. Remarkable improvement of shape memory effect in Fe-Mn-Si based shape memory alloys by producing NbC precipitates | Request PDF - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/257541600_Remarkable_improvement_of_shape_memory_effect_in_Fe-Mn-Si_based_shape_memory_alloys_by_producing_NbC_precipitates
36. Significant enhancement of shape recovery and pseudoelasticity in an intercritically-annealed Fe-Ni-Mn alloy through cold rolling | Request PDF - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/390411297_Significant_enhancement_of_shape_recovery_and_pseudoelasticity_in_an_intercritically-annealed_Fe-Ni-Mn_alloy_through_cold_rolling
37. repo.uni-hannover.de, accessed May 19, 2025,
<https://repo.uni-hannover.de/server/api/core/bitstreams/2a188cc4-0744-4826-9187-66fb84319949/content>
38. Fe-Al-Mn-C lightweight structural alloys: a review on the ..., accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC5090571/>
39. (PDF) Fe-Al-Mn-C lightweight structural alloys: A review on the microstructures and mechanical properties - ResearchGate, accessed May 19, 2025,
https://www.researchgate.net/publication/258304555_Fe-Al-Mn-C_lightweight_structural_alloys_A_review_on_the_microstructures_and_mechanical_properties
40. Precipitation Behavior of AlN Inclusions in Fe-0.5Al-2.0Mn Alloy Under Continuous Unidirectional Solidification Process - Frontiers, accessed May 19, 2025,
<https://www.frontiersin.org/journals/materials/articles/10.3389/fmats.2021.736284/full>
41. Research Progress and Applications of Fe-Mn-Si-Based Shape Memory Alloys on Reinforcing Steel and Concrete Bridges - MDPI, accessed May 19, 2025,

- <https://www.mdpi.com/2076-3417/13/6/3404>
42. On the origin of the improvement of shape memory effect by precipitating VC in Fe-Mn-Si-based shape memory alloys - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/profile/Md_Washim_Akram/post/What_is_the_reas_on_of_shape_memory_effect_in_the_materials/attachment/5cd67450cfe4a7968d9e80fe/AS%3A757268769406976%401557558352000/download/lai2018.pdf
 43. Surface modification of TiNi-based shape memory alloys by dry electrical discharge machining - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/274096799_Surface_modification_of_Ti_Ni-based_shape_memory_alloys_by_dry_electrical_discharge_machining
 44. Effects of grain orientation and precipitates on the superelasticity in ..., accessed May 19, 2025, https://www.researchgate.net/publication/303478413_Effects_of_grain_orientation_and_precipitates_on_the_superelasticity_in_directionally_solidified_FeNiCoAlTa_B_shape_memory_alloy
 45. Thermal Cycling Behavior of Aged FeNiCoAlTiNb Cold-Rolled Shape Memory Alloys - PMC, accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC11596731/>
 46. Manufacturing, processing, applications, and advancements of Fe-based shape memory alloys - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/384365018_Manufacturing_processing_applications_and_advancements_of_Fe-based_shape_memory_alloys
 47. Microstructural Evolution and Functional Properties of Fe-Mn-Al-Ni Shape Memory Alloy Processed by Selective Laser Melting | Request PDF - ResearchGate, accessed May 19, 2025, https://www.researchgate.net/publication/294573317_Microstructural_Evolution_and_Functional_Properties_of_Fe-Mn-Al-Ni_Shape_Memory_Alloy_Processed_by_Selective_Laser_Melting
 48. Prices of chemical elements - Wikipedia, accessed May 19, 2025, https://en.wikipedia.org/wiki/Prices_of_chemical_elements
 49. ZCE Ferrosilicon Historical Prices - Investing.com, accessed May 19, 2025, <https://www.investing.com/commodities/zce-ferrosilicon-futures-historical-data>
 50. Metal silicon price index - businessanalytiq, accessed May 19, 2025, <https://businessanalytiq.com/procurementanalytics/index/metal-silicon-price-index/>
 51. Manganese Ore - Price - Chart - Historical Data - News, accessed May 19, 2025, <https://tradingeconomics.com/commodity/manganese>
 52. The effect of cobalt alloying on the phase transformation kinetics of Ni-Ti alloys - PMC, accessed May 19, 2025, <https://pmc.ncbi.nlm.nih.gov/articles/PMC11416287/>
 53. Introducing cobalt nickel aluminum ferromagnetic shape memory alloy for endodontic file manufacturing - ScienceScholar, accessed May 19, 2025, <https://sciencescholar.us/journal/index.php/ijhs/article/download/10429/6879/7004>
 54. LME Cobalt | London Metal Exchange, accessed May 19, 2025, <https://www.lme.com/Metals/EV/LME-Cobalt>

55. Tantalum 99.95%Min United States Spot Historical Prices - Investing.com, accessed May 19, 2025, <https://www.investing.com/commodities/tantalum-99.95-min-united-states-futures-historical-data>
56. Historical Price of Niobium/Tantalum - Shanghai Metal Market, accessed May 19, 2025, <https://www.metal.com/en/markets/20>
57. Ferro-boron Price(28+) - Alibaba.com, accessed May 19, 2025, <https://www.alibaba.com/showroom/ferro--boron-price.html>
58. Ferro Boron - Made-in-China.com, accessed May 19, 2025, https://www.made-in-china.com/products-search/hot-china-products/Ferro_Boron.html
59. Ferroboron Price - High Quality Ferro Boron Alloys - Alibaba.com, accessed May 19, 2025, <https://www.alibaba.com/showroom/ferroboron-price.html>
60. Martensitic transformation temperature modification of Fe-SMA for efficient medical implants - Informit, accessed May 19, 2025, <https://search.informit.org/doi/pdf/10.3316/informit.T2024072300013700515752292>
61. High Quality Low Carbon Ferro Chrome Lump Price 60 - Alibaba.com, accessed May 19, 2025, <https://www.alibaba.com/product-detail/High-Quality-Low-Carbon-Ferro-Chrome-60798601748.html>
62. Vanadium Prices, charts, and News - Argus Metals, accessed May 19, 2025, <https://www.argusmedia.com/metals-platform/metal/minor-and-specialty-metals-vanadium>
63. Ferro-vanadium 80% V fob China prices USD/kg - Argus Media, accessed May 19, 2025, <https://www.argusmedia.com/metals-platform/price/assessment/ferro-vanadium-80--v-fob-china-prices-PA00144230000>
64. Historical Price of Titanium - Shanghai Metal Market, accessed May 19, 2025, <https://www.metal.com/en/markets/23>
65. Niobium Markets - Globe Metals & Mining, accessed May 19, 2025, <https://www.globemmm.com/niobium-markets>
66. Ferro Niobium Price - High Quality & Competitive Rates - Alibaba.com, accessed May 19, 2025, <https://www.alibaba.com/showroom/ferro-niobium-price.html>
67. Metallurgical Coke Futures Historical Prices - Investing.com, accessed May 19, 2025, <https://www.investing.com/commodities/metallurgical-coke-futures-historical-data>
68. Graphite Pricing - Northern Graphite, accessed May 19, 2025, <https://www.northerngraphite.com/graphite-pricing/>
69. Effect of Mo Alloying on the Precipitation Behavior of B2 Nano-Particles in Fe-Mn-Al-Ni Shape Memory Alloys - Bohrium, accessed May 19, 2025, <https://bohrium.dp.tech/paper/arxiv/811271092315357185>
70. Martensitic Transformation and Superelasticity in Fe-Mn-Al-Based Shape Memory Alloys, accessed May 19, 2025,

https://www.researchgate.net/publication/320680352_Martensitic_Transformation_and_Superelasticity_in_Fe-Mn-Al-Based_Shape_Memory_Alloys

71. Shape Memory Effect and Martensitic Transformation in Fe–Mn–Al–Ni Alloy - MDPI, accessed May 19, 2025, <https://www.mdpi.com/2075-4701/12/2/247>
72. Ferrochrome Price Index - Asian Metal, accessed May 19, 2025, <https://www.asianmetal.com/Ferro-chrome-Price-Index/>
73. Titanium - Price - Chart - Historical Data - News - Trading Economics, accessed May 19, 2025, <https://tradingeconomics.com/commodity/titanium>
74. Six Solutions to Battery Mineral Challenges - RMI, accessed May 19, 2025, <https://rmi.org/insight/six-solutions-to-battery-mineral-challenges/>
75. Iron Ore - Price - Chart - Historical Data - News - Trading Economics, accessed May 19, 2025, <https://tradingeconomics.com/commodity/iron-ore>
76. Manganese Price Today | Manganese Spot Price Chart | Historical Price of Manganese - Shanghai Metal Market, accessed May 19, 2025, <https://www.metal.com/en/markets/19>