
Band Structure (cold): hexagonal SnS_2 2x2
Biaxial strain = -5.0%; energy ordering (no overlap)
Band-gap edges
Energy relative to E_F (eV)
6
4
2
0
−2
−4
−6
Γ
M
K
Γ
High Symmetry Point