
Band Structure (fixed occupations): hexagonal SnS2 2x2
Biaxial strain = -1.0%
Band-gap edges
Energy relative to EF (eV)
4
3
2
1
0
−1
−2
−3
−4
Γ
M
K
Γ
High Symmetry Point