

## **MCQ**

1- Water of reaction needed to react chemically with 100 gm of calcium sulphate hemihydrate to convert it to calcium sulphate dihydrate:

a) 18.6 ml.

b) 22.2 ml.

c) 30.4 ml.

d) 45.3 ml.

1- For gypsum products, a suitable accelerator and retarder, respectively, would be:

a) Ethyl alcohol and oleic acid.

b) Oleic acid and glycerin.

c) Borax and potassium sulphate.

d) Potassium sulphate and borax.

2- The sprue of the wax pattern should:

a) Be long with large diameter.

b) Be short with small diameter.

c) Attached to the bulkiest portion.

4- ----- is produced during setting of -----:

A- Hydrogen gas, polysulphide

B- Water, Zinc oxide eugenol

C- Triglycerides, Polyether

D- Water, polysulphide

5- Sintering of dental ceramic can cause Expansion of ceramic restorations:

A- True

B- False

6- A: Lithium disilicate ceramic can be used as a full coverage anterior crown

**B: Lithium disilicate ceramic can be fabricated by machining:**

A- A is only right

B- B is only right

C- both A and B are right

D- Both A and B are wrong

### **Give a Scientific Term :**

**1- Type of gypsum expansion occurs by immersion in water after initial setting.**

( **Hygroscopic expansion** )

**2- Crystals that are responsible for pseudoplasticity of PE**

( **Triglycerides** )

**3- It is often sprayed on wax pattern before investing.**

( **Surfactant** )

***Good Luck***

***Dr Sherif Refat***

***Dr Marwa Bahaa***