

Laboratory Information

Laboratory: QA-LAB
Technician:
Sample By

Test Standard:
Test Date:
Report Date:

Test Method:
Prep. Method.
Splitting Method

Sample Information

Structure:
Work Area
Source
Material Type:

Sample Name:
Sample Number:
Sample Date:
Elevation

Depth From
Depth To:
North
East

ASTM C535 Grading of Test Samples

| Sieve Size, mm (in) | | Mass of Indicated Sizes, g | | |
|---------------------|--------------|----------------------------|--------------|--------------|
| Passing | Retained on | Grading | | |
| | | 1 | 2 | 3 |
| 75 (3) | 63 (2 1/2) | 2500 +/- 50 | - | - |
| 63 (2 1/2) | 50 (2) | 2500 +/- 50 | - | - |
| 50 (2) | 37.5 (1 1/2) | 5000 +/- 50 | 5000 +/- 50 | - |
| 37.2 (1 1/2) | 25 (1) | - | 5000 +/- 25 | 5000 +/- 25 |
| 25 (1) | 19 (3/4) | - | - | 5000 +/- 25 |
| Total | | 10000 +/- 100 | 10000 +/- 75 | 10000 +/- 50 |

Testing Information

| | |
|------------------|--|
| Selected Grading | |
|------------------|--|

| | |
|--------------------|--|
| Initial Weight (g) | |
| Final Weight (g) | |
| Weight Loss (g) | |
| Weight Loss (%) | |

Laboratory Comments:

Reviewed By: _____

Date:_____