
Pseudotime = first principal component; violins per phase, dots = median (validation)
Hand-crafted features
Spearman ρ = 0.45
SmallCNN embedding
Spearman ρ = 0.83
PC1 pseudotime (validation cells)
5
0
−5
−10
40
30
20
10
0
−10
−20
G1
S
G2
Pro
Meta
Ana
Telo