

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP - 680 (210 L)(0712241)**

Laboratory Serial No.	FB - 1454	Sample Drawn By	OPERATION OFFICER
JDE Serial No	1203670	Date Sample Drawn	12/12/22
Batch No / Lot No	M2-22-M-858	Date Received In Lab	12/12/22
Work Order No	1003297	Date Tested	12/12/22
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
3	PARTHAN EP 680 APPEARANCE	Visual	VISUAL	C	C	C
4	PARTHAN EP 680 DENSITY@29.5	KG / M3	P 16 D 1298 IP 180	-	-	.894
5	PARTHAN EP 680 FLASH POINT	°C	P 69 D 92 IP 36	230	-	272
6	PARTHAN EP 680 FOAM TEST SEQ1	.	P 67 D 892 IP 136	-	100/0	0/0
7	PARTHAN EP 680 FOAM TEST SEQ2	.	P 67 D 892 IP 136	-	50/0	0/0
8	PARTHAN EP 680 FOAM TEST SEQ3	.	P 67 D 892 IP 136	-	100/0	0/0
1	PARTHAN EP680 EMULSION,60 MINU	Milliliter	P 91 D 1401	40-40-0	40-40-0	40-40-0
2	PHOSPHOROUS	%Wt	P101 D1091 D6443	.0098	.0145	.0135
9	KV @ 40°C	cSt	P25 D445 D7042	625.0	700.0	650.3

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
DALVI P Y(30044160)