

**HINDUSTAN PETROLEUM CORPORATION LIMITED**

(A Government of India Enterprise)

**QUALITY CONTROL LABORATORY**

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

**LABORATORY TEST REPORT****ENKLO 100 (210 L)(0266241)**

|                       |             |                              |                  |
|-----------------------|-------------|------------------------------|------------------|
| Laboratory Serial No. | FB 1589     | Sample Drawn By              | BLENDING OFFICER |
| JDE Serial No         | 1211026     | Date Sample Drawn            | 06/01/23         |
| Batch No / Lot No     | M2-23-A-045 | Date Received In Lab         | 06/01/23         |
| Work Order No         | 1010818     | Date Tested                  | 06/01/23         |
| Tank /Kettle/Location | WHS2        | Particular of Sample         | DRUM             |
| Plant Code/ Name      | 14546       | Mazgaon TML Lubes-(STP 0101) | Sampling Plan    |
|                       |             |                              | IS 1447          |

| Test Line Number | Test Description/ Characteristics | Units      | Test Method           | Specifications |        | Result Value |
|------------------|-----------------------------------|------------|-----------------------|----------------|--------|--------------|
|                  |                                   |            |                       | Min            | Max    |              |
| 11               | ZINC                              | %Wt        | D6443 EDTA            | .026           | .070   | .033         |
| 1                | APPERANCE                         | Visual     | VISUAL                | B&C            | B&C    | B&C          |
| 4                | EMULSION CHAR @54 °C / 30 MIN     | Milliliter | P91 D1401             | -              | 3      | 0            |
| 9                | POUR POINT                        | °C         | P10 D97               | -              | 0      | -24          |
| 2                | ACIDITY TOTAL                     | mg KOH/g   | P2 D664 D974          | -              | 1.50   | .45          |
| 5                | FLASH POINT                       | °C         | P69 D92               | 210            | -      | 242          |
| 3                | DENSITY@29.5°C                    | gm/cc      | P16 D1298 D4052 D7042 | -              | -      | .8853        |
| 6                | FOAMING STABILITY SEQ1            | Milliliter | P67 D892              | NIL            | NIL    | NIL          |
| 7                | FOAMING STABILITY SEQ2            | Milliliter | P67 D892              | NIL            | NIL    | NIL          |
| 8                | FOAMING STABILITY SEQ3            | Milliliter | P67 D892              | NIL            | NIL    | NIL          |
| 10               | K V @ 40°C                        | cSt        | P25 D445 D7042        | 90.00          | 110.00 | 105.10       |
| 13               | RUST TEST                         | .          | P96 D665              | P              | P      | P            |
| 12               | VISCOSITY INDEX (VI)              | .          | P56 D2270             | 90             | -      | 100          |

Remarks : Sample meets the specification in above tests.

## Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

PAKALE SANTOSH BHIKAJI(38031160)