

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 32 (210 L)(0202241)**

Laboratory Serial No.	FB - 1303	Sample Drawn By	QC OFFICER
JDE Serial No	1195320	Date Sample Drawn	11/11/22
Batch No / Lot No	M2-22-L-716	Date Received In Lab	11/11/22
Work Order No	994295	Date Tested	12/11/22
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
16	ZINC	%Wt	ASTMD6443 ,EDTA	.020	.040	.037
1	APPEARANCE	Visual	VISUAL	B&C	B&C	B&C
2	DENSITY@29.5°C	gm/cc	P16, ASTMD1298,D4052,D7042	-	-	.8731
3	EMUL CHAR@54°C /20MIN	Milliliter	IS1448(P91),ASTM D1401	40-40-0	40-37-3	40-40-0
4	FLASH POINT, COC°C	°C	IS 1448(P:69), ASTM D 92	190	-	216
5	FOAMING STABILITY SEQ1	Milliliter	IS 1448(P:67), ASTM D892	0	0	0
6	FOAMING STABILITY SEQ2	Milliliter	IS 1448(P:67), ASTM D892	0	0	0
7	FOAMING STABILITY SEQ3	Milliliter	IS 1448(P:67), ASTM D892	0	0	0
8	FOAMING TENDENCY SEQ1	Milliliter	IS 1448(P:67), ASTM D892	0	50	50
9	FOAMING TENDENCY SEQ2	Milliliter	IS 1448(P:67), ASTM D892	0	50	30
10	FOAMING TENDENCY SEQ3	Milliliter	IS 1448(P:67), ASTM D892	0	50	50
11	K V @ 100° C	cSt	IS 1448(P25),ASTM D7042 ,D 445	-	9999999999.900	5.530
12	K V @ 40° C	cSt	IS 1448(P25),ASTM D7042 ,D 445	29.00	34.00	33.43
13	VISCOSITY INDEX	.	IS 1448(P56),ASTM D2270	90	-	102
14	POUR POINT°C	°C	IS 1448(P10),ASTM D97	-	-3	-3
15	RUSTTEST,SYNTHSEAWATER	.	IS 1448(P96),ASTM D665	P	P	P

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
DALVI P Y(30044160)