

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 320 210 Ltr Drum(0803011)**

Laboratory Serial No.	FB 595	Sample Drawn By	QC OFFICER
JDE Serial No	1053898	Date Sample Drawn	16/06/21
Batch No / Lot No	M2-21-F-038	Date Received In Lab	16/06/21
Work Order No	848321	Date Tested	16/06/21
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
13	ZINC	%Wt	P 77 D 4628 D 6443 EDTA	.040	.054	.049
2	ACIDITY TOTAL	mg KOH/g	P 1 D 974 IP 139	-	1.500	.810
12	VISCOSITY INDEX (VI)	.	P 56 D 2270 IP 226	90	-	100
1	APPEARANCE	Visual	VISUAL	B&C	B&C	B&C
3	DENSITY@29.5°C	gm/cc	P 16 D 1298 D 4052 IP 160	-	-	.8966
4	EMULSION CHAR@82°C / 30MIN	Milliliter	P 91 D 1401	40-40-0	40-37-3	40-40-0
5	FLASH POINT	°C	P 69 D 92 IP 36	230	-	254
6	FOAM STABILITY SEQ 1	Milliliter	P 67 D 892 IP 146P	-	0	0
7	FOAM STABILITY SEQ 2	Milliliter	P 67 D 892 IP 146P	-	0	0
8	FOAM STABILITY SEQ 3	Milliliter	P 67 D 892 IP 146P	-	0	0
11	K V @ 40°C	mm2/sec	P 25 D 445 D 7042 IP 71	310.0	340.0	319.4
9	POUR POINT	°C	P 10 D 97 IP 15	-	0	-3
10	RUST TEST SYNTHETIC SEA WATER	.	P 96 D 665 IP 135			P

Remarks : SAMPLE MEETS THE SPECIFICATION IN ABOVE TEST PARAMETERS.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
PAL TAPAS(31988540)