

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP-320 DRUM 210 LIT(0883011)**

Laboratory Serial No.	FB 269	Sample Drawn By	OPNS OFFICER
JDE Serial No	1123096	Date Sample Drawn	02/03/22
Batch No / Lot No	M2-22-C-295	Date Received In Lab	02/03/22
Work Order No	924769	Date Tested	02/03/22
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	APPEARANCE	.	VISUAL	C	C	C
2	ASH	%Wt	IS 1448(P4), ASTM D482	-	.100	.030
3	DENSITY@29.5°C	gm/cc	P16,ASTMD4052, D1298, D7042	-	-	.8920
4	FLASH POINT°C,COC	°C	IS1448(P69),ASTMD92	220	-	276
6	FOAMING TEST SEQ1	Milliliter	IS1448(P67), ASTM D892		100/0	0
7	FOAMING TEST SEQ2	Milliliter	IS1448(P67), ASTM D892	-	50/0	0
8	FOAMING TEST SEQ3	Milliliter	IS1448(P67), ASTM D892	-	100/0	0
9	RUST TEST A/B	.	IS1448(P96),ASTMD665	P	P	P
10	KINEMATIC VISCOSITY @40°C	cSt	IS1448(P25),ASTMD445, D7042	300.0	340.0	313.1
5	EMULSION TEST@82°C/30MIN	Milliliter	IS1448(P91), ASTM D1401	40-40-0	40-40-0	40-40-0
11	PHOSPHORUS	%Wt	IS1448(P101),ASTMD1091, D6443	.0098	.0145	.0110

Remarks : SAMPLE MEETS THE SPECIFICATION IN ABOVE TEST PARAMETERS

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
SHARMA TARUN(31960380)