

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP - 220 (210 L)(0706241)**

Laboratory Serial No.	FB - 274	Sample Drawn By	OPERATION OFFICER
JDE Serial No	1247552	Date Sample Drawn	05/06/23
Batch No / Lot No	M2-23-F-958	Date Received In Lab	05/06/23
Work Order No	1056939	Date Tested	06/06/23
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	APPEARANCE	.	VISUAL			CLEAR
2	ASH	%Wt	P4 D482	0	.100	.060
3	COPPER STRIP CORR @100°C	Hour		-	1	1
4	DENSITY@29.5°C	gm/cc	P16 D1298 D4052 D7042	-	999998.9933	.8808
5	FLASH POINT,COC	°C	P69 D92	220	-	212
6	FOAMING TEST SEQ1	Milliliter	P67 D892		100/0	0/0
7	FOAMING TEST SEQ2	Milliliter	P67 D892		50/0	10/0
8	FOAMING TEST SEQ3	Milliliter	P67 D892		100/0	10/0
9	EMULSION CHARAC.@82°C/30MIN.	Milliliter	IS1448(P91), ASTM D1401	40-40-0	40-40-0	40-40-0
10	RUST TEST A/B	.	P96 D665			P
11	VISCOSITY INDEX (VI)	.	P56 D2270	90	-	127
12	KINEMATIC VISCOSITY@40°C	cSt	P25 D445 D7042	210.0	240.0	215.9
13	PHOSPHORUS	%Wt	P101 D1091 D6443	.0098	.0145	.0106

Remarks : Sample fails in Flash Point test.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
DALVI P Y(30044160)