

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 68 210 Ltr Drum(0254011)**

Laboratory Serial No.	FB 044	Sample Drawn By	QC OFFICER
JDE Serial No	1109251	Date Sample Drawn	11/01/22
Batch No / Lot No	M2-23H0122	Date Received In Lab	11/01/22
Work Order No	909544	Date Tested	11/01/22
Tank /Kettle/Location	WHS	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
2	ACIDITY TOTAL	mg KOH/g	IS1448 (P2), ASTM D974, D664	-	1.50	.90
1	APPEARANCE	.	VISUAL	B&C	B&C	B&C
3	DENSITY@29.5°C	gm/cc	IS1448(P16), ASTM D1298, D 4052	.8000	.9500	.8601
4	FLASH POINT,COC	°C	IS1448(P69), ASTM D92	210	-	240
5	FOAM STABILITY ,SEQ 1	Milliliter	IS1448(P67), ASTM D892	0	0	0
6	FOAM STABILITY , SEQ 2	Milliliter	IS1448(P67), ASTM D892	0	0	0
7	FOAM STABILITY, SEQ 3	Milliliter	IS1448(P67), ASTM D892	0	0	0
11	KV @ 100 ° C	cSt	IS1448(P25), ASTM D445, D7042	-	-	9.462
10	KV @ 40 ° C	cSt	IS1448(P25), ASTM D445, D7042	62.00	74.00	70.10
8	POUR POINT ° C	°C	IS1448(P10), ASTM D97	-	0	-6
12	VISCOSITY INDEX (VI)	.	IS1448 (P56), ASTM D2270	90	-	113
9	RUST TEST SYNTHETIC SEA WATER	.	IS 1448(P96),ASTM D665	P	P	P

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) This is a system generated test report and hence does not require signature.

Approved By :

SHIRSAT NEETA VISHNU(38032820)