



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
MAZGAON LUBE PLANT
HAY BUNDER ROAD, MAZGAON
MUMBAI - 400033, MAHARASHTRA
LABORATORY TEST REPORT



Product	0254241 (HP ENKLO 68 - DRUM 210L (0.9 MM))	Test Report Number	4546232401969
Loc/ Customer/ Supplier	4546 (MAZGAON TML LUBES)	Sample Number	40000003672
Process/Purchase/Sales Order	10005846 4902905553 0001	Lab Sr. No	FB- 657
Source of the Sample	DRUM	ULR Number	TC-5177230000001969F
Tank No.	WHS1 (Lube Warehouse 1)	Date of Sampling	23.09.2023 21:01:04
Type of the Sample	COMPOSITE	Date of Receipt of Sample	22.09.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	22.09.2023 To 22.09.2023
Batch No.	M1-23J0712	Date of Issue of the Report	23.09.2023 21:16:51
Stock Represented	325.000 EA	Sample Drawn By	KUMAR AJAY
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	ACIDITY, TOTAL	mgKOH/g	ASTM D974	MAX 1.50	0.51
2	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
3	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	0.8000 - 0.9500	0.8778
4	FLASH POINT, COC	°C	ASTM D92	MIN 210	244
5	EMULSION CHARACTERISTICS AT 54°C/20 MIN	-	ASTM D1401	NOT WORSE THAN 40-37-3 (20)	40-37-3 (20)
6	FOAM STABILITY SEQUENCE I	mL	ASTM D892	0 - 0	0
7	FOAM STABILITY SEQUENCE II	mL	ASTM D892	0 - 0	0
8	FOAM STABILITY SEQUENCE III	mL	ASTM D892	0 - 0	0
9	KINEMATIC VISCOSITY AT 100°C	cSt	ASTM D7042	TO REPORT	8.660
10	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	62.00 - 74.00	67.88
11	POUR POINT	°C	ASTM D97	MAX 0	-6
12	VISCOSITY INDEX	-	ASTM D2270	MIN 90	99
13	ZINC CONTENT	%Wt	ASTM D6443	0.026 - 0.070	0.032
14	RUST TEST AT 60°C, 4 HOURS, SSW	-	ASTM D665	PASS	PASS

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
WARANG CHANDRAKANT PRABHAKAR (30074520)

Reviewed and Authorised By:
WARANG CHANDRAKANT PRABHAKAR
(30074520)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) Entire quantity of sample expended during testing.
6) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
7) This is a system generated test report. Hence, it does not require signature.

