

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**PARTHAN EP - 460 (210 L)(0707241)**

Laboratory Serial No.	FB - 1794	Sample Drawn By	OPERATION OFFICER
JDE Serial No	1222216	Date Sample Drawn	17/02/23
Batch No / Lot No	M2-23-B-306	Date Received In Lab	17/02/23
Work Order No	1023729	Date Tested	18/02/23
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name	14546	Mazgaon TML Lubes-(STP 0101)	Sampling Plan
			IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	APPEARANCE	.	VISUAL			CLEAR
2	ASH	%Wt	IS1448 (P4)	-	.100	.087
3	DENSITY@29.5°C	gm/cc	P16, ASTMD1298, D4052 ,D7042	-	-	.8977
4	FLASH POINT,COC	°C	IS1448(P69), ASTMD 92	230	-	262
6	FOAMING TEST SEQ1	Milliliter	IS1448 (P 67), ASTMD 892		100/0	0/0
7	FOAMING TEST SEQ2	Milliliter	IS1448 (P 67), ASTMD 892		50/0	20/0
8	FOAMING TEST SEQ3	Milliliter	IS1448 (P 67), ASTMD 892		100/0	0/0
9	RUST TEST A/B	.	IS1448(P96), ASTM D 665			PASS
5	EMULSION TEST @ 82°/30MIN	Milliliter	IS1448 (P 91),ASTM D1401	40-40-0	-	40-40-0
10	KV@40°C	cSt	IS1448(P25), ASTMD445,D7042	440.0	475.0	463.4

Remarks : Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:
DALVI P Y(30044160)