



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
MAZGAON LUBE PLANT
HAY BUNDER ROAD, MAZGAON
MUMBAI - 400033, MAHARASHTRA
LABORATORY TEST REPORT



Product	0706241 (HP PARTHAN EP 220 - DRUM 210L (0.9 MM))	Test Report Number	4546232401517
Loc/ Customer/ Supplier	4546 (MAZGAON TML LUBES)	Sample Number	40000002930
Process/Purchase/Sales Order	10003166 4902293322 0001	Lab Sr. No	FB 596
Source of the Sample	DRUM	ULR Number	TC-5177230000001517F
Tank No.	WHS1 (Lube Warehouse 1)	Date of Sampling	06.09.2023 13:48:58
Type of the Sample	COMPOSITE	Date of Receipt of Sample	04.09.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	04.09.2023 To 04.09.2023
Batch No.	M1-23J0564	Date of Issue of the Report	06.09.2023 15:02:54
Stock Represented	469.000 EA	Sample Drawn By	QC OFFICER
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	APPEARANCE	-	VISUAL	CLEAR	CLEAR
2	ASH	%Wt	ASTM D482	MAX 0.10	0.05
3	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	TO REPORT	0.8884
4	FLASH POINT, COC	°C	ASTM D92	MIN 220	268
5	EMULSION CHARACTERISTICS AT 82°C/30 MIN	-	ASTM D1401	NOT WORSE THAN 40-40-0 (20)	40-40-0 (20)
6	FOAM CHARACTERISTIC SEQUENCE I	-	ASTM D892	100/0	10/0
7	FOAM CHARACTERISTIC SEQUENCE II	-	ASTM D892	50/0	20/0
8	FOAM CHARACTERISTIC SEQUENCE III	-	ASTM D892	100/0	10/0
9	PHOSPHORUS CONTENT	%Wt	ASTM D6443	0.0098 - 0.0145	0.0112
10	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	210.00 - 240.00	210.2
11	RUST TEST AT 60°C, 4 HOURS, SSW	-	ASTM D665	PASS	PASS

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
PAKALE SANTOSH BHIKAJI (38031160)

Reviewed and Authorised By:
PAKALE SANTOSH BHIKAJI (38031160)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
6) This is a system generated test report. Hence, it does not require signature.

