



HINDUSTAN PETROLEUM CORPORATION LIMITED
(A Government of India Enterprise)
QUALITY CONTROL LABORATORY
SILVASA LUBE PLANT
KHANVEL UDVA ROAD, KHERDI
SILVASSA - 396230, DADRA AND NAGAR HAVELI



LABORATORY TEST REPORT

Product	0254008 (HP ENKLO 68 - DRUM 210L HDPE)	Test Report Number	4512232400843
Loc/ Customer/ Supplier	4512 (SILVASA LUBE TML)	Sample Number	40000003254
Process/Purchase/Sales Order	10005778 4902569232 0001	Lab Sr. No	FB 492
Source of the Sample	DRUM	ULR Number	TC-6943230000000843F
Tank No.	WHS (WAREHOUSE)	Date of Sampling	14.09.2023 12:39:31
Type of the Sample	COMPOSITE	Date of Receipt of Sample	12.09.2023
Number/Quantity of Sample	1*1 L	Date(s) of Sample Testing	12.09.2023 To 14.09.2023
Batch No.	SI-23J0607	Date of Issue of the Report	18.09.2023 16:29:04
Stock Represented	150.000 EA	Sample Drawn By	VATSAL PAJVANI
Test Required	FB		
Sampling Plan/Method	IS 1447	Seal No.	Wooden Box Seal
Reason for Testing	PRODUCTION - DRUM		Aluminium Box Seal

S.No	Characteristics	UOM	Test Method	Specifications	Result
1	ACIDITY, TOTAL	mgKOH/g	ASTM D974	MAX 1.50	0.52
2	APPEARANCE	-	VISUAL	BRIGHT AND CLEAR	BRIGHT AND CLEAR
3	DENSITY AT 29.5°C	g/cm ³	ASTM D7042	0.8000 - 0.9500	0.8767
4	FLASH POINT, COC	°C	ASTM D92	MIN 210	248
5	EMULSION CHARACTERISTICS AT 54°C/20 MIN	-	ASTM D1401	NOT WORSE THAN 40-37-3 (20)	40-37-3 (20)
6	FOAM STABILITY SEQUENCE I	mL	ASTM D892	0 - 0	0
7	FOAM STABILITY SEQUENCE II	mL	ASTM D892	0 - 0	0
8	FOAM STABILITY SEQUENCE III	mL	ASTM D892	0 - 0	0
9	KINEMATIC VISCOSITY AT 100°C	cSt	ASTM D7042	TO REPORT	8.178
10	KINEMATIC VISCOSITY AT 40°C	cSt	ASTM D7042	62.00 - 74.00	62.71
11	POUR POINT	°C	ASTM D97	MAX 0	-3
12	VISCOSITY INDEX	-	ASTM D2270	MIN 90	97
13	ZINC CONTENT	%Wt	ASTM D6443	0.026 - 0.070	0.030
14	RUST TEST AT 60°C, 4 HOURS, SSW	-	ASTM D665	PASS	PASS

Remarks : The Sample meets the Specification in the above tested parameters only.

Tested By:
PAL TAPAS (31988540)

Reviewed and Authorised By:
PAL TAPAS (31988540)

Note:
1) The sample is drawn by client and results apply to the sample as received.
2) The test report shall not be reproduced except in full without prior written approval of the Lab In-charge.
3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
4) Test results reported are valid for the sample tested, which was provided at the time of testing.
5) Entire quantity of sample expended during testing.
6) The details of sample submitted is provided by sender / customer. The authenticity / correctness of the submitted data is the responsibility of the sender/customer.
7) This is a system generated test report. Hence, it does not require signature.

