

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 68 (210 L)(0254241)**

Laboratory Serial No.	FB 764	Sample Drawn By	OPNS OFFICER
JDE Serial No	1220345	Date Sample Drawn	29/06/22
Batch No / Lot No	SI-23-B-133	Date Received In Lab	29/06/22
Work Order No	1021488	Date Tested	29/06/22
Tank /Kettle/Location	WHS	Particular of Sample	DRUM
Plant Code/ Name		Sampling Plan	IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
14	ZINC	%Wt	ASTM D6443, EDTA	.026	.070	.029
14	ACIDITY TOTAL	mg KOH/g	IS1448 (P2), ASTM D974, D664	-	1.50	.52
14	APPEARANCE	.	VISUAL	B&C	B&C	B&C
14	DENSITY@29.5°C	gm/cc	IS1448(P16), ASTMD1298, D 4052	.8000	.9500	.8815
14	EMULSION CHAR @ 54°C , 20MIN	Milliliter	IS1448(P91), ASTM D1401	40-40-0	40-37-3	40-37-3
14	FLASH POINT,COC	°C	IS1448(P69), ASTM D92	210	-	242
14	FOAM STABILITY ,SEQ 1	Milliliter	IS1448(P67), ASTM D892	0	0	0
14	FOAM STABILITY , SEQ 2	Milliliter	IS1448(P67), ASTM D892	0	0	0
14	FOAM STABILITY, SEQ 3	Milliliter	IS1448(P67), ASTM D892	0	0	0
14	KV @ 100 ° C	cSt	IS1448(P25), ASTM D445, D7042	-	-	8.885
14	KV @ 40 ° C	cSt	IS1448(P25), ASTM D445, D7042	62.00	74.00	71.56
14	POUR POINT ° C	°C	IS1448(P10), ASTM D97	-	0	-9
14	RUST TEST SYNTHETIC SEA WATER	.	IS1448(P96), ASTM D665	P	P	P
14	VISCOSITY INDEX (VI)	.	IS1448 (P56), ASTM D2270	90	-	96

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by:

AGARWALLA PRIYANKA(31960370)