

HINDUSTAN PETROLEUM CORPORATION LIMITED

(A Government of India Enterprise)

QUALITY CONTROL LABORATORY

MAZGAON TERMINAL

LUBE PLANT, HAY BUNDER ROAD, MAZGAON

MUMBAI,400033

LABORATORY TEST REPORT**ENKLO 460 (210 L)(0804241)**

Laboratory Serial No.	FB 1382	Sample Drawn By	QC OFFICER
JDE Serial No	1200204	Date Sample Drawn	26/11/22
Batch No / Lot No	M2-22-L-811	Date Received In Lab	26/11/22
Work Order No	999732	Date Tested	26/11/22
Tank /Kettle/Location	WHS2	Particular of Sample	DRUM
Plant Code/ Name		Sampling Plan	IS 1447

Test Line Number	Test Description/ Characteristics	Units	Test Method	Specifications		Result Value
				Min	Max	
1	ENKLO 460 ZINC	%Wt	P 77 D 4628 EDTA D 6443	.026	.070	.034
2	ENKLO 460 ACIDITY TOTAL	mg KOH/g	P 1 D 974 IP 139	-	1.50	.58
3	ENKLO 460 APPEARANCE	Visual	VISUAL	B&C	B&C	B&C
4	ENKLO 460 FLASH POINT	°C	P 69 D 92 IP 36	230	-	262
5	ENKLO 460 K V @ 100	cSt	P 25 D 445 IP 71	-	-	31.5
6	ENKLO 460 K V @ 40	cSt	P 25 D 445 IP 71	430.00	500.00	474.00
7	ENKLO 460 POUR POINT	°C	P 10 D 97 IP 15	-	0	-3
8	ENKLO 460 COP STRIP COR@ 100	ASTM		-	1	1
9	ENKLO 460 DENSITY@29.5	gm/cc	P 16 D 1298 IP 160	-	-	.8965
10	ENKLO 460 FOAM STAB SEQ1	Milliliter	P 67 D 892 IP 146	-	0	0
11	ENKLO 460 FOAM STAB SEQ2	Milliliter	P 67 D 892 IP 146	-	0	0
12	ENKLO 460 FOAM STAB SEQ3	Milliliter	P 67 D 892 IP 146	-	0	0
13	ENKLO 460 FOAM TEND SEQ1	Milliliter	P 67 D 892 IP 146	-	-	0
14	ENKLO 460 FOAM TEND SEQ2	Milliliter	P 67 D 892 IP 146	-	-	10
15	ENKLO 460 FOAM TEND SEQ3	Milliliter	P 67 D 892 IP 146	-	-	0
16	ENKLO 460 R.TST 24HRS DIST WAT	.	P 96 D 665 IP 135	P	P	P
17	ENKLO 460 VISCOSITY INDEX	.	P 56 D 2270 IP 226	90	-	97

Remarks : Emulsion Test :40-40-0 Sample meets the specification in above tests.

Note:

- 1) The report refers only to the sample tested.
- 2) The test report shall not be reproduced except in full without prior written approval of the Lab Incharge.
- 3) This test report shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of Laboratory.
- 4) Test results reported are valid at the time of testing
- 5) This is a system generated test report and hence does not require signature.

Reviewed and Authorized by: